

From: George Dick
To: INTERNET:joseph.bauer@exeloncorp.com
Date: Thu, Jan 25, 2001 7:56 AM
Subject: Appendix G & H Questions

Joe,

Please see attached questions regarding compliance with 10 CFR Appendixes G and H for the power uprate request for Byron and Braidwood.

George

CC: Chia-Fu Sheng, Mahesh Chawla

Mail Envelope Properties

(3A702290.527 : 22 : 21110)

Subject: Appendix G & H Questions
Creation Date: Thu, Jan 25, 2001 7:56 AM
From: George Dick

Created By: OWFN_DO.OWF4_PO:GFD

Recipients	Action	Date & Time
Post Office INTERNET bauer (INTERNET:joseph.bauer@exeloncorp.c	Transferred	01/25 7:57 AM
Post Office OWFN_DO.owf2_po SHENG CC (Chia-Fu Sheng)	Delivered Opened	01/25 7:57 AM 01/25 8:29 AM
Post Office OWFN_DO.owf4_po MLC CC (Mahesh Chawla)	Delivered Opened	01/25 7:56 AM 01/25 9:32 AM
Domain.Post Office INTERNET INTERNET:exeloncorp.com:joseph	Delivered	Route
OWFN_DO.owf2_po	01/25 7:57 AM	OWFN_DO.owf2_po
OWFN_DO.owf4_po	01/25 7:56 AM	OWFN_DO.owf4_po

Files	Size	Date & Time
AppendixG&H questions.wpd	6596	Thursday, January 25, 2001 7:55 AM
MESSAGE	768	Thursday, January 25, 2001 7:56 AM

Options

Auto Delete: No
Expiration Date: None
Notify Recipients: Yes
Priority: Standard
Reply Requested: No
Return Notification: None

Concealed Subject: No
Security: Standard

To Be Delivered: Immediate
Status Tracking: Delivered & Opened

QUESTIONS RELATING TO THE
REQUEST TO AMEND THE OPERATING LICENSE
FOR THE BYRON AND BRAIDWOOD, UNITS 1 AND 2:
POWER UPRATE REQUEST

**Questions Regarding Compliance with 10 CFR Part 50, Appendix G,
and 10 CFR Part 50, Appendix H**

1. The licensee's response provides actual data to support the revised higher USE values for certain RPV welds. However, the reference was simply stated as "Record of Filler Wire Qualification Test." Confirm that the "Record of Filler Wire Qualification Test" is just a different name for "Weld QTR" that was used in a previous submittal (ComEd letter of 11/19/93). Otherwise, the licensee needs to address differences, if any, in welding procedure and stress relief of the filler wire qualification test specimen and the actual RPV welds and assess their impact to the USE values. In addition, please address the staff comments in the following table to justify the use of the revised initial USE values proposed for the power uprate. The pages referenced in the "Staff Source" column refer to the 11/19/93 submittal.

Unit	Weld ID and Heat	USE (RVID)	Staff Source	Comment	USE (Uprate)
Byron 1	WF336 (442011)	74	Page 13	To abandon your previous conservative approach, you need to demonstrate that the USE of 78 ft-lb from "Weld QTR" were from three specimens. Otherwise, you need to use the average value of 78 and 74 reported on Page 13.	77
Byron 2	WF447 (442002)	67	Page 15	The document stated, "The source of the 80 ft-lb value is undetermined."	80
	WF562 (442011)	70	Page 15	The document cited WCAP-12685 for this information.	80
Braid-wood 1	WF562 (442011)	70	Page 10	To abandon your previous conservative approach, you need to demonstrate that the USE of 78 ft-lb from "Weld QTR" were from three specimens. Otherwise, you need to use the average value of 78, 70, and 71, reported on Page 10.	80
Braid-wood 2	WF562 (442011)	70	Page 10	Same as above	80

2.

The heatup curves are less conservative than those calculated by the staff by more than 10 F° at high pressure. An additional examination by the staff indicated that the heatup curve generated by P-T Calculator of EPRI agrees with the staff's values. To resolve this discrepancy, provide the detailed calculation for the heatup curve (100 F°/hour) at high pressure (say 1500 psi) for Byron Unit 1.