

## 5. LOSS OF COOLANT ACCIDENT (LOCA) TESTING OF CABLES

During the design life of a nuclear power plant, cables used to operate safety-related equipment must be capable of delivering electric power, controlling equipment, and transmitting data to prevent and mitigate the consequences of an accident. To ensure this, the environmental qualification process simulates the postulated accident environments, which include simultaneous exposure to radiation, steam, thermal, and possibly, chemical sprays (PWR) or deionized water sprays (BWR). The cables are generally pre-aged or pre-conditioned, in most cases, to an equivalent age of 40 years (i.e., the original license period of a nuclear power plant) before their exposure to these accident conditions. IEEE Std 323-1974 (Ref. 5.1) describes the principles, procedures, and methods for qualifying Class 1E equipment, such as cables. Its daughter standard, IEEE Std 383-1974 (Ref. 5.2) delineates specific details on qualification parameters applicable to cables. The IEEE Std 323-1974 is endorsed by the NRC in Regulatory Guide 1.89, Rev. 1 (Ref. 5.3) and its guidance meets the requirements of 10CFR50.49 (Ref. 5.4). The Regulatory Guide recognizes that qualification may be accomplished in several ways, i.e., through type testing, operating experience, analysis, or a combination of these methods. Most cable qualifications are type tested, by subjecting the cables to the environments and operating conditions for which they are designed.

Qualification by testing is satisfied only when the cables to be tested are aged (except those qualified to older requirements, DOR Guideline, NUREG-0588/Category II), subjected to potential environmental influences, and operated under post-accident conditions to provide reasonable assurance that they can perform their intended functions for a specified time. One of the practical difficulties encountered in early development of the qualification process was to apply all test environments simultaneously. In particular, radiation testing usually was done sequentially and separately from the other environments. A typical qualification test consisted of the following sequence:

- thermal aging equivalent to a 40-year service life
- gamma radiation which simulates the effect of 40-year ambient radiation plus that released by the accident (e.g., typically a LOCA event)
- steam/chemical-spray exposure which simulates the non-radiation portions of a LOCA.

Such tests are referred to as sequential-exposure tests, or simply, sequential tests. In a few cases, simultaneous-exposure tests were conducted which consisted of the following exposures:

- combined accelerated thermal and radiation aging
- combined radiation-, steam-, and chemical spray-exposure simulating a LOCA.

Although the sequential test is not as realistic as the simultaneous test, intuitively it is conservative, primarily because the cables are thought to be more degraded (after exposure to radiation) when they are exposed to severe thermal transients and high temperatures of the steam/chemical-spray exposure than they are in a simultaneous test at the start of the combined exposure. Because sequential tests are intuitively conservative and are substantially less expensive than simultaneous tests, most qualification programs have been sequential<sup>1</sup>. In addition to these qualification tests, SNL has built facilities to perform EQ-related research where any combination of sequential and simultaneous procedures are simulated to verify these contentions.

Since its inception in 1975, the Qualification Testing Evaluation (QTE) Program at SNL has outlined and performed research on a number of broad issues in the EQ process, including both aging and accident

---

<sup>1</sup>According to Dr. S.P. Carfagno, Franklin Research Center (FRC) performed several simultaneous simulation tests for cable manufacturers (i.e., Anaconda, Kerite, Boston Cables, Rockbestos, Okonite). Tests were conducted at a special test facility built by FRC at Isomedix.

simulation methods (Ref. 5.5). Recently, the EQ-Risk Scoping Study used the probabilistic risk assessment (PRA) techniques to assess the impact of various EQ requirements on plant risk and to identify any needed modifications to the current EQ practices to reduce the risk or its uncertainties stemming from lacking of qualification of safety-related equipment (Ref. 5.6). The study suggested that (1) EQ should focus on assuring equipment's operability for the first few days of the accident rather than over a long term, (2) operability of the equipment during steam conditions is more important than during irradiation<sup>2</sup>, (3) the equipment's reliability might increase the estimates of core damage frequency, and (4) instrumentation and control devices for accident management and plant status indicators are important, although it is difficult to assess their impact from the PRA techniques. To date, PRA techniques have not played a role in EQ. Therefore, the uncertainties and the differences among various test conditions and parameters associated with the qualification for accident conditions are discussed in this section.

Table 5.1 summarizes typical EQ requirements for the qualification of electric cables in several countries including the United States<sup>3</sup>, for both aging and accident simulation requirements. Some details on test durations, chemical sprays, and post-design basis are not available. Nevertheless, this comparison of requirements in different countries with nuclear programs provides a basis for the results presented in this literature review which includes studies from the U.S. and abroad. Significant differences exist in the total radiation doses and dose rates used during both aging and accident irradiation. Some irradiations were performed at room temperature and others at elevated temperatures. Based on the information presented in the previous section, irradiation at elevated temperatures can degrade certain organic materials significantly when compared to irradiation at room conditions. Another area with large variations is in the definition of the accident steam conditions (e.g., pressure and temperature profiles) and their durations. Since these accident conditions are specific to the design of a plant, such variation from plant to plant, and hence, from country to country can be possible. However, the variation in the duration of an accident transient for different countries is noteworthy.

As indicated in Table 5.1, the total radiation doses used in qualification testing vary from as low as 4Mrad to 50Mrad for aging, and 20Mrad to 150Mrad for accidents (except for Spain where the LOCA radiation values are uncertain). Results from one nuclear power plant (Ref. 4.12) presented in the previous section indicated that with the exception of hot spots, the majority of cables inside the containment are exposed to an TID of 10 Mrad during 40 years of design life. Also, based on results from the TMI accident discussed in this section, the TID absorbed by cables during that accident was less than 12 Mrad. This disparity between actual plant data and typical qualification values, specifically in U.S., may need further examination of the current EQ requirements.

In early years, most of the industry's qualification as well as research tests, were conducted at the Franklin Institute Research Laboratories (FIRL), Philadelphia. Over the last two decades, significant research was carried out at Sandia National Laboratory (SNL) sponsored by the NRC (Ref. 5.7). The following four major facilities were built to simulate the environmental qualification conditions: Low-Intensity Cobalt Array (LICA), High-Intensity Adjustable Cobalt Array (HIACA), I-Steam, and V-Steam with transient superheat capability.

---

<sup>2</sup> Note that LOCA testing results have indicated radiation causing more degradation than steam exposure. In fact, for certain insulation materials, steam conditions had enhanced cable's elongation properties. However, most cable failures were reported during the saturated steam exposure (i.e., post-transient duration) of the LOCA testing.

<sup>3</sup>Personal communication with Mr. D.J. Stonkus of DJS Associates.

Table 5.1 Typical EQ Requirements for Cables Used in Different Countries (Mr. D.J. Stonkus)

Country	Aging Simulation			LOCA Simulation						Post-Design Basis
	Thermal	Radiation	Comments	Radiation	Steam Conditions (extremes)	Chemical Spray	Durations (Hours)		Comments	
							Transient	Post-Transient		
USA	168 hrs @150°C(air)	50 Mrad @≤1Mrad/hr	Irradiation at room temp.	150 Mrad @≤1Mrad/hr (room temp.)	174°C@880kPa 100°C@100kPa	Boron Sol. pH 10.5	96	624	Total 30-day LOCA test	93°C @ 100% RH for 100 days
UK	240 hrs @150°C(air)	20 Mrad @≤0.3Mrad/hr	Irradiation at 90°C	30 Mrad @≤0.3Mrad/hr (90°C)	200°C@490kPa 50°C@100kPa	Boron Sol. pH 8.5	22.4+	n/a	none	100°C @215kPa Duration based on activation energy
France	950 hrs @135°C(air)	25 Mrad @0.05-0.15Mrad/hr	Irradiation at 70°C	60 Mrad @0.15-0.75Mrad/hr (70°C)	157°C@560kPa	Yes	96	n/a	none	n/a
Germany	240 hrs @135°C(air)	5 Mrad @0.05Mrad/hr	none	20 Mrad @0.05Mrad/hr	180°C to 100°C 50°C	Yes	241	n/a	none	400 hours
Japan	168 hrs @121°C(air)	50 Mrad @≤1Mrad/hr	Irradiation at room temp.	150 Mrad @≤1Mrad/hr	150°C	Yes	n/a	n/a	none	n/a
Canada	31years life based on Arrhenius	20 Mrad @≤1Mrad/hr	none	30 Mrad @≤1Mrad/hr (room temp.)	115°C@196kPa 65-40°C	Boric acid pH 10	12	n/a	Negative steam press. for 6 hours	90days @40°C and 100% RH
Italy	n/a	35 Mrad	Irradiation at 57°C	18Mrad γ and 27Mrad β	130°C@280kPa 80°C@100kPa	Yes	12	n/a	none	100 days @ 50°C
Belgium	40years life @90°C based on Arrhenius	50 Mrad @≤1Mrad/hr	Irradiation at 30°C	150 Mrad @≤1Mrad/hr (30°C)	180°C@1000kPa 120°C@100kPa	Boron Sol. pH 10.5-11	504*	n/a	none	1 year @ 70°C
Spain	n/a	n/a	none	5380 Mrad γ & 714 Mrad β (?)	165°C 57°C	n/a	24	100 days*	Total radiation 175-350 Mrad(?)	n/a
Brazil	n/a	4 Mrad @≤1Mrad/hr	none	200 Mrad	149°C@467kPa 122°C@215kPa	Boric acid pH 8-8.5	240*	n/a	none	n/a

NOTES: \* Presumably these numbers represent total LOCA duration including transient and post-transient durations. n/a = not available  
Accident radiation doses for Spain are uncertain.

In addition to verifying industry's claims on the current qualification requirements, the goals of this research were to understand the effects of each of the environmental conditions and any of their synergistic effects. Additional studies were carried out on oxygen effects, post-accident environments and their durations, sensitivity to aging methods, post-accident tests, and comparisons were made with actual accidents (e.g., TMI).

## 5.1 Simultaneous/Sequential Exposures

Bonzon (Ref. 5.8) reported test results on nine generic LOCA type tests conducted on electric cables, cable-connector assemblies, and cable field-splice assemblies, including sequential and simultaneous exposures to LOCA radiation, steam, and chemical sprays. For all tests, saturated steam conditions (without air) were employed. The materials tested were EPR/CSPE, XLPE/XLPE, Neoprene/Neoprene, and XLPE/no jacket. The cables showed no obvious synergistic effects in either the electrical or material properties. Some of the conclusions from this study were: (1) elongation is an inverse function of total radiation dose, (2) radiation is a principal mechanism of damage in the LOCA type test environment<sup>4</sup>, (3) there is no correlation between the extent of damage and the type of test (sequential or simultaneous), (4) in terms of elongation, all cables failed at the bend area, (5) although all cables failed at the bend area, visual examination would not necessarily reveal the failure or the relative failure, and (6) there was no significant difference in the response of the cable types tested.

Tensile specimens of two compounds of typical radiation-crosslinked, highly flame-retardant polyolefins were tested under sequential and simultaneous conditions; Table 5.2 summarizes the results. One general comment that can be made is that the effect of aging is apparent, and the pre-aged samples are more severely degraded than those that were not pre-aged by the manufacturers. It may be noted that the radiation doses were low by comparison with the values used in typical cable qualification programs.

The compound B data shows that increasingly severe degradation correlates well with the increasingly severe environment or environments. The normalized elongations are almost identical from both environment conditions, indicating no synergisms exist.

The NUREG also reported on FIRL's study (Ref. 5.9) of their own 1969-1977 historical data to determine the synergistic effects resulting from simultaneous applications of radiation, steam, and chemical spray during qualification of safety-related electric cable. Among the 49 test programs examined, only a single pair of tests (one sequential and one simultaneous) met certain basic requirements for synergistic comparison; i.e., that the cable specimens and the accident test profiles are essentially the same in both tests. The cables were multiconductor 600 Vac control cables with primary insulations of flame-resistant XLPE, EPR, and SR. The outer jackets consisted of flame-resistant Neoprene and silicone-saturated asbestos.

All of the cables in the sequential test exposure maintained their electrical load during the 30-day steam and chemical-spray exposure, whereas in the simultaneous test, none maintained their loads beyond 13 days. Two of the three cables used in the simultaneous test program failed before the LOCA exposure. An analysis of these two tests revealed significant differences in cable handling, thermal aging conditions, and gamma-irradiation dose rates. These differences might account for the fact that all three cables in the simultaneous test failed, whereas none failed in the sequential test. Because of these uncertainties, this comparison was not regarded by the authors as a clear source of information on synergisms.

---

<sup>4</sup> see footnote #2 on page 5-2.

**Table 5.2 Comparison of Sequential and Simultaneous LOCA Test Data on Two Compounds (A and B) of Radiation-XLPO Insulation Samples (Ref. 5.8)**

Conditioning Sequence	Radiation Dose Range (Mrads)	e/e <sub>0</sub>							
		Sequential				Simultaneous			
		A	P-A	B	P-B	A	P-A	B	P-B
Aging	-	.39	.58	.94	.59				
Aging	5-8.5					.58	.57	.92	.58
Aging+LOCA	-	.59	.47	.40	.19				
Aging+LOCA	20.5-38.5					.46	.38	.26	.30
Aging+Radiation	38-95	.16	.14	.46	.31				
Aging	10.5-18.5					.70	.43	.83	.58
Age+Rad.+LOCA	38-95	.30	.24	.27	.13				
Aging+LOCA	45.5-78.5					.30	.26	.21	.24
Radiation	12-31	.86	.48	.92	.47				
Radiation+LOCA	12-31	.55	.32	.38	.18				
LOCA	15.5-30					.53	.36	.30	.21
LOCA	-	.81	.39	.44	.27				
LOCA	35-60					.38	.26	.28	.24

**Notes:**

1. Initial percent ultimate elongation for A and B was 530% and 468%, respectively
2. Radiation dose varies from top(1st figure) to bottom (2nd figure) of sample
3. All values are the average of 3 tests
4. P-A/P-B: Pre-aged samples received additional thermal aging of 168 hrs at 175°C
5. Sequential: Thermal 130°C/5 days-Ambient Radiation at 1 Mrad/h (Aging+Accident) -LOCA(Steam+Chemical)  
Simultaneous: (Thermal(130°C/5days)+Radiation at .2 Mrad/h) - (Accident Rad. + (LOCA) Steam +Chem.)

Bustard (Ref. 5.10) discussed the electrical and mechanical properties of seven commercial EPR materials subjected to three simulations of pre-aging and accident conditions. One set of cables and separate tensile specimens underwent accelerated thermal aging (140°C for 168 hours), then irradiation to a combined aging and LOCA total dose of ~160-170 Mrad (at ~.75 Mrad/hr), and then steam exposure (saturated) for 4 days with 17 additional post-transient days. For a second and third set of cables and separate tensile specimens, simultaneous applications of elevated temperature (~140°C for 168 hours) and radiation (~40-45 Mrad at .35 Mrad/hr) were used for pre-aging, followed by simultaneous exposure of accident radiation (.8 Mrad/hr for

Mrad/hr) were used for pre-aging, followed by simultaneous exposure of accident radiation (.8 Mrad/hr for 4 days followed by much lower dose rates for the remaining 17 days of post-transient exposure; total accident dose of ~105-115 Mrads), and steam exposures to simulate accident environments. In all three simulations, saturated steam conditions (without air) were employed but no chemical sprays. The cable samples included both single and multiconductor specimens. Reference 5.11 summarizes the results from three similar sets of accident simulation tests applied to three commercial XLPO insulation materials.

Except for the EPR-D cables, leakage currents were comparable (0.6-1.9 mA) for simultaneous and sequential testing. For multiconductor EPR-D cables, there was a significant difference in leakage current between sequential (1.2 mA) and simultaneous exposures (#1:180-750 mA; #2:150-550 mA). Surprisingly, the electrical properties for EPR-D single conductors remained small (<1.0 mA) for all LOCA conditions. Periodic measurements of insulation resistance (Figure 5.1) throughout the LOCA simulation indicated that electrical degradation of the EPR-D multiconductor began several days after the start of the simultaneous LOCA simulation. EPR-D insulation also exhibited substantial dimensional swelling, more, in fact, than any of the EPR or XLPO materials. The dimensional swelling was more severe with simultaneous exposure.

Bustard (Ref. 5.10) suggested that the substantial absorption of moisture and dimensional changes produced mechanically damaged the EPR-D multiconductors leading to their electrical degradation. It was hypothesized that dimensional swelling of the insulation caused buildup of stresses within the multiconductor geometry. When the jacket split to relieve the stress, the sudden release of constrictive force on the insulation may have caused it to crack or breakup. Alternatively, sections of the insulation which adhered to the jacket during splitting were pulled away from the conductor. Bare copper conductors, observed at the completion of simultaneous testing are suggestive of such a process. The report also presents two additional hypotheses which are less acceptable. One relates to chemical interactions of the jacket and insulation such as evolution of HCL from the jacket and its interaction with the EPR-D insulation. The other relates to dimensional swelling of the EPR-D single conductors spirally wound around each other in a multiconductor geometry, resulting in the buildup of stresses.

Table 5.3 shows data on the tensile property for EPR-A after aging and sequential LOCA irradiation testing for a variety of aging sequences (compare, Table 4.6). Those samples which degraded significantly after aging simulations, also degraded significantly after the LOCA steam exposure. Table 5.4 shows the wide variation in the tensile properties of different EPR samples. Also, the tensile properties do not predict electrical degradation for multiconductor cables (see EPR-D data). Sequentially exposed EPR-D multiconductors performed substantially better electrically than did simultaneously exposed ones, even though the former's insulation tensile properties were equally degraded by the end of test.

Table 5.5 gives the results from the same study for the EPR-1483 material. There were six different aging simulations (as defined in Table 4.6) followed by three distinct LOCA conditions; steam only, sequential radiation followed by steam, and finally, simultaneous radiation and steam. This particular material degraded to a range of 0.32-0.47 in its elongation at break values after aging, suggesting that there is very little effect on aging degradation under various simulation procedures. On the other hand, the LOCA responses to these pre-aged specimens vary significantly from one LOCA simulation to another. In regard to their relative variations in elongation data after different aging simulations, all aged specimens under each LOCA conditions responded similarly. However, the increase in weights during each LOCA simulation shows significant variation from one pre-aged specimen to another. Samples aged simultaneously have significantly higher weight increases than those exposed to sequential aging conditions.

Based on the test results on EPR cables, the report concluded that single conductor specimens should not be used to establish qualification for multiconductors. Both jacket-insulation interactions and the helicity of multiconductor geometries need to be considered in a qualification program. Since there is a large variation in EPR behavior, generic EPR responses should be avoided. The qualification tests should correlate test conditions to actual installed conditions (e.g., bends). Also, no final conclusion on the simulation technique (simultaneous or sequential) could be made for this material.




Figure 5.1 Insulation resistance for EPR-D multiconductor cable #2 during simultaneous test #2 (Ref. 5.10)

Table 5.3 Relative Tensile Properties of EPR-A after Aging and Sequential LOCA Irradiation  
(Ref. 5.10)

Aging Method	After Aging		After Sequential Accident Irradiation	
	Ultimate Tensile Elongation $e/e_0$	Ultimate Tensile Strength $T/T_0$	Ultimate Tensile Elongation $e/e_0$	Ultimate Tensile Strength $T/T_0$
Unaged	$1.00 \pm .08$ (360 $\pm$ 30%)	$1.00 \pm .03$ 8.7 $\pm$ 0.3 MPa)	$.32 \pm .04$	$.65 \pm .03$
4 d T + R	$0.88 \pm .08$	$0.98 \pm .06$	$.26 \pm .03$	$.61 \pm .05$
30 T + R	$< .03^*$	$\sim 0.2^*$	**	**
28 d T + 28 d R	$0.33 \pm .04$	$0.85 \pm .03$	$.18 \pm .03$	$.59 \pm .14$
28 d R + 28 d T **	$< .03^*$	$0.26 \pm .07^*$		**
28 d T + 55 h R	$0.31 \pm .04$	$0.99 \pm .21$	$.19 \pm .04$	$.64 \pm .06$
55 h R + 28 d T	$0.06 \pm .03$	$0.21 \pm .02$	$\sim .03$	$.18 \pm .01$
7 d T + R	$0.03 \pm .03$	$0.26 \pm .02$	$\sim .03^*$	$< .36^*$

NOTES: (1) Errors reflect one standard deviation of three measurements.  
 (2) Insulation thickness is nominally 0.8 mm.  
 \* Samples were extremely brittle and sometimes cracked in the pneumatic jaws used for the tensile measurements.  
 \*\* Samples were too brittle to measure.



Table 5.4 Tensile Properties of EPR After Aging and LOCA exposures (Ref. 5.10)

Material	e/e <sub>0</sub>			
	Sequential Test		Simultaneous Test #1	
	After Aging	After LOCA	After Aging	After LOCA
EPR-A	.29±.03	Uncertain	.05±.03	Uncertain
EPR-B	.37±.06	.20±.04	.28±.08	.14±.03
EPR-C	.38±.05	.13±.03	.58±.16	.15±.03
EPR-D	.41±.04	.06±.04	.19±.02	.13±.02
EPR-E	.34±.04	.05±.01	.49±.07	.19±.03

Table 5.5 LOCA Responses for EPR-1483 Material (Ref. 5.10)

Aging Conditions	After Aging (e/e <sub>0</sub> )	Steam Only			Sequential R-S			Simultaneous R+S		
		After 4 days (e/e <sub>0</sub> )	After LOCA (e/e <sub>0</sub> )	Weight Increase (%)	After 4 days (e/e <sub>0</sub> )	After LOCA (e/e <sub>0</sub> )	Weight Increase (%)	After 4 days (e/e <sub>0</sub> )	After LOCA (e/e <sub>0</sub> )	Weight Increase (%)
Unaged	1.00	0.96	1.02	-1	0.14	0.16	34	0.27	0.16	17
30d T + R	0.41	0.43	0.42	55	0.12	0.11	66	0.21	0.16	45
7d T + R	0.41	0.36	0.32	46	0.11	0.09	53	0.21	0.08	67
28d T-R(LDR)	0.47	0.42	0.44	5	0.11	...	...	0.23	0.16	22
28d T-R(HDR)	0.35	0.40	0.38	8	0.12	0.11	55	0.21	0.14	24
28d R-T(LDR)	0.41	0.43	0.46	12	0.12	0.11	63	0.22	0.16	30
28d R-T(HDR)	0.32	0.31	0.41	10	0.09	0.12	58	0.18	0.13	30

NOTES: LDR=Low dose rate (0.065Mrad/hr); HDR=High dose rate (0.85Mrad/hr); Aging+LOCA Radiation=175Mrad.

After 4 days=Post-transient; After LOCA=Post-LOCA; Weights were measured after LOCA.

7day T+R was performed at 0.29Mrad/hr and 139°C; 30d T+R was performed at 0.06Mrad/hr and 120°C. All other thermal aging was performed at 120°C.

Bustard (Ref. 5.11) presented the results for XLPO material from similar tests to those performed on EPR samples. XLPO-B was tested for all three test procedures (one sequential test, two simultaneous tests). XLPO-A and XLPO-C were tested for one of the simultaneous test program, in which both multiconductor and single conductor specimens were included for A and B, and multiconductor specimens for C. All thermal aging was done for 7 days at 139°C. An aging radiation dose of ~40Mrad and accident dose of ~110Mrad, with a total dose of approximately 150Mrad, were used. The LOCA included a 21-day exposure to saturated steam with 4 days of transient and 17 days of post-transient period; chemical spray was not used. XLPO-A and XLPO-C also were tested by the manufacturer for sequential conditions, including 7-day thermal aging conditions for XLPO-A at 150°C and that for XLPO-C at 136°C. Both were exposed to a total radiation dose of 200 Mrad before they were LOCA-tested for 30-day saturated steam conditions.

Bustard concluded that the electrical properties for XLPO-A and XLPO-B cables did not depend on whether single conductor or multiconductor was tested. The results for XLPO-B, which was exposed to all three test methods (aging and accident conditions for all three test methods were almost the same), indicated that there was no significant difference in the insulation resistance values between the three and that the testing technique did not impact the leakage current during post-test measurements. The electrical performances of XLPO-C during the simultaneous test and the sequential test performed by the manufacturers (with higher radiation doses and temperatures) were comparable.

Table 5.6 LOCA Responses for XLPO Materials (Ref. 5.11)

Material Specimens	Unaged Samples			Aged Samples			
	4d LOCA (e/e <sub>0</sub> )	16d LOCA (e/e <sub>0</sub> )	Weight Gain (%)	Aging (e/e <sub>0</sub> )	4d LOCA (e/e <sub>0</sub> )	16d LOCA (e/e <sub>0</sub> )	Weight Gain (%)
XLPO-A	0.30	0.23	10	0.58	0.25	0.16(60%)*	15
XLPO-B	0.50	0.41	32	0.79	0.42	0.30(96%)*	58
XLPO-C	0.47	0.30	37	0.64	0.29	0.17(56%)*	25

\* Values within bracket are absolute values of corresponding elongation at break.

Table 5.6 summarizes results from the simultaneous test sequence #2 for the three different XLPO materials. Aged samples absorbed more moisture than unaged samples except XLPO-C. It was suggested that XLPO-C underwent additional crosslinking during LOCA with a resultant reduction in moisture absorption. The weight and dimensional changes for these materials are substantially less than that observed for EPR-D whose jacket for multiconductor samples opened, presumably due to excessive dimensional changes during LOCA conditions.

Visually, the CSPE jacket on XLPO-C cables appeared substantially degraded by the simultaneous #2 test, consistent with the results from the previous study on EPR cables with an CSPE jacket. On the other hand, the CSPE jacket on XLPO-A showed no evidence of degradation after the same LOCA test. Thus, the degradation of this jacket material depends strongly on the specific manufacturer and cable product. Based on the manufacturer's data for XLPO-A and XLPO-C, sequential testing more severely degraded this jacket material than did simultaneous testing. Longitudinal and circumferential cracks were reported, as well as complete loss of the jacket from parts of the cable. The manufacturer's test was to high steam temperature (196°C versus 171°C) and the effect of this LOCA peak temperature has not been reported.

XLPO-B's Neoprene jacket also was substantially degraded by simultaneous test exposures compared with sequential testing. This was further verified by the Japanese tests (Refs. 5.12-5.14), discussed later, where more tensile degradation was observed for simultaneous than for sequential exposures.

The aging results in Reference 4.81 (see Section 4.3.3) were extended to include the influence of accident irradiation, steam, and chemical spray exposures on the behavior of pre-aged polymer samples. Both U.S. and French samples were tested at the French laboratories and the results were reported in Reference 5.15. The purpose of these tests was to observe the effect of the following factors on cable insulation materials during accident simulations: (1) the aging simulation method, (2) the order of accident simulation phases, (3)

the comparison of reference accident simultaneous or sequential simulation, (4) the temperature during accident-phase irradiation and, (5) the presence or absence of oxygen during the accident simulations.

The following four accident simulations were performed on each of the five groups of pre-aged French samples (A,B,C,D, Unaged: as explained in Section 4.3.3):

L1=R70-LOCA(air): Accident irradiation at 70°C, followed by thermodynamic and post-accident exposures with air.

L2=LOCA(air)-R70: Reverse of L1.

L3=R+LOCA(air): Simultaneous accident irradiation and thermodynamic exposures with air followed by a post-accident exposure with air.

L4=R28-LOCA(air): Same as L1, except accident irradiation at 28°C instead of 70°C.

Experimentally, the LOCA simulation included both a thermodynamic (steam and chemical spray) and post-accident exposures. Results on French materials are not presented in this section; however, the reference documents give details.

For U.S. samples pre-aged by the six methods (A,B,C,D,E, and F=Unaged: as explained in Section 4.3.3), the accident simulation cycles were as follows:

L5=R70-Steam(air): Same as L1.

L6=R70-Steam(N<sub>2</sub>): Same as L5, but air was replaced by nitrogen.

L7=R28-Steam(air): Same as L4.

L8=R28-Steam(N<sub>2</sub>): Same as L7, but air was replaced by nitrogen.

L9=R+Steam(air): Same as L3.

L10=R+Steam(N<sub>2</sub>): Same as L9, but air was replaced by nitrogen.

Experimentally, the LOCA simulation included both thermodynamic (steam and chemical spray) and post-accident exposures. The terminology LOCA(air) and Steam(air) refer to similar accident simulations. The average dose rate used in the French test program was approximately 300 krad/hr, and the irradiation time was calculated to obtain a maximum of 60 Mrad at the midpoint of each oven and each container. The vapor temperature, pressure, and chemical spray profiles were recommended by French nuclear safety organizations. Each test was comprised of two thermodynamic transients, followed by exposures to temperature, pressure, and chemical spray. During the second thermodynamic exposure, beginning 220 seconds after the start of the test, the sample were sprayed with borated solution (H<sub>3</sub>BO<sub>3</sub>=15 g/l and NaOH=6 g/l) at pH 9.25; the spray rate was 6.1 liters/min per square meter of horizontal section of the chamber, and lasted for 24 hours. After the LOCA exposure was over, the samples were exposed to 100°C and ~100% relative humidity for ten days.

Figures 5.2 to 5.13 show the results from this test program for the U.S. samples only. The report has similar plots for the French materials. The tensile elongation plots are normalized by their unaged values which allows an evaluation of the most conservative combinations of aging and accident simulation techniques. Plots indicating "accident effect only" have the tensile elongation value normalized by their after-aging values to illustrate the accident method's contribution to the degradation of mechanical property. Since the tensile properties alone may not indicate the severity of degradation in the insulation materials after the LOCA exposures, the moisture-absorption data (i.e., weight gain) also are plotted. For all these plots, the aging technique employed is displayed in the X-axis and the measurement location in the test sequence is indicated by the plotting symbols.

### CSPE

Figures 5.2-5.4 present the test results for the U.S. CSPE material. Figure 4.52 in section 4 shows the aging results from different combinations of the environmental conditions. Figure 5.2 shows that there is not a large difference in results between alternative accident-exposure techniques. The influence of the aging technique is more pronounced; the R70-T and the R120 aging exposures lead to the most severe degradation. Since after the R70-T aging sequence, elongation already was substantially degraded (to 6% of the original value), the large scatter in additional degradation due to different accident simulation strategies is shown in Figure 5.3. Figure 5.4 shows the weight gains up to 35% for certain CSPE samples. *For this material, the R70-T aging sequence followed by any accident sequence is considered appropriate.*

For the French material, the R+LOCA(air) exposure was less damaging than all the sequential aging and accident techniques. *Hence, any sequential accident exposure qualification procedure is appropriate.*

### CPE

Figure 4.53 shows the tensile properties for different aging sequences. The two R-T sequences reduced the ultimate tensile elongation to approximately 10-15% of its original value. After the accident exposures, most CPE samples had a value less than or equal to 0.1. Samples pre-conditioned by R120, T-R70, R27-T, and T-R27 yielded similar elongation values (see Figure 5.5). Moisture-absorption data is shown in Figure 5.6; the weight gains generally appear to be independent of the preaging technique used before the start of the accident simulations. *For this material, the R70-T aging technique followed by any accident simulation is considered appropriate.*

### EPR

Two U.S. and three French samples were tested in this program. Figures 5.7 - 5.9 show the results for one U.S. EPR-1 material. Each material underwent a different combination of aging and accident simulation procedures. However, the R-T aging sequence satisfied all five materials. For French materials, the R70-LOCA (air) simulation approached the R+LOCA(air) results best. For U.S. materials, the use of a nitrogen atmosphere during the accident simulation was found to be less conservative, unless the containment is inerted. Also, the R120 and T-R27 aging techniques would be less conservative than the other three aging techniques. *Although each sample of this material had a different simulation scenario, a R-T aging sequence followed by the R70-LOCA (air) accident simulation is the preferred combination.*

### XLPO

Two U.S. and one French samples are represented this material; Figures 5.10 - 5.12 show the results for one U.S. sample. The U.S. materials were irradiation cross-linked, while the French material was chemically cross-linked. The effect of alternative accident simulation techniques on the two U.S. materials is vastly different than that for the French material. However, the choice of aging simulation is less important than the choice of accident simulation. *For both U.S. materials, any sequential simulation is appropriate. For French material, any aging simulation followed by the R70-LOCA(air) accident simulation is preferred.*

### Tefzel

Two U.S. samples were included in this category. Figure 5.13 shows the weight loss for one of these materials. A similar trend also was observed for the other samples. For each combination of aging and accident simulations, four samples were successively wrapped around tubes of smaller diameter until insulation cracking or breakage was observed visually. Both materials were more degraded when oxygen was present during simultaneous LOCA simulations (R+Steam). *If sequential qualification procedures are employed, then it is desirable to perform the aging and accident irradiation at elevated temperatures (i.e., 70°C). The aging sequence should be R70-T. Any accident simulation consistent with these constraints is acceptable.*




Figure 5.2 Ultimate tensile elongation of CSPE (Ref. 5.15)




Figure 5.3 Ultimate tensile elongation of CSPE (accident effect only) (Ref. 5.15)




Figure 5.4 Weight gain of CSPE (Ref. 5.15)




Figure 5.5 Ultimate tensile elongation of CPE (Ref. 5.15)




Figure 5.6 Weight gain of CPE (Ref. 5.15)




Figure 5.7 Ultimate tensile elongation of EPR-1 (Ref. 5.15)




Figure 5.8 Ultimate tensile elongation of EPR-1 (accident effect only) (Ref. 5.15)




Figure 5.9 Weight gain of EPR-1 (Ref. 5.15)






Figure 5.10 Ultimate tensile elongation of XLPO-1 (Ref. 5.15)




Figure 5.11 Ultimate tensile elongation of XLPO-1 (accident effect only) (Ref. 5.15)




Figure 5.12 Weight gain of XLPO-1 (Ref. 5.15)




Figure 5.13 Weight gain of Tefzel-1 (Ref. 5.15)

Summarizing the results in this program, cable materials were subjected to a thermal aging, radiation aging of 25Mrad @0.1Mrad/hr and 70°C, accident radiation of an additional 60Mrad @0.3Mrad/hr and 70°C, 4-day LOCA transient at saturated steam condition and chemical spray, and 10 days of post-transient period at 100°C and 95 % humidity. U.S. materials were aged in six different procedures in addition to unaged samples(see Section 4.3.3) and exposed to six different accident conditions (L5 to L10 discussed earlier). Based on the results presented from all possible combinations of the aging and accident sequences, the following observations are made:

- (1) Two XLPO insulation materials behaved differently and both still possessed at least 70% of elongation (absolute) at the end of testing. One material exhibited a small weight loss (<1%) during steam exposure, while the other had weight gain of 2-6%. In sequential accident simulations, the elongation values improved from their post-radiation conditions after being exposed to steam. The results from sequential tests were more severe than from simultaneous tests.
- (2) Two EPR insulation materials behaved differently. One material exhibited weight gain of 1-12% during steam exposure, while the other gained 8-50%. Both materials had a remaining elongation of 7-150%(absolute), with a large number of cases exhibiting less than 50%(absolute) at the end of testing. The elongation values did not improve, in general, during steam exposure from their post-radiation conditions. Both sequential and simultaneous simulations yielded almost similar results.
- (3) For the CSPE jacket material, the weight changes ranged from -5% to 37%, while the remaining elongation values after testing were below 50%(absolute) excepting unaged samples which possessed about 100%(absolute) or larger. No particular difference was noted between all possible different aging and accident simulations. No significant change in elongation occurred during steam exposure.
- (4) The results for CPE were more or less similar to those responses observed for CSPE.

Bonzon and his colleagues (Ref. 5.7) discussed several Japanese studies. The tensile properties for two EPR materials were monitored in simultaneous, sequential (150 Mrad - Steam/Chemical), and reverse- sequential tests (Ref. 5.12); there was very little difference between the results. However, the sequential method was most destructive and the simultaneous method was intermediate between the sequential and the reverse-sequential methods. Reference 5.7 indicated that one Japanese manufacturer's study compared the tensile properties of a flame-resistant EPR with Hypalon jacket and concluded that there was no synergistic effect. In Reference 5.13, both BWR and PWR LOCA conditions were simulated with and without air. The total accident radiation doses were 150 Mrad for PWR and 26 Mrad for BWR. Pre-aging for all specimens was a sequential exposure to high temperatures (7 days at 121°C) followed by irradiation (50 Mrad). When air was not included during the PWR accident simulations, sequential techniques seemed appropriate for most materials including EPR and XLPE. However, when air was present, simultaneous techniques were more damaging. In BWR simulations, the radiation dose was not sufficient enough to promote oxidative degradation. Similar observations were presented in Reference 5.14. For both Hypalon and EPR materials, the ultimate tensile elongation was dominated by the total radiation dose and affected only slightly by the test sequence. However, the ultimate tensile strength for both materials was affected considerably by the test sequence. Simultaneous tests with air was the most degrading, and without air the least.

## **5.2 Effect of Superheated and Saturated Steam Conditions**

Bennett, Clair, and Gilmore (Ref. 5.16) discussed the results of a superheated steam test conducted on three different EPR cable products. Unaged and simultaneously aged (282°F for 168 hours and 40 Mrad, 40 year equivalent) cable specimens were tested in a simultaneous radiation and steam environment. The cables were energized at 480 V and 0.6 A throughout the exposure, and insulation resistance was measured periodically.

They compared the results obtained by Bustard (Ref. 5.10), in which similar cable products were tested under saturated steam. The cables were exposed to the same IEEE Std 323-1974 (Ref. 5.1) temperature profiles in both tests (340°F peak), but the chamber pressure was maintained at 77 psia for the two peaks and the first 320°F plateau during the superheat test. Cable specimens included single conductors and multiconductors; however, only one cable set was the same for both tests. The report summarizes the following comparisons of results:

- (1) Single conductor cables exhibited high IR readings and low leakage currents in both tests.
- (2) Both tests showed the following results for the multiconductor cables:
  - the jacket had a longitudinal split;
  - the exposed gap in the jacket was approximately 0.6 cm wide;
  - bare conductors were visible;
  - the circumference of the jacket increased during the test, although the increase was not large enough to contain the bundle of conductors;
  - the cables had large leakage currents after one minute at the following voltages:

Saturated Steam  
600 V: 180-750 mA

Superheated Steam  
600 V: 2 mA  
1200 V: 5 mA  
1800 V: 750 mA

- the values for insulation resistance followed the same pattern throughout the tests except that in the superheated-steam test the readings were below the instrument's range at 19-21 days, whereas in the saturated-steam test, the readings were below the instrument's range at approximately 8, 12, and 18 days into the accident.

The report concluded that (1) the results from single conductor cable tests may not be conservative for qualifying multiconductor cables; (2) superheat has little effect on cables other than slightly delaying the time of failure; and (3) the differences between the electrical degradation of single and multiconductor cables do not appear to be generic to all cables.

### 5.3 Effect of Radiation Dose-Rates During Accident Simulations

Bustard (Refs. 5.10 and 5.11) discussed the effects of LOCA simulation procedures on EPR and XLPO insulation materials, respectively. The test series include both sequential and simultaneous aging and LOCA radiation exposures in the range of 0.08 - 0.7 Mrad(air)/hr. Material degradation was monitored twice during a saturated-steam LOCA simulation. Some samples were removed after a 4-day LOCA exposure that included a simultaneous exposure to radiation (~65 Mrad at ~0.68 Mrad/hr); the remainder of the samples were tested after another 12-17 days of exposure that included simultaneous exposures to an additional 44 Mrads at lower dose rates (~0.2 and ~0.08 Mrad/hr). Examination of the two sets of data (Table 5.7), allows a qualitative assessment of the importance of the low dose-rate "tail" of the LOCA exposure to material degradation.

Ito and his co-workers (Ref. 5.17) reported a test of electric cable materials conducted to simulate post-LOCA conditions on an accelerated basis. A three-month, 55 krad/hr test was compared against a one-week, 925 krad/hr test, both with and without oxygen present; Table 5.8 summarizes some of these results. Degradation at low dose rates used in 3-month testing were higher than at high dose rates in one week. These results should be taken as a qualitative indication of accident dose-rate effects on the materials tested, since other factors

(such as presence of oxygen) may not have had an effect. The effect of oxygen was significant during the three-month LOCA simulation.

**Table 5.7 Comparison of Tensile Elongation and Weight Gain for EPR and XLPO (Refs. 5.10 and 5.11)**

Material	<u>4-day LOCA Exposure</u>		<u>21-day LOCA Exposure</u>	
	e/e <sub>0</sub>	%Wt. Gain	e/e <sub>0</sub>	%Wt. Gain
<b>A: Properties for EPR During Simultaneous Test #1</b>				
EPR-B	0.17	0	0.14	-1
EPR-C	0.21	9	0.15	23
EPR-D	0.13	120	0.13	173
EPR-E	0.27	N/A	0.19	N/A
<b>B: Properties for EPR and XLPO During Simultaneous Test #2</b>				
EPR-D (Unaged)	0.33	16	0.25	23
(Aged)	0.16	144	0.18	172
EPR-F (Unaged)	0.28	8	0.10	20
(Aged)	0.22	59	0.10	94
XLPO-A(Unaged)	0.30	4	0.23	10
(Aged)	0.25	9	0.16	15
XLPO-B(Unaged)	0.50	15	0.41	32
(Aged)	0.42	33	0.30	58
XLPO-C(Unaged)	0.47	26	0.30	37
(Aged)	0.29	14	0.17	25

**Table 5.8 Rate of Decrease (K) in Ultimate Elongation Under LOCA (1/100 Mrad) (Ref. 5.17)**

Sample	<u>Non Air</u>		<u>Air 0.05MPa</u>	
	One Week	Three Months	One Week	Three Months
EPR-A	0.40	0.40	0.83	1.57
EPR-B	0.46	0.46	0.74	1.46
CSPE-A	0.56	1.00	0.77	1.60
CSPE-B	0.80	1.11	1.09	2.14

Decay curves are taken as Maxwellian (i.e.  $e_t/e_0 = \exp(-Kt)$  where K is rate of decrease and similar to activation energy for a total irradiation of 100 Mrad.

Kusama and his colleagues (Ref. 5.18) studied five different Japanese cable materials irradiated at different dose rates and steam/spray at different temperatures. Figure 5.14 illustrates radiation effects at different dose rates on the elongation at break values for these materials. All had lost their elongation by the end of 2MGy (200Mrad) radiation dose. The XLPE and, to some extent, Hypalon exhibited some dose rate effects. However, when these aged specimens (with 1.5 MGy irradiation) were exposed to steam/spray conditions at 120°C, the LOCA responses for each of these materials were quite different, as shown in Figure 5.15.




Figure 5.14 Elongation at break during irradiation for Japanese Cable Materials (Ref. 5.18)




Figure 5.15 Effect of radiation aging on steam/spray exposure for Japanese materials (Ref. 5.18)

For EPR, specimens irradiated at low dose rates degraded significantly more than those at high dose rates. In the case of XLPE, which indicated dose-rate effects during irradiation, degradation during steam exposure was not significant; instead elongation improved. The results for SR indicated no significant dose-rate effect during steam exposure. Both Hypalon and chloroprene jacket materials exhibited a large decrease in elongation with some dose-rate effects. All materials aged at elevated temperatures and in a pressurized oxygen environment underwent significant loss in elongation when compared to those irradiated in non-oxidative conditions.

The volume resistivity of EPR and XLPE decreased remarkably when the samples were irradiated at lower dose rates; EPR showed a more significant decrease. It was hypothesized that unstable oxidized species formed during irradiation did not affect the tensile properties, but decomposed during steam exposure promoting mechanical degradation. Formation of these species depends on oxygen diffusion during irradiation and at low dose rates, this diffusion through samples can be significant. This diffusion process also can be enhanced at high temperature or in pressurized oxygen. Higher water absorption on these oxidized samples was observed during steam exposure, as well.

Figure 5.16 shows the effect of steam temperature on tensile properties and water sorption for Hypalon and EPR. Samples irradiated to 1.5MGy with a dose rate of 10kGy/hr were exposed to steam conditions at 120°C, 140°C, and 160°C for 264 hours. Both electrical and mechanical properties degrade significantly with the increase in steam temperature, especially in air-containing environment. The decrease in volume resistivity was presumed to be due to water molecules absorbed in the material and the process was further promoted in an elevated temperature and air-containing environment. In case of SR, this effect was not noted; however, a larger decrease in elongation at a higher steam temperature was assumed to be caused by hydrolysis of the material in the presence of chemical spray.

#### **5.4 Effects of Beta and Gamma Radiation During LOCA Exposures**

Bonzon (Ref. 5.19) was the first to define the radiation exposure during a LOCA event and his study had three significant results: (1) A definition of the expected magnitudes of combined gamma and beta dose and rates for a typical PWR containment; typical values of initial dose rate are 3.5 and 70 Mrad/hr, and of 30-day dose are 50 and 300 Mrad, respectively; (2) The beta dose and rate are about six times greater than the corresponding gamma values; (3) The gamma and beta spectra exhibit a changing energy with time, not typical of mono- or fixed-energy simulators. For both, the spectra are initially "hard", then "soften" until a minimum at about 4 days post-LOCA, then "rearden".

Leadon and Lurie (Ref. 5.20) identified five different failure mechanisms caused by the radiation exposure: (a) The failure mechanism is basically chemical, resulting in crosslinking and then chain scission, accompanied by evolution of gas. This occurs generally in low-dose rate and high dose environments. Gas evolution can result in bubble formation on the cable materials. (b) Radiation-induced heat can cause deterioration of cable polymers and their bondings. Synergistic effects could be important. (c) Non-uniform charge distributions in insulation can result from either incident gamma rays or electrons. (d) High incident dose rate can cause transient electrical signals in the cable. (e) Discharge of trapped electrons can cause transient electrical signals and noise in the cable. An evaluation by the authors on nuclear power plant cables concluded that chemical and mechanical deterioration of the insulation, exacerbated by a large temperature rise, would be the most significant. These damages depend on the total dose and hence, can be adequately caused by nearly any type of radiation source.






Figure 5.16 Effect of steam temperature on irradiated Japanese cables (Ref. 5.18)

Buckalew and his co-workers (Ref. 5.21) investigated charge breakdown from beta irradiations of EPR insulation material slabs and typical electric cables. Under certain conditions, charge accumulated and spontaneous breakdown occurred during irradiation in a vacuum; however, there was no evidence of breakdown during ambient air exposures. It was concluded that buildup and breakdown of electron charge is not apt to occur in EPR insulation exposed to electrons from a LOCA radiation environment, provided that the insulation is in contact with an ionized medium.

They were concerned with the adequacy of isotopic photon sources (e.g.,  $^{60}\text{Co}$ ) to simulate the combined beta-gamma radiation environment accompanying a LOCA. A multi-year NRC/French/SNL cooperative test program was initiated, including a study of any synergistic effects associated with a mixed beta/gamma radiation field. They discussed the first results obtained by the complementary beta-gamma equivalence test program at Sandia (Ref. 5.22). These tests attempted to identify the degree to which factors, such as (1) differences in energy deposition profiles between electrons and photons, (2) differences in energy deposition for each particle type, and (3) differences in radiation-induced damage mechanisms (e.g., cross-linking, charge build-up/breakdown) might influence the dose-damage equivalence in certain organic materials.

These tests considered one EPR formulation in slabs of three different thicknesses (1, 1.5, and 2 mm), exposed to  $^{60}\text{Co}$  or accelerated electrons at energies ranging between 0.235 and 0.85 MeV. In each case, the samples were irradiated at 2 Mrad/hr to 10 Mrad/hr. Analyses of the radiation-exposure data (tensile elongation and strength) suggest that the observed damage is a slowly varying function of absorbed energy and independent of particle type, within experimental uncertainty. Absorbed energy, particle energy, and surface dose are all interrelated parameters, and the data analysis on the basis of these parameters yields similar results. Data on material thickness indicates that, for the energies and thicknesses considered, the distribution of energy deposition within the sample is not significant; rather, damage is a function only of the total energy absorbed.

They provided the results of the U.S./French research program which investigated the relationship between the damage from beta and gamma radiation in polymer base materials used for cable insulations and jackets (Ref. 5.23). The results obtained for the thinner slab-geometry specimens reinforced the conclusions of the earlier studies, namely, that beta- and gamma-ray induced damage could be related on the basis of average absorbed radiation dose. However, data from thicker (4 and 6 mm) slabs were in disagreement, and displayed some effects of the material's thickness on its response. However, the preponderance of the results predict an equivalence between beta and gamma radiation damage on the basis of radiation-absorbed dose.

The results obtained for the EPR and Hypalon materials in a cylindrical cable geometry were similar to those obtained for the EPR materials in a slab configuration. Again, some slight deviations in the data were observed. However, the preponderance of data for cylindrical specimens indicate that electron beams and cobalt gamma-ray induced damage can be related on the basis of average absorbed radiation dose. Thus, it appears possible to qualify materials for beta radiation damage by exposing them in gamma ray irradiators. The study concludes that the results also can be used to estimate radiation damage to polymers exposed to the large beta dose rates associated with the release of fission products into a containment during accidents.

They concluded that  $^{60}\text{Co}$  irradiators represent a conservative method of simulating the LOCA environment which is a mixture of both beta and gamma radiations (Ref. 5.24). Results for a cable with EPR insulation and Hypalon jacket predicted that conventional LOCA radiation simulation testing of jacketed cable components would overstress the jacket and insulation materials by factors of two and five, respectively. Shielding of the insulation (EPR) by the Hypalon jacket and enhancement of the EPR gamma dose by reflection from copper conductor also were noted. They considered that this conclusion may not be appropriate for radiation exposure of 1000 Mrad level.

## 5.5 Effect of the Presence of Oxygen During LOCA Exposures

The effects of oxygen on polymer materials were discussed in Reference 5.15, and Figures 5.2-5.13 illustrate the results with air and nitrogen environments for various simultaneous and sequential tests. For some materials, the presence of oxygen during accident simulations enhanced the degradation of tensile properties. For EPR materials, the tensile elongation was more degraded by LOCA simulations that included oxygen than those that did not. Oxygen also was important to the degradation of Tefzel materials for some aging and accident simulation techniques. For example, simultaneous steam, chemical spray, and radiation exposures typically were more degrading if there was an overpressure of oxygen rather than an overpressure of nitrogen. The presence of oxygen was not important for CSPE and CPE samples. For XLPO materials, a simultaneous accident simulation with oxygen typically was the least degrading. The report concluded that the presence or absence of air during accident simulations can influence the degree of degradation in some materials.

Gillen and his colleagues (Ref. 5.25) presented the results of the cooperative U.S.-French test program where nine materials commonly used as electric cable insulations and jackets were monitored in terms of mechanical properties, weight increases, solubility measurements, and infrared spectroscopy. Three different LOCA simulation tests were employed. In addition to a steam environment, the three simulations used 0% oxygen (L-0: containing nitrogen), 10% oxygen (L-10), and air (L-21: 21% oxygen) with constant gas pressures. Figures 5.17 - 5.24 illustrate the ultimate tensile properties for the different polymer materials. In each Figure, the circles give the results measured at Sandia, and the triangles denote those obtained from CEA-ORIS-STBR, France. The numbers on the abscissa refer to four aging conditions: (1) unaged; (2) 21 Mrad at 880 krad/hr; (3) 45 Mrad at 880 krad/hr; and (4) 23 Mrad at 24 krad/hr.

The chloroprene material, shown in Figure 5.17, appeared to suffer significantly more damage in LOCA simulations containing oxygen, a conclusion which was valid even for samples which were not aged. EPR (see Figure 5.18) also had substantially decreased tensile properties when oxygen was included; solubility, swelling ratio, and FTIR results indicated that increased oxidative scission enhanced the degradation. On the other hand, for a PVC material, the damage may become more severe as the oxygen content is lowered, as shown in Figure 5.19 (slightly greater mechanical damage, substantially greater swelling). Thus, a LOCA simulation without oxygen may underestimate the changes which occur in some materials, while overestimating the changes in others.

These results have important implications for material qualification testing relative to a LOCA. Since very low leak rates are designed into containment, it appears that the original oxygen content in the air is largely trapped in the containment area for the duration of the accident. Since there is no mechanism for replenishing oxygen, its concentration might decrease as the accident progresses due to leakage and its reaction with the material in containment. Therefore, it is important to estimate the time-dependent oxygen concentration during a LOCA more precisely, and to use it as a guide to the proper oxygen concentration to use in LOCA simulations.

For EPR insulation, which previously showed dose-rate effects during aging, evidence was found for dose-rate-induced effects being further amplified during the LOCA simulation. Another finding includes the widely varying responses of different materials to the aging and LOCA simulation sequences in terms of the kind and magnitude of the induced degradation. PVC and chloroprene exhibited huge steam-induced swelling. CLPO (Figure 5.20) and Silicone (Figure 5.22) were degraded by aging, but showed little or no further deterioration in a subsequent LOCA simulation. Tefzel (Figure 5.23), chloroprene, and PVC showed moderate to significant aging-related degradation, which was strongly amplified by the subsequent LOCA simulation.




Figure 5.17 Tensile property results for CP (Ref. 5.25)




Figure 5.18 Tensile property results for EPR (Ref. 5.25)




Figure 5.19 Tensile property results for PVC (Ref. 5.25)




Figure 5.20 Tensile property results for CLPO (Ref. 5.25)




Figure 5.21 Tensile property results for CLPE (Ref. 5.25)




Figure 5.22 Tensile property results for silicone (Ref. 5.25)




Figure 5.23 Tensile property results for Tefzel (Ref. 5.25)




Figure 5.24 Tensile property results for CSPE (Ref. 5.25)

Materials, such as Tefzel, EPR, and PVC exhibited substantial degradation from the combination of aging and LOCA simulation, yet showed little or no damage when unaged samples were exposed to the LOCA simulation. Tefzel, chloroprene, and PVC were badly degraded (i.e., tensile values reduced to near zero) after exposure to the various aging and LOCA simulation sequences. Finally, CLPE (Figure 5.21), CSPE (Figure 5.24), and CLPO exhibited only modest damage in all the tests.

Based on the results presented, the effects of various pre-conditions and conditions during LOCA simulation on material responses were evaluated; this qualitative assessment is shown in Table 5.9. Because of the different behavior of cable insulation and jacket materials, the researchers suggested using thermal ovens in screening the importance of aging conditions on a material's response to LOCA. This sequential procedure could offer a relatively easy method for choosing materials and optimizing material formulations for applications to electric cables.

The results from Japanese studies discussed in some of the earlier sections indicate that oxygen may have some effects during LOCA simulations. Reference 5.13 presents data on volume resistivity for EPR, Hypalon, and Neoprene both with and without air in the steam, showing that it was degraded by 2 to 3 orders of magnitude in air-containing simulations, but only by 0-2 orders of magnitude when air was absent (see Figure 5.43). A relationship between swelling of materials and decrease in volume resistivity reveals that materials which show a larger drop in volume resistivity swelled easily under LOCA conditions, especially with air. Reference 5.14 concluded that the tensile properties for Hypalon were slightly degraded by simulations containing air, but reached no clear conclusion about EPR.

Ito (Ref. 5.17) compared the behavior of cable's EPR insulation and Hypalon jacket materials to the electrical performance of cables. Insulation resistance did not exhibit large effects, as indicated by the tensile and volume resistivity properties. Figures 5.25 and 5.26 demonstrate that differences in insulation resistance between air and non-air LOCA simulations are small. When the results of slab specimens were compared, it was found that the cable's jacket apparently reduced the oxygen available for interacting with the insulation.

## **5.6 Effect of Chemical Spray During LOCA Simulations**

The chemical spray commonly used in qualification tests consists of 0.28 molar boric acid, 0.064 molar sodium thiosulfate, and sodium hydroxide added to obtain a pH between 10 and 11 at 77°C (IEEE Std 323-1974, Table A1). Chemical spray, deposited on the surface, affects the properties of electrical insulators. Most LOCA simulations at Sandia did not include chemical sprays. Some French studies and practically all qualification tests by the Franklin Research Center did include chemical sprays, but did not address specific effects due to their presence<sup>5</sup>.

Yagi and his co-workers (Ref. 5.26) considered eight elastomer formulations exposed to boiling spray solutions (water and IEEE Std 323-1974 solution). Figures 5.27 and 5.28 summarize the results for the Hypalon and EPR materials. The study found that (1) all eight elastomers showed remarkable swelling with an increase of radiation dose when they were irradiated in air, (2) swelling in boiling water was about twice that in chemical solution, and (3) some types of Neoprene and Hypalon showed maximum swelling at a particular

---

<sup>5</sup> In a test program on the effect of different sprays on coating materials, the Franklin Research Center found that demineralized water sprays produced much more damage than three different chemical sprays; and there was very little difference among the effects of different chemical sprays (Personal communication with Dr. S.P. Carfagno).



Table 5.9 Material Behaviors under Radiation Aging and LOCA Simulations (Ref. 5.25)

Material	Original E(%) T(MPa)	Weight Changes Due to LOCA	Dose Rate Effect (Aging)	Effect of Oxygen During LOCA	Effect of Pre-Aging on LOCA Responses	Comments
CLPE (Chem XL)	350 16.2	Insignificant	Insignificant	Insignificant	Insignificant(E), None(T)	Some minor pre-aging and LOCA effects exist
Tefzel	290 54	Insignificant	Very Significant	None	Very Significant(E), None(T)	Excellent thermal properties, but sensitive to radiation. After LOCA, samples were extremely brittle.
Silicone	430 7.6	Insignificant	Insignificant	None	Very Significant(E), Insignificant(T)	Major elongation changes occurred due to aging rather than LOCA.
EPR-S (molded)	360 12.2	Insignificant	Insignificant	None	None(E), Insignificant(T)	L10 was not performed.
CLPO(Rad XL,FR)	240 13.7	Significant	Insignificant	None	None	Radiation aging caused significant decrease in elongation. LOCA had no effect.
CSPE	300 24.4	Significant	Insignificant	Insignificant	Insignificant	L10 was run 5 months after other two LOCA tests.
PVC	300 20	Very Significant	Insignificant(T) Significant(E)	Mixed	Very Significant(E), Significant(T)	Because of large dimensional changes, samples were constrained during LOCA tests, giving inconsistent responses.
CP (Chloroprene)	185 11	Very Significant	N/A	Very Significant	Not Conclusive	Presence of oxygen caused significant degradation.
EPR	340 6.9	Significant	Insignificant	Very Significant	Insignificant	Carbonyl species (esters, acids, ketones, aldehydes) were found on aged samples.

NOTES: AGING: No Thermal; Lot 1: Unaged; Lot 2: 21Mrad @ 880 krad/hr 24hrs @44°C; Lot 3: 45Mrad @ 880 krad/hr 50.5hrs @ 44°C; Lot 4: 23Mrad @24 krad/hr 958 hrs @26°C (CLPE: 622hrs@26°C)

LOCA: No Chemical Spray; L0: Nitrogen Environment; L10: 10% Oxygen Environment; L21: Air Environment

Insignificant = Minor Changes; Significant = Moderate changes; Very Significant = Large changes; N/A = Not applicable; Mixed = Changes involve both large and minor changes under certain conditions; None = No noticeable change




Figure 5.25 Electrical cable performance during a non-air LOCA exposure (Ref. 5.14)






Figure 5.26 Electrical cable performance during an air LOCA exposure (Ref. 5.14)



**Figure 5.27 Comparison of swelling behavior of Hypalon in water and in chemical solution (Ref. 5.26)**  
 Reproduced with permission from Dr. Toshiaki Yagi, JAERI, Japan.



**Figure 5.28 Comparison of swelling behavior of EPR in water and chemical solution (Ref. 5.26)**  
 Reproduced with permission from Dr. Toshiaki Yagi, JAERI, Japan.




Figure 5.29 Effect of chemical spray on Japanese materials (Ref. 5.18)

dose, above which the swelling ratio decreased with dose. Reference 5.18 gives the results for material responses to spray conditions shown in Figure 5.29. Spray promoted degradation of Hypalon and XLPE, while SR showed no such influence. On the other hand, spray did not affect the electrical degradation of XLPE and SR, but enhanced that of EPR. The resistivity of Hypalon degraded when irradiated at elevated temperature. Chloroprene samples degraded severely after steam/spray exposure, and therefore, the effect of spray was not evaluated further.

### 5.7 Effect of Acceleration of Post-Transient Environments

The qualification of safety-related equipment must demonstrate that the equipment can perform its safety function during normal operations, and for the duration of a design basis event. A post-transient environment is defined as the fully saturated steam condition with 100% relative humidity at ~100°C; this simulates the conditions and durations of the inside containment after design-basis event transients. To reduce the cost and time, it is common industry practice to time-compress the post-transient environment simulation. The results by Gillen and his co-workers (Ref. 5.25) on the effects of various concentrations of oxygen during LOCA simulations have the potential for post-transient acceleration. Table 5.10 compares the 10% oxygen LOCA simulation (L-10) tests with air oven tests consisting of 96 hours exposure at 145°C. The temperatures during the LOCA simulations ranged from 171°C at the beginning and dropped off to 121°C after 4 days. Many materials exhibited comparable degradation during both tests, which suggests that similar degradation mechanisms may be involved. Hence, they suggested that this may provide a basis for post-transient acceleration.

**Table 5.10 Sequential Screening Comparisons (Ref. 5.25)**

Material	Aging Condition	e/e <sub>0</sub>	
		Air Oven	L-10
CLPE	1	0.65	0.68
	3	0.05	0.42
	4	0.56	0.53
Tefzel	1	0.92	1.02
	4	0	0.04
Silicone	1	0.93	0.96
	2	0.24	0.38
	4	0.17	0.38
CLPO	1	0.79	0.98
	2	0.33	0.70
	3	0.24	0.49
	4	0.26	0.72
CSPE	1	0.40	0.74
	2	0.27	0.61
	3	0.19	0.48
	4	0.15	0.58
PVC	1	0.57	0.53
	2	0.18	0.09
	4	0.04	0.03
CP	1	0.01	0.05
	2	0.01	0.03
EPR	1	0.77	0.89
	2	0.49	0.38
	3	0.12	0.17
	4	0.14	0.12

Aging: 1-Unaged; 2-21 Mrad at 880 krad/hr; 3-45 Mrad at 880 krad/hr; 4-23 Mrad at 24 krad/hr

Ito and his colleagues (Ref. 5.17) discussed a limited Japanese experiment on this subject; the results are given in Table 5.8. They claimed that oxygen partial pressure should be included in the LOCA simulation if the samples are sensitive to the presence of oxygen. They had observed some differences in material and electrical properties during post-transient acceleration experiments.

Okada and his co-workers (Ref. 5.27) studied Hypalon and EPR subjected to LOCA testing. Simultaneous exposure of radiation and steam/chemical spray was performed in two distinct cases: one for a week at a high dose rate of 10 kGy/hr up to 1.5MGy (Sim-A and Sim-C) and the other for three months at a dose rate of 0.6kGy/hr up to 1.4MGy (Sim-B and Sim-D). Both were performed in air-free (Sim-A and Sim-B) and air-containing steam conditions (Sim-C and Sim-D). Sequential tests included irradiation performed first in air at high dose rate of 10kGy/hr and room temperature (Seq-a and Seq-b). Low dose rate conditions included dose rate of 1kGy/hr at room temperature in air, dose rate of 5kGy/hr at 70°C in air, and dose rate of 4.2kGy/hr at room temperature in pressurized oxygen (0.5MPa). Both groups were irradiated up to 1.5 MGy. Steam/chemical spray followed irradiation and several other variables such as steam temperature and oxygen pressure were changed to evaluate their effects on the mechanical and electrical properties of the two cable polymers.

Figures 5.30 and 5.31 illustrate the results for Hypalon and EPR materials, respectively. Both materials under one week LOCA simulations degraded less than those simulated for three month exposures. The Hypalon was more sensitive to presence of oxygen than EPR. Compared with sequential simulations, the degradation in both materials was less severe than simultaneous conditions (except Sim-A). Therefore, accelerating the simulation of the post-transient duration to a shorter period may underestimate the material's responses to LOCA conditions.

## **5.8 Effect of Aging Methods on LOCA Simulations**

An important question is which combination of alternative sequential aging and accident simulations closely represent the real-time degradation of cable materials in the containment of a nuclear power plant in normal and accident environments. Most studies discussed have addressed various aspects of this question including the relationship between the aging simulation and the accident simulation techniques, synergistic and sequencing effects in various combinations of these techniques, and the importance of the aging pre-conditioning to the subsequent performance of cables during accident simulation. Results from the U.S.-French test program in Reference 5.25, test results on EPR and XLPO materials given in References 5.10 and 5.11, respectively, and accident simulation results in Reference 5.15 concluded that choice of aging simulation method does affect the cable's behavior during an accident simulation.

Reference 5.25 gives the results of a U.S.-French test program in which the mechanical properties, weight increases, solubility measurements, and changes in infrared spectroscopy of nine different materials were monitored. Three different LOCA simulations and four different aging simulations were employed. For the LOCA simulations, the only planned difference among the three tests was the composition of the overpressure gas. The study noted that aging conditions are a parameter that helps define the material's response during subsequent LOCA simulations. Table 5.11 has the data on weight change for a PVC material. The moisture absorbed during the LOCA simulation depended strongly on the aging technique (total dose and dose rate).

EPR-1483 (Ref. 5.10) is similar in composition to EPR-A and EPR-B discussed earlier, and is qualified for control and instrument cables in nuclear facilities. This material also was exposed to the eight different aging techniques (given in Table 5.3 for EPR-A), followed by the three accident simulations. After the 21-day





Figure 5.30 LOCA simulations for Hypalon (Ref. 5.27)





Figure 5.31 LOCA simulations for EPR (Ref. 5.27)



LOCA exposures, its tensile properties, weight changes, and dimensional changes were measured (Figures 5.32 - 5.34). There was not a large variation caused by alternative sequential aging techniques nor by dose-rate effects. Rather, differences between the simultaneous and sequential aging techniques were more important; the former caused more degradation during accident simulations than did the latter. Moreover, the degradation in tensile strength caused by simultaneous aging was amplified by subsequent LOCA exposures. However, thermal aging at 139°C instead of 120°C might have been the reason for such increased degradation for simultaneous aging. The data also illustrates the importance of aging to total material degradation. For example, specimens unaged before LOCA exposures tended to gain less weight and less volume than did aged ones.

**Table 5.11 Weight Change Due to LOCA Simulation for a PVC Material (Ref. 5.25)**

LOCA Test %Oxygen	Aging* Method	Percentage Weight Change After		
		6 Hour	1500 Hour	5000 Hour
0	1	93	14	-4
	2	220	50	-1
	3	347	46	-4
	4	330	62	-7
10	1	53	-2	N/A
	2	150	-4	N/A
	3	360	-3	N/A
	4	230	-4	N/A
21	1	0	-1	-1
	2	18	0	-2
	3	39	4	-2
	4	35	4	-3

\* Aging: 1-Unaged; 2-21 Mrad at 880 krad/hr; 3-45 Mrad at 880 krad/hr; 4-23 Mrad at 24 krad/hr

N/A=Not Applicable

**Table 5.12 Effect of Accelerated Age on EPR Moisture Absorption (Ref. 5.10)**

Material	Accelerated Age	Moisture Absorption (% Weight Increase)
EPR-D	Unaged	16
	40-year Equiv.*	172
EPR-F	Unaged	20
	40-year Equiv.*	94
Japanese EPR-5	Unaged	49
	40-year Equiv.*	77
EPR-1483	Unaged	17
	5-year Equiv.**	22
	40-year Equiv.***	67

\* 7-day 139°C with simultaneous irradiation for 6 days to 40 Mrad.


\*\* A 94-day simultaneous exposure to 120°C and 4.9 Mrad Irradiation.

\*\*\* A 30-day simultaneous exposure to 120°C and 39 Mrad Irradiation.

Unlike EPR-A and EPR-1483, unaged and simultaneously aged specimens of other EPR materials were exposed to the simultaneous accident simulations. Table 5.12 shows that accelerated aging was important to subsequent moisture-absorption during simultaneous steam and irradiation LOCA simulations. A higher weight increase in some EPR material might have been due to pre-aging at 139°C.

**AGING  
TREATMENT**

UNAGED  
5 yr equiv.  
94h T+R<sup>1</sup>  
40 yr equiv.  
7d T+R<sup>2</sup>  
30d T+R<sup>1</sup>  
28d T→28d R<sup>3</sup>  
28d R→28d T<sup>3</sup>  
28d T→55h R<sup>4</sup>  
55h R→28d T<sup>4</sup>



NOTES: 1: 120°C and 53 krd/h (air-equiv.)  
 2: 139°C and 250 krd/h (air-equiv.)  
 3: 120°C; 57 krd/h (air-equiv.)  
 4: 120°C; 750 krd/h (air-equiv.)

Figure 5.32 Effect of aging and accident techniques on normalized tensile strength of EPR-1483 (Ref. 5.10)




Figure 5.33 Effect of aging and accident techniques on percentage weight gain of EPR-1483 (Ref. 5.10)




Figure 5.34 Effect of aging and accident techniques on percentage volume change of EPR-1483 (Ref. 5.10)

In Reference 5.11, none of the XLPO products exhibited as much degradation as some of the EPR products. XLPO-A and XLPO-B experienced the same effects from aging as did the EPR products; namely, there were larger increases in weight and dimensions for the aged specimens than the unaged ones. In contrast, unaged XLPO-C absorbed more moisture than did aged material. The ultimate tensile strength was enhanced by aging, suggesting additional crosslinking of the polymer matrix; this might explain the reduced moisture-absorption of the aged compared to the unaged specimens.

One of the goals of the accident simulation studies discussed in Reference 5.15 was to evaluate whether some combinations of alternative aging and accident simulation techniques were better suited for qualification than others. As shown in Figures 5.2 to 5.13, for some materials, the effects of the accident simulation technique were sensitive to the aging method, but for others, the aging method had very little impact on material properties subsequently (e.g., EPR and XLPO-2).

The study examined whether age pre-conditioning techniques might reduce synergistic and sequencing effects during accident simulations. Section 5.1 identifies the appropriate sequential simulation procedures for each material included in the test program. These sequential techniques produced deteriorations similar to those achieved during simultaneous irradiation and LOCA (with air) accident simulations except for a fire-retardant French EPDM material (EPDM-8219). The study considered the simultaneous accident simulation to be the best representation of postulated design-basis accident conditions. For several materials, irradiation followed by thermal exposure is the most appropriate technique for age pre-conditioning.

References 5.28 and 5.29 give tensile data for two chemically cross-linked polyolefin insulations. Both materials were exposed to three different aging exposures:

1. A high dose rate (865 krad/hr) irradiation to a total dose of 42.5 Mrad followed by thermal aging for 240 hours at 150°C.
2. Reverse of 1.
3. Same as 1, but the dose rate was 48 krad/hr.

After aging, the specimens were further irradiated at 865 krad/hr dose rate, in increments of 50 Mrad, up to a total dose of 200 Mrad. Figures 5.35 and 5.36 present the results for one of the materials. The effects of alternative aging techniques is clearly evident at completion of the aging exposures. However, after the accident irradiations, the insulations had very little remaining life and all three groups approached the same level of mechanical degradation<sup>6</sup>. The results for the other material are shown in Figures 5.37 and 5.38; this material exhibited similar behavior, but showed much more variability.

The Japanese studies described in Ref. 5.13 include tensile properties and volume resistivity data after both PWR and BWR LOCA testing (with and without air) for several polymers. Both pre-aged and unaged specimens were tested. Pre-aging for all specimens was a sequential exposure of thermal aging followed by irradiation (50 Mrad). The total accident radiation-exposure for PWR conditions was 150 Mrad, while that for the BWR was 26 Mrad. Simultaneous and sequential accident simulations were employed. Figures 5.39 to 5.42 compare the mechanical properties for different materials. Not unexpectedly, the effect of aging is more noticeable for the BWR simulations because there the accident irradiation is approximately half that of the aging irradiation, while for the PWR accident, irradiation is three times the aging irradiation.

---

<sup>6</sup> This finding tends to diminish the importance of differences among different methods of accelerated aging, because it indicates that the condition of cable insulation before the steam/chemical spray portion of the LOCA simulation might be nearly independent of the aging method.




Figure 5.35 Elongation vs. radiation exposure for XLPO (Ref. 5.29)




Figure 5.36 Tensile force vs. radiation exposure for XLPO (Ref. 5.29)




Figure 5.37 Elongation vs. radiation exposure for XLPO (Ref. 5.28)








Figure 5.38 Tensile force vs. radiation exposure for XLPO (Ref. 5.28)



□ ; Pre-conditioned  
 ■ ; Not pre-conditioned

Figure 5.39 Comparison of mechanical properties after simultaneous and sequential LOCA testing (PWR Conditions) (Ref. 5.13)



**Figure 5.40 Comparison of mechanical properties after simultaneous and Sequential LOCA testing (PWR conditions containing air) (Ref. 5.13)**







Figure 5.41 Comparison of mechanical properties after simultaneous and sequential LOCA testing (BWR conditions) (Ref. 5.13)





Figure 5.42 Comparison of mechanical properties after simultaneous and sequential LOCA testing (BWR conditions containing air) (Ref. 5.13)

Figure 5.43 shows data on volume resistivity for several insulating materials after LOCA simulations. For EPR, Hypalon, and Neoprene, volume resistivity was degraded by two or three orders of magnitude in simulations in air, but only degraded by zero to two orders of magnitude when air was absent. In the former, the simultaneous method degraded for the resistivity of the unaged samples the most, while the reverse sequential was least degrading. For the pre-conditioned samples, however, the degradation from both was equal. Hence, perceptions about which accident simulations are the most severe are influenced by pre-aging.

Kawakami and his colleagues studied the effect of pre-conditioning on several cable materials (Ref. 5.30). The Japanese materials studied include CSM (Hypalon), EPR, XLPE, CR (chloroprene), and SR. The testing included a sequential procedure. The pre-conditioning was done by either thermal aging (168 hrs @ 121°C) followed by irradiation of 0.5 MGy at a dose rate of 10 kGy/hr in room temperature, or irradiation of 0.5 MGy at a dose rate of 5 kGy/hr in an oxygen environment followed by thermal aging (168 hrs @ 121°C). The LOCA simulation included irradiation of 1.5 MGy for PWR or 0.26 MGy for BWR followed by a 120°C steam/spray exposure. Testing also included other pre-conditioning methods, including thermal exposure followed by irradiation in oxygen environment, and irradiation without thermal aging (see Figure 5.44).

Oxygen consumption was strongly dependent on the pre-conditioning state of the material; irradiation followed by thermal treatment caused larger oxygen consumption comparable to the simultaneous method with a similar radiation dose and thermal conditions. The effect of pre-conditioning on material degradation is not significant, except for Hypalon in a BWR environment. However, the study concluded that pre-conditioning of cable materials prior to accident simulations is an important factor in the EQ process.

## 5.9 Life Extension, Submergence, and High Temperature Test Results

Jacobus (Refs. 5.31-5.33) studied aging, condition monitoring, and accident testing of several safety-related cables. Table 5.13 lists the cable products included in this program. One objective was to determine the long-term aging degradation behavior of popular cable products. The experimental program consisted of two phases. Phase I was simultaneous thermal (~100°C) and radiation (~0.10 kGy/hr) aging exposures for 3 months, 6 months, and 9 months in three different chambers. (A fourth chamber, containing unaged cables, was used only for the accident exposure). Phase II was an accident exposure of the aged and unaged cables, consisting of high dose rate irradiation (~6 kGy/hr) to a total dose of 1100 kGy (110 Mrad), followed by a LOCA steam exposure. The tests followed the guidance of IEEE Std 323-1974 (Ref. 5.1) and IEEE Std 383-1974 (Ref. 5.2). No chemical spray was used during the steam exposure, but a 1000-hr post-LOCA submergence test (in a chemical solution similar to the chemical spray at 95±5°C with a slightly positive pressure) was carried out on the cables that had been aged for 6 months and accident-tested. The accelerated aging temperature was determined by equating the 6-month exposure to a 40-year life, and assuming an activation energy of 1.15 eV and a plant ambient temperature of 55°C. The accelerated radiation-aging dose-rate was determined by assuming a 40-year radiation dose of 400 kGy. Therefore, the 3-month chamber was nominally equivalent to 20 years of aging, and the 9-month chamber to 60 years of aging. Similar to the submergence test using the cable group subjected to 6-month aging and accident-tested, cables that were aged for 3 months and then LOCA-tested, were subsequently exposed to a high-temperature steam-fragility test that included a peak temperature of 400°C (750°F) to study the ultimate fragility level of typical types of cables. Insulation resistance was monitored throughout the high-temperature steam test and at discrete times during the submergence test. Dielectric withstand testing was performed before both test programs. Cables that passed the post-submergence dielectric test subsequently were wrapped around a 40 times cable diameter mandrel and subjected to a final dielectric withstand test. The results of the submergence and high-temperature steam tests are given in Reference 5.34. The following is a summary of findings for each material group.






Figure 5.43 Log mean values of volume resistivity after simultaneous, sequential and reverse sequential LOCA tests (Ref. 5.13)



SEQUENTIAL LOCA CONDITIONS (1.5 MGy → 120°C STEAM)



SEQUENTIAL LOCA CONDITIONS (0.26 MGy → 120°C STEAM)

121°C, 168hr → 0.5MGy AT 10kGy/h  
 0.5MGy AT 5kGy/h IN OXY. → 121°C, 168hr

Figure 5.44 Effect of LOCA on pre-aged Japanese materials (Ref. 5.30)

**Table 5.13 Cable Products Included in the Test Program (Ref. 5.31)**

<u>Supplier</u>	<u>Group</u>	<u>Description</u>
1. Brand Rex	XLPO	XLPE Insulation, CSPE Jacket, 12 AWG, 3/C, 600 V
2. Rockbestos	XLPO	Firewall III, Irradiation XLPE, Neoprene Jacket, 12 AWG, 3/C, 600 V
3. Raychem	XLPO	Flamtrol, XLPE Insulation, 12 AWG, 1/C, 600 V
4. Samuel Moore	XLPO	Dekoron Polyset, XLPO Insulation, CSPE Jacket, 12 AWG, 3/C and Drain
5. Anaconda	EPR	Anaconda Y Flame-Guard FR-EP, EPR Insulation, CPE Jacket, 12 AWG, 3/C, 600 V
5a. Anaconda *	EPR	Anaconda Flame-Guard EP, EPR Insulation, Individual CSPE Jacket, CSPE Jacket, 12 AWG, 3/C, 1000 V
6. Okonite	EPR	Okonite Okolon, EPR Insulation, CSPE Jacket, 12 AWG, 1/C, 600 V
7. Samuel Moore	EPR	Dekoron Dekorad Type 1952, EPDM Insulation, Individual CSPE Jackets, Overall CSPE Jacket, 16 AWG, 2/C TSP, 600 V
8. Kerite	Misc	Kerite 1977, FR Insulation, FR Jacket, 12 AWG, 1/C, 600 V
9. Rockbestos	Misc	RSS-6-104/LE Coaxial Cable, 22 AWG, 1/C Shielded
10. Rockbestos	Misc	Firewall Silicone Rubber Insulation, Fiberglass Braided Jacket, 16 AWG, 1/C, 600 V
11. Champlain	Misc	Polyimide (Kapton) Insulation, Unjacketed, 12 AWG, 1/C
12. BIW	EPR	Bostrad 7E, EPR Insulation, Individual CSPE Jackets, Overall CSPE Jacket, 16 AWG, 2/C TSP, 600 V

\* This cable was only used for the multiconductor samples in the 3-month chamber.

**Abbreviations used in table:**

XLPO - Cross-linked polyolefin	CPE - Chlorinated polyethylene
XLPE - Cross-linked polyethylene, a subset of XLPO	EPR - Ethylene propylene rubber
CSPE - Chlorosulfonated polyethylene	EPDM - Ethylene propylene diene monomer
AWG - American Wire Gauge	TSP - Twisted shielded pair
/C - number of conductors	FR - Flame retardant
FR-EP - Flame retardant ethylene propylene	BIW - Boston Insulated Wire

## XLPO

- (1) Out of 40 conductors tested, one from one of three conductors of a Rockbestos multiconductor cable failed during the accident tests. The failed cable was exposed to the 9-month aging chamber.
- (2) The three multiconductor cable products had accident IRs<sup>7</sup> that were within an order of magnitude of each other. The single conductor cable tested had an IR that was 2-3 orders of magnitude higher than the multiconductor.
- (3) With the exception of one conductor that failed during the accident test, all conductors afterwards successfully passed high-voltage tests at an applied voltage of 80 Vac/mil (dielectric strength as high as 400-700 Vac/mil). Three conductors (Dekoron Polyset XLPO) failed a similar high-voltage test after the post-accident mandrel-bend test, and cracking extending through to the conductor was observed.
- (4) For 3 of the 4 XLPO materials aged for 9 months, elongation was greater after the accident than before; this may be the result of melting and reforming of the crystalline structure, or of moisture being absorbed into the cable and acting as a plasticizer.
- (5) Most properly installed XLPO cables should survive an accident after 60 years for total aging doses up to 400 kGy (40 Mrad), and for moderate ambient temperatures about 50°C-55°C.

## EPR

- (1) Four conductors out of 72 failed during the accident tests. Failures also were recorded for one conductor of a Dekoron Dekorad multiconductor aged for 3 months, two conductors of the same manufacturer's multiconductors aged for 9 months, and one Okonite Okolon single conductor aged for 9 months. In addition, the aged BIW conductors had minimum IRs that were potentially low enough to affect the accuracy of some sensitive instrumentation circuits.
- (2) The multiconductor cable products showed accident IRs differing by more than 3 orders of magnitude, indicating significant variation in the behavior of EPR products from different manufacturers. The single conductor-cable product from the same manufacturers had an IR generally within the range of the IRs of the multiconductors.
- (3) After aging and accident testing, several conductors failed a 5-minute withstand test at a nominal voltage of 80 Vac/mil; these included the four failed during the accident test, one additional Okonite Okolon, and eight more Dekoron Dekorad conductors.
- (4) The cables that survived aging for 9 months, accident testing, and post-accident dielectric tests then underwent a mandrel-bend test and a second dielectric test. All of the single conductor cables with bonded CSPE jackets cracked through to the conductor during the mandrel bend; only the Anaconda single and multiconductors and the BIW multiconductors remained functional. Part of the reason why the BIW multiconductors passed while the single conductors did not is that the latter were bent around a mandrel of much smaller diameter than the multiconductors.
- (5) Most properly installed EPR cables should survive an accident after 60 years for total aging doses of about 150-200 kGy and for moderate ambient temperatures of 45°C-55°C. By 200 kGy, the residual elongation of the EPR materials that had a bonded CSPE jacket approached zero. Some of the cables with essentially zero elongation remaining at the end of aging performed acceptably in the subsequent LOCA tests.

---

<sup>7</sup>IR represents insulation resistance in this section.

### Miscellaneous Cable Types

- (1) Three conductors out of 35 failed during the accident tests, one Kapton conductor from each of the three aging exposures. In each case, the conductors had been damaged during installation or handling. The Rockbestos coaxial cables had minimum IRs, in some cases low enough to affect the accuracy of radiation monitoring circuits.
- (2) The accident IRs of the Rockbestos coaxial cable decreased slightly as aging increased. The accident IRs of the Kerite cable decreased more significantly with aging, with up to about a two orders of magnitude difference between unaged and aged cables.
- (3) After aging and accident testing, several conductors failed a 5-minute post-accident dielectric withstand test. They included conductors that had failed during the accident tests, as well as an additional five Kapton conductors after the accident test on unaged cables, one Kerite conductor after each of the accident tests of cables that had been aged for 3 and 6 months, and all three Kerite conductors after the accident test of cables that had been aged for 9 months.
- (4) All the conductors from the accident test that followed the 9-month aging exposure were subjected to a mandrel bend and an additional dielectric test. All passed, including the Kerite conductors that had failed the post-accident dielectric test, and the Kapton conductor that had failed during the accident test. The Kerite conductors apparently had dried sufficiently to allow them to pass the test.
- (5) If properly installed, most of the various miscellaneous cable products tested should survive an accident after 60 years for total aging doses of at least 150 kGy or higher, and for moderate ambient temperatures of 45°C-55°C. By 200 kGy, the residual elongation of the silicone rubber cables approached zero. The cables with essentially zero elongation remaining at the end of aging performed acceptably in subsequent LOCA tests.

### Submergence and High Temperature Steam Testing

- (1) EPR cables generally survived to higher temperatures than XLPO cables. XLPO-insulated conductors had no insulation remaining at the end of the test (after a 400°C peak exposure).
- (2) XLPO cables generally performed better than EPR cables in submergence tests and in post-submergence dielectric testing. By the end of the final dielectric test (after a 40 time cable diameter mandrel bend), only 1 of 11 XLPO-insulated conductors had failed, while 17 of 20 EPR-insulated conductors had failed.
- (3) Several cables that performed well during the submergence test failed post-submergence dielectric withstand testing (either before or after the mandrel bend) indicating that both the IEEE Std 383 tests can cause otherwise functional cables to fail.
- (4) The IEEE Std 383-1974 dielectric withstand tests are very severe, even if a mandrel bend is not performed. This is evidenced by the failure of 9 conductors and near-failure of 3 more in the post-submergence dielectric withstand test, only 2 of which were showing strong indications of degradation during submergence.

Based on the results from LOCA testing on three groups of cables for life extension possibilities, several important conclusions are cited in Reference 5.35. Most cables successfully passed the accident exposures following accelerated aging (with a factor of 80) to normal service life of 20, 40, and 60 years (see Table 5.14). However, further studies with lower acceleration factors or naturally-aged cables are necessary. There are several cable samples which opened 1 amp fuses during accident exposures, with earliest failure (other than the damaged polyimide cables) at 80 hours into the accident simulation. Other samples had IR readings early in the accident exposure that might be marginal for some applications. Several polyimide failures were attributed to handling damages during test setup. Qualification using single conductors for multiconductor



cables was found to be non-conservative, specifically in estimating accident IRs. Total thermal lag time was typically 3 minutes for the multiconductor cables and 30 seconds for the single conductors tested. Finally, the IR measurements were found independent of applied voltage range, and discrete time IR testing appeared suitable for monitoring performance. However, IR values had very little correlation with the amount of aging in the cable's insulation and jacket materials. The elongation-at-break measurements were the best condition-monitoring method to assess the physical condition of the polymeric materials. Indenter modulus testing mirrors the effectiveness of the elongation data on certain polymers. None of the electrical tests detect incipient degradation in cable's insulating system. Rather, by the time any electrical parameter indicates trouble in an electrical circuit, the degradation in the cables may have reached a point where their replacement is needed to eradicate the problem.

Based on the results presented in Tables 4.11 on aging degradation and Table 5.14 on LOCA responses of several commonly used cables in U.S. nuclear power plants, the following conclusions are made from this review:

Most cable materials, except a few insulation materials, become completely brittle at the end of 50Mrad irradiation together with standard thermal aging conditions. At the end of accident irradiation, and before DBA steam exposure all have zero elongation values. Jacket materials degrade much faster than insulation products. Therefore, issues relating to aging sequence, synergistic effect, dose rate effect, and other relevant considerations during pre-aging of the EQ process can have very little impact on the final state of the cable before testing for the accident steam conditions.

Even with zero elongation properties before the DBA steam testing, most cables survived saturated steam conditions during LOCA. Some Dekorad and Okolon multiconductors, and Kapton-insulated cables failed during LOCA after being exposed to at least 174 hours of saturated steam. Failures of Dekorad and Okolon cables presumably are attributable to severe degradation of bonded Hypalon jackets on individual conductors and the mechanical failure of the severely degraded Hypalon overall jacket. Failures of Kapton-insulated cable are found to be due to mishandling of specimens during testing. The findings from these studies indicate that accident steam conditions used in the EQ process may not be that detrimental to cable performances during an accident, as long as cables are not physically disturbed from their installed positions (which might cause cracking).

Minimum IR values during accident steam exposure are important for cables qualified for certain applications. Therefore, cables passing EQ requirements should demonstrate adequate IR threshold for specific applications, especially for I&C use. To assess the physical condition of these cables, parameters such as tensile properties, indenter modulus should be monitored at each juncture of the EQ process.

## **5.10 TMI-2 Experience**

The TMI-2 accident provides a unique opportunity to evaluate cables after a real accident. Reference 5.37 reports on TMI-2 cable sections, connected to the HP-R-214 Dome Monitor, that were removed after the accident. The testing showed:

1. No detectable difference between cable in conduit or out of conduit.
2. No damage to the cable compared to a virgin cable.

Reference 5.38 discusses analyses of the dome radiation monitor at TMI-2; this was the only instrument inside containment capable of measuring the high radiation levels which might be present during a LOCA. The

Table 5.14 Summary of Results from NUREG/CR-5772 on LOCA and NUREG/CR-5655 on Fragility (Ref. 5.36)

Cable Manufacturer	Insulation/Jacket Materials	Samples Passed DBA	Peak DBA** Temperatures(°F)	Max. TID** (Mrad)	Fragility* Temperatures(°F)	Remarks
Brand Rex	XLPE w/CSPE Jacket	9 of 9	345/385	133/200	329/725	Minimum IR10 <sup>5</sup> Ω-100 m
Rockbestos	Firewall III; XLPE w/Neoprene Jacket	11 of 12	345/346	169/200	412/608	1 of 4 energized 9 month samples whose fuse opened at about 84 hrs into LOCA
Raychem	Flamtrol; XLPO w/CSPE Jacket	7 of 7	345/340	163/200	627/726	Minimum IR10 <sup>5</sup> Ω-100 m
Samuel Moore	Dekoron Polyset; XLPO w/CSPE Jacket	12 of 12	345/unknown	146/unknown	408/569	Minimum IR5x10 <sup>4</sup> Ω-100 m
Anaconda	Y-Flame Guard FR-EP; EPR w/CPE Jacket	9 of 9	345/385	140/200	453/742	Minimum IR10 <sup>4</sup> Ω-100 m
	Flame Guard EP; EPR w/individual CSPE Jacket and overall CSPE Jacket	12 of 12	345/385	155/200	546/717	
Okonite	Okolon; EPR w/CSPE Jacket	10 of 11	345/355	169/200	320/729	Minimum IR10 <sup>5</sup> Ω-100 m. One failed 174 hrs into LOCA
Samuel Moore	Dekoron Dekorad Type 1952 Single Conductor; EPDM w/individual CSPE Jacket	6 of 6	345/340	161/200	474/698	Minimum IR10 <sup>5</sup> Ω-100 m. Three failed after 178,181, and 220 hours into LOCA. Hypalon bonded jacket and insulation interaction effect.
	Dekoron Dekorad Type 1952 Multi-conductor; EPDM w/individual CSPE Jacket and overall CSPE Jacket	13 of 16	345/340	166/200	345/345 (Failed during DBA)	
Kerite	Kerite 1977; FR w/FR Jacket Thicker insulation w/thinner Jacket	4 of 4	345/340	158/200	218/702	Minimum IR350 Ω-100 m.
	Kerite 1977; FR w/FR Jacket Thinner insulation w/thicker Jacket	5 of 5	345/340	158/200	218/702	
Rockbestos	RSS-6-104/LE Coax	6 of 6	345/331	136/200	430/712	Minimum IR10 <sup>4</sup> Ω-100 m
	Firewall; SR w/Fiberglass braided Jacket	7 of 7	345/295	133/100	742/744	Minimum IR10 <sup>4</sup> Ω-100 m
Champlain	Polyimide; Kapton w/o Jacket	10 of 13	345/360	144/140	743/751	4 behaved erratic including 3 failed due to handling damage
BIW	Bostrad 7E; EPR w/individual CSPE Jacket and overall CSPE Jacket	18 of 18	345/340	167/200	273/723(single) 289/707	Minimum IR2100 Ω-100 m Can affect low current ckts.

NOTES: Except fragility temperature values (from NUREG/CR-5655), all other information are taken from LOCA test results presented in 3 volumes of NUREG/CR-5772 and Ref. 5.36.

Statements in the "Remarks" column are based on results from DBA testing of 0-, 3-, 6-, and 9-month simulations.

\* Minimum high temperature test values for two failure criteria; Failure Criteria @  $\leq 100$  kΩ-100 m /  $\leq 0.1$  kΩ-100 m.

\*\* First values are taken from NUREG/CR-5772 reports for all four LOCA simulations and the second values are industry's qualification test values on similar cables given in Ref. 5.36.

detector failure modes included moisture intrusion into the electronics package, DC feedback in the preamplifier, MOS transistor degradation, and electrolytic capacitor failure. Using degradations in transistor current gain and elastomeric material properties, the total gamma-radiation dose received by the Dome Monitor (HP-R-214) electronics inside the stainless-steel vessel and the dose to the multiconductor cable outside the vessel was estimated. Table 5.15 lists the doses received by the radiation detectors, which were analyzed at Sandia.

**Table 5.15 Estimated Gamma Radiation Doses Received at TMI-2 Radiation Detectors**  
(Ref. 5.38)

Containment Elevation (Feet)	Instrument	Dose (Mrad)
305	HP-R-211	0.25
305	HP-R-212	0.45
347	HP-R-213	0.99
372	HP-R-214(Cable)	7.90
372	HP-R-214(Detector)	0.22

Bennett (Ref. 5.39) presented information on the accident environment at TMI-2:

Peak Temperature:	185°F
Pressure:	Atmospheric
Atmosphere:	Air
Total Dose:	1-10 Mrad
Relative Humidity:	100%

These parameters were used to establish exposure conditions for the laboratory control samples. None of the techniques (FTIR, RAMAN spectroscopy, density profiling) used to analyze surface damages was sensitive at a dose level less than, or equal to, 10 Mrad as estimated in the TMI-2 accident environment.

**Table 5.16 Penetration Environment and Damage Summary** (Ref. 5.40)

Penetration Section	Penetration Elevation (ft)	Irradiation (R/hr)	Cable References to Water			
			# of Cables	Cable Marginal <sup>a</sup>	Cables <sup>b</sup> Below Water	Inoperable (%)
R400, R402 &						
R407	292	20 to 50	117	117	0	4.3
R405	292	50 to 1000	5	4	1	80.0
R406	292	20 to 50	6	4	2	16.7
R504	323	20	10	4	0	30.0
R505	319	20	10	3	0	10.0
R506	323	20	19	4	0	31.0
R534	300	20	14	6	0	35.7
R607	292	20 to 50	52	38	14	61.5

a. Cables which were partially above and below water level. b. Peak water level 292-ft elevation.

Reference 5.40 summarizes the results of diagnostic tests conducted on selected cable channels within the TMI-2 reactor building. Two hundred and thirty-three cables were tested in situ; anomalous electrical behavior was observed in 103 (44%) of them. Of these, 57 cables (24%) contained inoperable circuits; Table 5.16 is a summary of inoperable cables, by penetration, and also includes some general environmental conditions.

Dandini and Bustard (Ref. 5.41) described the results of examining a short length of Raychem Flamtrol cable, which was connected to the HP-RT-211 radiation detector from the TMI-2 containment building. The ultimate tensile strength, the percent elongation-at-break, and the insulation resistance were measured. All three techniques detected no damage in comparison with a "virgin" specimen.

Yancey (Ref. 5.42) presented the results of instrument cables used with two Foxboro pressure transmitters and a Bailey liquid level transmitter. Raychem manufactured the cable installed with the core flood transmitters, and Anaconda supplied the test cable (FR-EPR insulation w/CSPE jacket). The average total dose of radiation received by the two coils of cables was 12 Mrad. The cables showed no major signs of deterioration during irradiation. The insulation resistance decreased 10% and the dielectric constant increased 1%; this disappeared when the fuel was removed, indicating the apparent effect of the presence of a radiation source.

Meininger (Ref. 5.43) also reported the results from in-place tests on 460 circuits; 178 abnormalities were identified, of which 36 circuits failed, 38 circuits showed significant changes, and 104 circuits showed minor changes. The circuits represented a two-wire transmission line from the reactor building wall up to and including the end device. Generally, there was no evidence of moisture and degradation which might be expected as a result of corrosion.

R607 is a 137-channel instrumentation and control penetration. Of those available channels, 49 were initially chosen for testing. Most screening tests indicated there were several broken wires and corroded contacts. Measurements of insulation resistance between wires of different cables yielded evidence of "cross talk," an interference between wires in the penetration. The penetration was at the 292-ft elevation that was submerged until the water level in the reactor building's basement was lowered, and water remaining in the penetration may be the cause of the cross talk. The predominant anomaly encountered was a shift in the cable's characteristic impedance, which also could be caused by the ingress of moisture through the insulation. Subsequently, three additional channels were tested. Of the 52 channels, 47 exhibited anomalous behavior, and 33 of these were inoperable.

Five cables were tested in penetration R405 and all exhibited anomalous behavior; four were judged inoperable. Also, fourteen instrumentation cables were tested in penetration R534; anomalies were observed in seven, of which five were judged inoperable. Cross-talk voltages were observed, which suggested possible corrosion or water contamination. However, the environmentally sealed splices survived well.

Penetration R506 contains reactor control circuits, including current transformers, level (pressure) transmitters, and temperature, pressure, and limit switches. Nineteen cables were tested; 16 exhibited anomalous behavior, of which six were judged inoperable. Additionally, of 39 pressurizer heater cables, anomalous behavior was observed in 12. Five were inoperable; one with an open circuit, one with a short circuit, and three with low insulation resistance.

Since the penetrations evaluated were selected because of their high probability of impairment, the data are not statistically representative of the 1800 circuits in the reactor building, but serve to indicate the circuit damage to be expected from this type of accident. Finally, hydrogen burn did not substantially damage the instrumentation.

The effect of TMI -2 accident and post-LOCA environments on cable/connection components were studied by Westinghouse Hanford Company (Refs. 5.44 and 5.45). These components involved penetration assemblies, terminal boxes (NEMA boxes, pull boxes), splices, terminal blocks, bulk cable, and connectors. A total of 1800 in-containment electrical channels were identified. About 10-20% of them were subjected to in situ electrical tests. During the first day of the accident, the environment inside the reactor containment was one of intense radiation, steam, temperature excursions, a hydrogen burn, and a chemical suppression spray. Post-accident environmental conditions included low-level dose rates that integrate to 0.1 Mrad and moisture exposure either by submersion or high relative humidity. As the accident progressed, spurious electrical signals were observed on plant instrumentation systems. Shortly after the reactor scram, the output signals on any of the plant self-powered-neutron-detectors rose to 3 times that for normal full power flux levels. Thermocouple signals from adjacent positions varied by as much as 2000°F. Based on the preliminary in situ test data on 25% of the 1800 circuits and laboratory testing of cables subjected to both electrical and mechanical tests, elongation was essentially unchanged over the length of the cable, and the trend of decreasing tensile strength with increasing height did not follow the radiation pattern. Therefore, it was hypothesized that the reduction in tensile strength was more likely due to heat from hydrogen burn. Moreover, no significant difference in electrical properties were observed between the different cable sections.

The analysis of polar crane pendant cable had been identified with cuts and abrasions which indicated that the impact of maintenance accidents on cables might have compromised their ability to function properly (Ref. 5.46). The radioactive contamination present on the portion of this cable lying horizontally on the D-ring was approximately 10 times greater than found on a contiguous section that hung vertically. Testing indicated that the contamination caused no dramatic changes in either the material or the electrical properties of this cable.

### **5.11 Effect of Hydrogen Burn**

The hydrogen-burn environment differs from LOCA transient profiles and depends on the specific reactor and accident sequence. The containment's size and geometry as well as the amount of hydrogen generated, are important. The typical LOCA environmental test profile has a 10-second ramp to perhaps 340°F, which is maintained for several hours. A hydrogen-burn environment is likely to have temperature increases from LOCA temperatures up to 1500K (and pressures up to 400 kPa) with a ramp time of about 10 seconds. The temperature is not maintained and drops off relatively rapidly (depending on many factors). It should be noted that hydrogen-burn conditions are not part of the EQ requirements, and typically are considered as part of a severe accident scenario. Since cables can be affected significantly from these conditions during an accident, a short discussion on the subject is included here.

The effects of hydrogen burn on a non-safety related cable at TMI-2 (Ref. 5.46) were studied by analyzing char patterns; the results indicated that shielding plays a major role, and survivability depends on its location within the containment. The hydrogen-burn survival program concluded that each piece of equipment will respond differently because of differences in thermal mass, geometry, and location, shielding effects, and the hydrogen burn itself (Ref. 5.47). Cables installed in conduits will experience significantly smaller rises in temperature than exposed cables.

An EPRI study tested 25 cable types in a series of large-scale hydrogen-burn simulations at NTS (Ref. 5.48). From one to four specimens of each cable type, totalling 56 specimens, were exposed to hydrogen burns; 52 cable specimens from 24 cable types were classified as safety-grade cables. Each cable was exposed passively in from one to eleven experiments. Some cables had no visible damage, but those exposed to the more severe burns had extensive damage in the form of charring, cracking, and bulging of the outer jackets. The cables,

submerged in water, were tested in an ac withstand-test at rated voltage, an insulation resistance test at 500 volts, and a dc withstand test at three times rated voltage. About 50 out of 52 safety-grade cables passed the performance test after the burns, even though many had been exposed in several experiments. This study also acknowledged the fact that local variations in the environment were very significant.

To augment EPRI-NTS study, NRC sponsored several tests at SNL's Central Receiver Test Facility (CRTF) to simulate the heat flux incident upon test specimens for the 13 volume-percent hydrogen burn at NTS using solar reflectors (Refs. 5.49-5.51). In addition to several electrical devices, cables included in these tests were Okonite Okolon single conductor cable, Rockbestos Firewall III 3-conductor cable, and Brand Rex XLP/CU 3-conductor cable (Ref. 5.49). Blistering and cracking of the jacket materials were observed for all cables. Unlike Okonite and Brand Rex which also exhibited flaking and charring, no significant flaking was seen on Rockbestos. However, all samples maintained the applied voltage and no short circuits were detected. Multiconductor cables were more able to withstand the effects of severe heat flux pulses than smaller diameter single conductor cables. Though multiconductor cables appeared severely degraded, their electrical properties remained essentially intact, i.e., insulation resistance remained in the range of  $10^{11}$ - $10^{12}$  ohm-ft. The single conductor Okonite samples, which had the largest change in the insulation resistance, had a value on the order of  $10^6$  ohm-ft.

Dandini (Ref. 5.50) described the results of accelerated aged and unaged samples of Brand Rex XLP/CU 12 AWG 3-conductor cable specimens subjected to simulated hydrogen burns of increasing severity. Visible damage to the cables increased with the severity of the pulse. Generally, aged samples experienced less severe visible damage than the unaged samples at each flux level. Blistering and coating with soot were common to all cable jackets above 1.5 flux levels. Crack penetration into the jacket exposed the insulation materials and the filler materials melted. After the exposure, all cables were hi pot tested. With one exception, all insulation maintained their integrities. The exception was the black conductor from the unaged sample, in which the insulation (exposed to 3.0 pulse) broke down within seconds after applying the 2400 Vac test voltage.

From several other simulations of various hydrogen-burn environments, SNL concluded that, if the expected temperatures are higher than LOCA temperatures, cables should be qualified for the more severe hydrogen-burn environment, or their installation inside the containment should be modified to protect them from the burn (e.g., install the cable in conduits).

#### **5.12 LOCA Testing of Damaged Cables**

Experiments were conducted to assess the effects of high potential testing of cables flooded with water, and to determine the amount of insulation necessary to survive aging (equivalent to 40 and 60 years of service) and a LOCA exposure (Ref. 5.52). Three types chosen for this program included (1) Okonite Okolon cable with EPDM insulation and bonded CSPE jacket, (2) Rockbestos SR cable with a fiberglass braid jacket, and (3) Brand Rex cable with XLPE insulation. Samples from each type were damaged at five locations. Each damage consisted of one-inch length with various depths of insulation removed by grinding to simulate cable conditions.

Based on the ultimate voltage-breakdown strength, the high potential testing of virgin Brand Rex cables at 35 kVdc did not fail the cables. Also, in a limited set of tests with applied dc voltages, there were no unexpected effects on length. To detect 7 mils of remaining insulation for Brand Rex cables, a test voltage of 35 kVdc suffices (1170 Vdc/mil based on the nominal insulation thickness). A test criteria for Rockbestos cables was not established since the level of damage that would allow the cable to survive an accident simulation could not be defined.

Brand Rex XLPE cables with 7 mils of insulation remaining are likely to survive in an accident after thermal and radiation aging to the conditions defined in this program. However, if higher applied voltages ( $> 110$  Vdc) or ac voltages had been used during the LOCA simulation, earlier failures may have occurred. Rockbestos SR cables with as little as 4 mils of insulation remaining have a reasonable probability of surviving in an accident after radiation (20 Mrad aging plus 110 Mrad accident dose) followed by thermal aging to the conditions defined in this test program. However, thermal aging may have been a significant factor (together with the reduced wall thickness) in causing two failures of Rockbestos SR cables. Thus, reduced thermal aging probably would lower the failure rate of these cables. Survival data for Okonite Okolon cables were not available because of failures after thermal aging. All of the intentionally damaged Okonite EPDM/CSPE cables, with less than 15 mils of insulation remaining, failed before aging was completed. The one undamaged cable failed during LOCA exposure shortly after the test chamber was filled with saturated steam. The one cable that had approximately 15 mils of insulation remaining caused a 1A fuse to open at 182 hours into the LOCA simulation, although there were earlier indications of its erratic behavior. The major causes of the Okonite cable failures are the extent of pre-conditioning by irradiation (including both aging and accident radiation doses) followed by thermal aging, and the presence of a bonded CSPE jacket that ages more rapidly than the underlying insulation.

The failures of Okonite EPDM/CSPE cables in this program, and one Okonite Okolon and three Dekorad in a previous program (Ref. 5.32) suggest that the bonded CSPE jacket is detrimental to overall integrity of the cable. Even the undamaged cable cannot meet its rating with the bonded CSPE jacket when thermal aging is performed according to the Arrhenius theory, as used in this testing. Another interesting result indicates that even though the Okonite cables sustained cracks during thermal aging (before the LOCA simulation), all of the cables then survived for some time. The first Okonite failure (opening of 1A fuse) occurred at 11 hours (just after the chamber's environment became saturated steam) and the final Okonite failure occurred at 182 hours into the LOCA profile (although there were indications of erratic behavior and, perhaps, even failure well before the fuse opened). However, no chemical spray was used during the LOCA simulation; its use would have caused failures to appear shortly after it was started because of the enhanced ground plane it creates.

Hanson (Ref. 5.53) studied EPR and XLPE cables subjected to various mechanical damages and accelerated aging conditions. EPR samples included artificial damages by scrapes, transverse cuts, and longitudinal cuts, whereas XLPE had only scrapes and transverse damages. Some samples were aged up to 1 MGy; others were thermally aged at  $130^{\circ}\text{C}$  for up to 50 days. The breakdown voltage was measured for cables under a variety of these conditions. Theoretical models were developed for electric field calculations and were used to analyze the breakdown voltage versus thickness data.

The study concluded that as long as there was more than 0.60 mm of insulation remaining in both material types, the breakdown voltage remained unchanged. For severe damage conditions (0.60 mm or less remaining insulation), the breakdown voltage decreased linearly with the decreasing thickness of the remaining insulation. The dielectric strengths for both cable materials were not affected by mechanical damage, except for XLPE with transverse cuts, in which dielectric strength appeared to decrease.

The accelerated aging used in this study did not affect the dielectric strength of undamaged or damaged cables, except for XLPE with radiation dose above 0.5 MGy (50 Mrad) when transverse cuts failed at very low voltages. The effect was most likely due to radiation-induced cross-linking causing the XLPE insulation to become brittle. The study also concluded that this might have been caused by stress fractures which was exacerbated by radiation.

The effects of cable length, bend radius, and ambient temperature on the breakdown voltage of undamaged cables also were studied. There was no observable difference in the dielectric strength of the longest cables compared to the shortest. Similarly, the strain ranging from about 5% to 15% caused by bends had no effect on the dielectric strength of the cables. Finally, statistical comparisons of the pore radii, and thus, dielectric strength for each temperature did not reveal any effect due to different ambient conditions.

A Japanese study on the effect of initial strain on the degradation of CSPE, chloroprene, SR, and EPR during irradiation is presented in Reference 5.54. Cable samples were elongated by certain ratio from their initial length and then irradiated to different dose levels at several different dose rates. This condition may simulate excessive pulling of cables during installation or conditions at sharp bends where initial stress conditions exist. The samples were irradiated at dose rates of 1, 5, 10 kGy/hr in air and 4.5 kGy/hr under oxygen pressure of 0.5 MPa at room temperature. Total doses ranged from 0.25 and 2.0 MGy. Constant strains of 50% and 100% of the original length were considered. Several mechanical tests were made such as elongation and strength at break, gel fraction, and swelling ratio.

The stress relaxations are very small in unirradiated and already irradiated samples, but large for samples undergoing irradiation indicating faster degradation of cables under stress in radiation environment. The permanent strains in the samples increased with the dose and were not affected by irradiation and heating. The degradation of tensile properties increases with the increase in total dose and initial strain.

### 5.13 Summary

In reality, in an accident cables may be exposed simultaneously to environments including total radiation dose and dose rate, oxygen, chemical spray, superheated and saturated steam, steam impingement, and hydrogen burn. The environmental qualification of these cables has followed both sequential and simultaneous simulations of aging and accident conditions to provide reasonable assurance of their survivability in an accident any time during their design life. Post-accident testing assesses their residual life after exposure to severe aging and LOCA conditions. The results presented in this section cover various elements that govern the environmental qualification of Class 1E cables. The effects of steam impingement are included to the extent necessary in establishing DBE environment with shielding considerations, fracture mechanics studies, and leak-before-break scenarios, and thus are not typically needed to be demonstrated in an EQ test program. In addition, the effect of high temperature and radiation, together with the saturated conditions during the qualification process, may overpredict the real-life degradation of cable materials.

Most studies on LOCA testing were performed by NRC at SNL, including a collaborative effort with the French Regulatory Agency, and JAERI in Japan. Studies in Great Britain and Germany have not been published. Also, some qualification tests performed by test laboratories for the cable industry and utilities, and material tests performed by the manufacturers were not reviewed. However, the results from these tests could be of significant value to this research program.

Examination of cables after the TMI accident give precarious results on the survivability of cables inside the containment. However, these studies did not provide the most important information relating to the wiring systems' responses during and immediately after the accident. Although many circuit failures or malfunctions were reported, the causes of these failures or their physical conditions were not completely analyzed to derive any inferences for future cable qualification. However, studies on TMI cables after the accident indicate that the total integrated dose on any cable product was about 12 Mrad or less, and the majority of electrical circuit failures were attributed to submergence or exposure of saturated steam at the cables' interfaces. Many of these



circuit failures were assumed by many as non-safety related. Some studies indicated that very few circuits failed immediately after the accident and a large number of failures occurred several days later.

Studies on LOCA-testing of the EQ process have produced a large mass of data. The variety of topics and cable materials included makes it difficult to understand and derive conclusions on a particular issue. Although most results provided some insight into the responses of various cable materials and constructions in the LOCA, in some cases, they raised more questions than answers on survivability. Many earlier studies at SNL involved detailed evaluations of failures that were reported during the test, and often, these were due to experimental anomalies. On the other hand, recent studies used an approach which considers a cable to have failed when it cannot carry a fixed amount of current (e.g., 1 amp); this test has been a subject of discussion among many researchers and the industry.

There is some information showing that a cable's condition is approximately the same after LOCA radiation, regardless of how aging is accelerated and how much the cable's condition differs at the end of aging. Further evidence could be very important; because it would simplify qualification, if it was concluded that the sequence of thermal and radiation aging (or whether thermal and radiation aging are conducted simultaneously) makes little difference to the end result.

No single research appears to have been done on the adequacy of LOCA profiles. Significant research was performed on specific elements, such as the effect of superheated steam, the presence of oxygen, and a few other variables. However, recent SNL studies (Refs. 5.31-5.34) have evaluated certain elements of the LOCA profile. Gleason (Ref. 5.36) discussed the results from these studies on LOCA profile adequacy, duration of test, single/multiple peaks, and post-LOCA mandrel bends. Based on these results, he concluded that substantial margin in LOCA profiles, excessive severity of post-LOCA mandrel bends, and no effect from multiple peak testing exist.

Issues relating to LOCA sequence, dose rate effects, synergistic effects, presence of oxygen, use of Co-60 gamma source, chemical spray effects, and hydrogen burn have been largely resolved. Questions on single versus multiconductor performance, wiring system problems, determination of how much oxygen is present in an actual LOCA environment, and margins available in LOCA-test profiles need further studies.

There is not much research on hot spots or weak links in cable systems. Recent studies by Siemens of Germany, and a cooperative program by U.S. and France provide some insights. More insights may be gained once the results from the EPRI sponsored study at UConn are available. The SNL study on artificially damaged cables partially simulated installation damages. Cables and wiring systems from operating or decommissioned reactors should be considered for further testing and the program should focus on issues and on cable products that have raised concerns in earlier studies.

## 5.14 References

- 5.1 "IEEE Standard for Qualifying Class 1E Equipment for Nuclear Power Generating Stations," IEEE Std 323-1974.
- 5.2 "IEEE Standard for Type Test of Class 1E Electric Cables, Field Splices, and Connections for Nuclear Power Generating Stations," IEEE Std 383-1974, ANSI N41.10-1975, 1974.
- 5.3 "Environmental Qualification of Certain Electric Equipment Important to Safety for Nuclear Power Plants," NRC Regulatory Guide 1.89, Rev.1, 1984.
- 5.4 "Environmental Qualification of Electric Equipment Important to Safety for Nuclear Power Plants," Code of Federal Regulations, Title 10, Part 50.49, 1983.
- 5.5 Bonzon, L.L., "Equipment Qualification and Survivability Research at Sandia National Laboratories," SAND85-1712C, SNL, 1985.
- 5.6 Bustard, L.D., Clark, J., Medfod, G.T., Kolaczowski, A.M., "Equipment Qualification (EQ) - Risk Scoping Study," NUREG/CR-5313, SAND88-3330, 1989.
- 5.7 Bonzon, L.L., Wyant, F.J., Bustard, L.D., and Gillen, K.T., "Status Report on Equipment Qualification Issues Research and Resolution," NUREG/CR-4301, SAND85-1309, 1986.
- 5.8 Bonzon, L.L., "An Experimental Investigation of Synergisms in Class 1 Components Subjected to LOCA Typetests," NUREG/CR-0275, SAND78-0067, 1978.
- 5.9 Paulson, D.V. and Carfagno, S.P., "A Review of Class 1E Electrical Cable Qualification Data," FIRL Report F-C4598-1, 1977.
- 5.10 Bustard, L.D., "The Effect of LOCA Simulation Procedures on Ethylene Propylene Rubber's Mechanical and Electrical Properties," NUREG/CR-3538, SAND83-1258, 1983.
- 5.11 Bustard, L.D., "The Effect of LOCA Simulation Procedures on Cross-Linked Polyolefin Cable's Performance," NUREG/CR-3588, SAND83-2406, 1984.
- 5.12 Yoshida, K., Nakase, Y., Okada, S., Ito, M., Kusama, Y., Tanaka, S., Kasahara, Y., Machi, S., "Methodology Study for Qualification Testing of Wire and Cable at LOCA Condition," Eighth Water Reactor Safety Research Information Meeting, October 27-31, 1980. NUREG/CP-0023, Vol. 2, 1981.
- 5.13 Kusama, Y., Okada, S., Yoshikawa, M., Ito, M., Yagi, T., Nakase, Y., Seguchi, T., and Yoshida, K., "Methodology Study for Qualification Testing of Wire and Cable at LOCA Conditions," Tenth Water Reactor Safety Research Information Meeting, October 12-15, 1982. NUREG/CP-0041, Vol. 5, 1983.
- 5.14 Yoshida, K., Seguchi, T., Okada, M., Ito, M., Kusama, Y., Yagi, T., and Yoshikawa, M., "Progress on Qualification Testing Methodology Study of Electric Cables," Eleventh Water Reactor Safety Research Information Meeting, October 24-28, 1983. NUREG/CP-0048, Vol. 5, 1984.
- 5.15 Bustard, L.D., Chenion, F., Carlin, C., Alba, G., Gaussens, G., and Le Meur, M., "The Effect of Alternative Aging and Accident Simulations on Polymer Properties," NUREG/CR-4091, SAND84-2291, 1985.
- 5.16 Bennett, P.R., St. Clair, S.D., and Gilmore, T.W., "Superheated-Steam Test of Ethylene Propylene Rubber Cables Using a Simultaneous Aging and Accident Environment," NUREG/CR- 4536, SAND86-0450, 1986.
- 5.17 Ito, M., Kusama, Y., Yagi, T., Okada, S., Yoshikawa, M., and Yoshida, K., "Progress on Qualification Testing Methodology Study of Electric Cables," Twelfth Water Reactor Safety Research Information Meeting, October 22-26, 1984. NUREG/CP-0058, Vol.5, 1985.
- 5.18 Kusama, Y., Yagi, T., Okada, S., Ito, M., Yoshikawa, M., Yoshida, K., Tamura, N., and Kawakami, W., "Progress on Qualification Testing Methodology Study of Electric Cables," Fourteenth Water Reactor Safety Information Meeting, October 27-31, 1986, NUREG/CP-0082, Vol.3, 1987.

- 5.19 Bonzon, L.L., "Radiation Signature Following the Hypothesized LOCA," NUREG76-6521, SAND76-0740, 1977.
- 5.20 Leadon, R.E. and Lurie, N.A., "Damage Mechanisms to Cables in Reactor Loss-of-Coolant Accident Environments," Nuclear Technology, Vol. 46, 1979.
- 5.21 Buckalew, W.H., Wyant, F.J., and Lockwood, G.J., "Response of Rubber Insulation Materials to Monoenergetic Electron Irradiations," NUREG/CR-3532, SAND83-2098, 1983.
- 5.22 Buckalew, W.H., "First Results from Electron Photon Damage Equivalence Studies on a Generic Ethylene-Propylene Rubber," NUREG/CR-4543, SAND86-0462, 1986.
- 5.23 Buckalew, W.H., Chenion, J., Carlin, F., Gaussens, G., Le Tutour, P., and Le Meur, M., "U.S./French Joint Research Program Regarding the Behavior of Polymer Base Materials Subjected to Beta Radiation," NUREG/CR-4530, SAND86-0366, IPSN-1/88, Vol. 3, 1989.
- 5.24 Buckalew, W.H., "Cobalt-60 Simulation of LOCA Radiation Effects," NUREG/CR-5231, SAND88-1054, 1989.
- 5.25 Gillen, K.T., Clough, R.L., Ganouna-Cohen, G., Chenion, J., and Delmas, G., "Loss of Coolant Accident (LOCA) Simulation Tests on Polymers: The Importance of Including Oxygen," NUREG/CR-2763, SAND82-1071, 1982.
- 5.26 Yagi, T., Kusama, Y., Ito, M., et al., "Swelling Behavior of Gamma-ray Irradiated Elastomers in Boiling Spray Solution," JAERI-M 83-072, Department of Development, Takasaki Radiation Chemistry Research Establishment, JAERI, Japan. 1983.
- 5.27 Okada, S., Kusama, Y., Ito, M., Yagi, T., Yoshikawa, M., Yoshida, K., Tamura, N., and Kawakami, W., "Progress on Qualification Testing Methodology Study of Electric Cables," Thirteenth Water Reactor Safety Research Information Meeting, October 22-25, 1985, NUREG/CP-0072, Vol.3, 1986.
- 5.28 Minor, E.E. and Furgal, D.T., "Equipment Qualification Research Test of Electric Cable with Factory Splices and Insulation Rework Test No.2 Report No. 1," NUREG/CR-2932/1 of 2, SAND81-2027/1 of 2, 1982.
- 5.29 Minor, E.E. and Furgal, D.T., "Equipment Qualification Research Test of Electric Cable with Factory Splices and Insulation Rework Test No.2 Report No.2," NUREG/CR-2932/2 of 2, SAND81-2027/2 of 2, 1982.
- 5.30 Kawakami, W., Kusama, Y., Yagi, T., Arakawa, K., Ito, M., Okada, S., Yoshikawa, M., Yoshida, K., and Tamura, N. "Progress on Qualification Testing Methodology Study of Electric Cables," Fifteenth Water Reactor Safety Research Information Meeting, October 26-29, 1987, NUREG/CP-0091, Vol.3, 1988.
- 5.31 Jacobus, M.J., "Aging, Condition Monitoring, and Loss-of-Coolant-Accident (LOCA) Tests of Class 1E Electrical Cables: Crosslinked Polyolefin Cables," NUREG/CR-5772, SAND91-1766/1, Vol.1, 1992.
- 5.32 Jacobus, M.J., "Aging, Condition Monitoring, and Loss-of-Coolant-Accident (LOCA) Tests of Class 1E Electrical Cables: Ethylene Propylene Rubber Cables," NUREG/CR-5772, SAND91-1766/2, Vol.2, 1992.
- 5.33 Jacobus, M.J., "Aging, Condition Monitoring, and Loss-of-Coolant-Accident (LOCA) Tests of Class 1E Electrical Cables: Miscellaneous Cable Types," NUREG/CR-5772, SAND91-1766/3, Vol.3, 1992.
- 5.34 Jacobus, M.J. and Fuehrer, G.F., "Submergence and High Temperature Steam Testing of Class 1E Electrical Cables," NUREG/CR-5655, SAND90-2629, 1991.
- 5.35 Jacobus, M.J., "Loss-of-Coolant Accident (LOCA) Testing of Aged Cables with Application to Nuclear Plant Life Extension," Nuclear Engineering and Design, 134, pp.267-275, 1992.
- 5.36 Letter report from J. Gleason to R. Lofaro on Analysis of the Sandia Reports NUREG/CR-5772 and NUREG/CR-5655, December, 1994.

- 5.37 Richards, E.H. and Dandini, V.J., "Analysis and Testing of the HP-R-214 Dome Monitor Cable From Three Mile Island Unit 2," GEND-INF-072, SNL, 1986.
- 5.38 Murphy, M.B., Mueller, G.M., and Jernigan, W.C., "Analysis of the TMI-2 Dome Radiation Monitor," GEND-INF-063, SNL, 1985.
- 5.39 Bennett, P.R., "Progress Report on the TMI-2 Equipment Examination Program: Beta Radiation Damage Assessment," SAND84-1520, UC-78, 1985.
- 5.40 Helbert, H.J., et al., "TMI-2 Cable/Connections Program FY-84 Status Report," GEND-INF-056, EG&G, 1984.
- 5.41 Dandini, V.J. and Bustard, L.D., "HP-RT-211 Cable Analysis," GEND-INF-010, EG&G, 1981.
- 5.42 Yancey, M.E., "Irradiation Test Report - Foxboro E11GM, Bailey BY3X31A, and Flame Retardant Ethylene Propylene Instrumentation Cable," GEND-INF-058, 1984.
- 5.43 Meininger, R.D., "Three Mile Island Technical Information and Examination Program Instrumentation and Electrical Summary Report," GEND 050, 1985.
- 5.44 Cannon, N.S., Helbert, H.J., Trijillo, R., Hecker, L.A., and Cannon, C.P., "Effect of Three Mile Island LOCA on Cables, Connector Components," HEDL-SA-2980, 1983 Winter Meeting of ANS, San Francisco, 1983.
- 5.45 Cannon, C.P. and Cannon, N.S., "The Effects of the TMI-2 Accident and Post-Accident Environments on Cable/Connection Components - Program Status Report," Proc. of Intl. Conf., San Diego, 1985.
- 5.46 Trujillo, R.E., Richards, E.H., and Cannon, C.P., "Analysis of the Polar Crane Pendant Cable from Three Mile Island - Unit 2," GEND-INF-069, SNL, 1986.
- 5.47 McCulloch, W.H., Ratzel, A.C., Kempka, S.N., et. al. , "Hydrogen Burn Survival: Preliminary Thermal Model and Test Results," NUREG/CR-2730, SAND82-1150, 1982.
- 5.48 Achenbach, J.A., Miller, R.B., Srinivas, V., "Large-Scale Hydrogen Burn Equipment Experiments," EPRI NP-4354, Westinghouse Electric Corporation, 1985.
- 5.49 Dandini, V.J. and Aragon, J.J., "Simulation of an EPRI-Nevada Test Site (NTS) Hydrogen Burn Test at the Central Receiver Test Facility," NUREG/CR-4146, SAND85-0205, 1985.
- 5.50 Dandini, V.J., "Testing of Nuclear Qualified Cables and Pressure Transmitters in Simulated Hydrogen Deflagrations to Determine Survival Margins and Sensitivities," NUREG/CR-4324, SAND85-1481, 1985.
- 5.51 Berry, D.L., "Fire Protection and Hydrogen Burn Equipment Survival Research," Thirteen Water Reactor Safety Research Information Meeting, October 22-25, 1985, NUREG/CR-0072, Vol.3, 1986.
- 5.52 Vigil, R.A. and Jacobus, M.J., "Aging, Loss-of-Coolant Accident (LOCA), and High Potential Testing of Damaged Cables," NUREG/CR-6095, SAND93-1803, 1993.
- 5.53 Hanson, B.A., "The Effect of Aging on the Breakdown Voltage of Artificially Damaged Cables," PhD Thesis (A.B. Reynolds as Advisor), University of Virginia, Charlottesville, SEAS Reort No. UVA/529875/MANE94/101, 1994.
- 5.54 Yagi, T., Kusama, Y., Itoh, M., and Kawakami, W., "Radiation Degradation of Insulating Materials under Stress," Conf. OPERA, Lyon, France, 1989.

## 6. CONDITION MONITORING METHODS FOR CABLES

Nuclear power plants contain a myriad of electric cables of all sizes, voltage ratings, and lengths delivering electric power to much vital, as well as non-vital equipment. Invariably, cables are insulated with some form of polymeric insulation. In this section, the focus is limited to low voltage (<1000 volts) safety-related cables that are used for power supply, control, and instrumentation applications inside the containment. The polymers used in this class of cables vary from noncrystalline types, such as plasticized PVC and Tefzel, to semicrystalline polyolefins, usually crosslinked polyethylene and EPDMs.

Despite all the advances in the technology of cable insulation, insulating materials can be damaged mechanically during transportation, installation, and maintenance, or they may gradually age from exposure to heat, radiation, moisture, and chemicals. On-site testing of the condition of these cables is necessary to ensure their continued reliability in service, and to predict their remaining life. Cables must operate safely, and reliably in the harsh steam environments produced by postulated design-basis events (e.g., MSLB, LOCA). There is a world-wide search for effective testing methods which can assess the present condition of a cable's electrical property and can also predict its remaining life and LOCA survivability with some assurance. Researchers and engineers believe that one all-encompassing method or procedure for achieving this goal does not exist.

The desirable attributes of such a condition monitoring (CM) technique are (Ref. 6.1): (a) non-intrusiveness; (b) reproducible results; (c) non-destructive; (d) unaffected by, or can be adjusted for, the environment (i.e., variations in temperature, dose rate or moisture); (e) sensitive to the rate of degradation (preferably during an incipient-failure condition); (f) applicable to a wide range of materials and construction; (g) portability of test equipment; (h) assessment along the entire length of cables; and finally (i) cost-effectiveness. An additional important attribute for safety considerations is that CM techniques be able to detect cable characteristics, the level of which reliably predicts LOCA survivability. Since the primary objective of this technique should be to monitor the rate of degradation in the cable's insulation and jacket materials in an inside-containment environment of a nuclear power plant, developing a single test method (or a combination of several techniques) satisfying all these attributes has been a challenging issue.

The EPRI conducted two workshops, the first in 1988 (Ref. 6.2) and the second in 1993 (Ref. 6.3), to bring the utilities, research organizations, cable manufacturers, test equipment manufacturers and consulting firms, and universities from all over the world to share their experiences and to formulate an aggressive research program. In the first workshop, all agreed that the conventional monitoring techniques could not characterize the gradual degradation of aging cables. As a result, EPRI-sponsored research activities were started at the University of Tennessee on fingerprinting the thermal history of polymeric materials; at the University of Connecticut on using ionized gas to troubleshoot the cables; at the University of Virginia on oxidation-induction-time testing; and at Sandia National Laboratory (SNL) on pre-ionized gas high-potential testing. Efforts at Ontario Hydro Research under the cooperative sponsorship of the EPRI, the Canadian Electric Association, and Consolidated Edison, at SNL under the sponsorship of the NRC, and at the IAEA and other foreign institutions (including Britain, France, German, Sweden, and Japan) have continued to investigate various CM techniques. Candidate CM methods for detecting incipient failures in cables were summarized at the 1988 EPRI workshop (Ref. 6.4). Recently, a working group of a technical committee of the International Electrotechnical Commission (IEC), SC15B-WG2 has been developing a guide for in-service monitoring of radiation aging of insulating materials (Ref. 6.5). The results presented at the 1993 EPRI workshop are an indication of the ongoing work although the search is far from over, as was reiterated during the discussions among the U.S. nuclear industry and the NRC at the EQ workshop (Ref. 6.1) in November, 1993.

Research efforts to develop an analytical and/or an experimental method to monitor the condition, to predict the remaining life, and to determine the degradation mechanism of cables used in radiation environment have been ongoing for over one decade. Earlier studies developed an analytical approach using shift factors for radiation and thermal aging conditions (Ref. 6.6), and included experimental methods, such as percent swelling and percent extractables (Ref. 6.7), and chemiluminescent spectra for thermo-oxidative degradation (Ref. 6.8). The extracted components then were separated by either gel permeation or liquid chromatography. Measuring the amount of antioxidant depletion and infrared spectroscopy were used to study the chemical changes in the polymer structures. Reference 6.9 presents the results from several electrical and spectrographic measurements of PE exposed to different aging conditions. Correlations were developed between aging time and electrical parameter degradation, and aging time and infrared absorption spectra. Electrical parameters included dielectric strength and loss factor, while the spectrographic parameters included infrared absorption and degree of crystallinity. These kinds of relationships between the structural and electrical changes seem to produce results which can effectively predict the electrical life of cables based on the physical or chemical changes in the insulating media.

Recent studies assessed the usefulness of various analytical and experimental methods in monitoring the condition and predicting the life of cables in nuclear power plants (Refs. 6.10-6.13). These activities included validating predictive models by tests (Ref. 6.10), assessing conditions of naturally aged cables from generating stations (Ref. 6.11), and evaluating CM methods during the EQ process (Refs. 6.12-6.13). Most findings were discussed at the two workshops held by the EPRI in 1988 and 1993. It was recognized that the weak links in a cable system lie at the cable's interfaces with other equipment or devices (e.g., connections, splices, electrical penetrations), and the intrusion of, or exposure to, a moisture/high humidity environment has the greatest impact on the overall reliability of electrical circuits (Ref. 6.14).

In this section, the results from all advancements on the CM issue are summarized. The purpose is to identify those efforts which have the potential of satisfying some of the CM attributes discussed above, together with evaluating their limitations and difficulties. All the CM methods now available in various stages are discussed, ranging from in-laboratory to in-plant installed cable applications.

## **6.1 Parameters for Monitoring Cable Degradation**

Among all attributes of an effective CM method discussed earlier, those which involve the degradation processes in the insulation material, the sensitivity to stressors causing this degradation, and the effectiveness of the monitoring parameter to trend this degradation are important to the researchers.

One very important issue which can affect the outcome of any CM research involves a clear definition of *what constitutes a cable failure and how CM data interpret this failure*<sup>1</sup>. Is this definition valid for both the normal life-aging phase and the postulated accident-phase of the cable qualification process? From the results presented in the previous two sections on pre-aging and LOCA testing, elongation-at-break for aging degradation, and insulation resistance during LOCA simulation (also weight gain before and after LOCA testing) typically are the monitoring parameters chosen by most researchers. But can the LOCA response of a cable's insulating system be predicted from the threshold value of the parameter monitoring the aging degradation? On the other hand, qualification tests are considered successful provided that after experiencing both pre-aging and LOCA simulations, the cable demonstrates its survivability in post-LOCA dielectric-

---

<sup>1</sup> Note that the role of CM is not to detect failures, but to detect the approach to a condition at which the cable is still able to function during an accident.

withstand tests and sometimes post-LOCA mandrel-bend tests (Ref. 6.15). Some researchers have expressed their reservations on the severity of these test methods on the already significantly degraded insulation materials after the LOCA exposure. It was demonstrated that insulating systems exhibiting zero tensile elongation before the accident successfully passed subsequent accident simulations (Refs. 6.16-6.18).

In addition to mechanical damage during handling, installation, and maintenance, the polymers in the cable's insulating system undergo changes in chemical structure due to thermal oxidation, radiation, and other chemical reactions (Ref. 6.19). This change involves both physical changes, such as orientation, crystallization, and flow, and also chemical changes, such as scission and crosslinking. Simultaneously, changes in mechanical properties can occur within the polymeric materials under mechanical and environmental influences. Some cases are more involved and the changes in mechanical properties and structure can influence each other. To understand the degradation phenomena in a particular cable insulating material (with the proprietary nature of a specific composition of a base resin and additives, and the curing process by the manufacturer), several different types of laboratory tests may have to be undertaken.

Once the chemical and the physical (or mechanical) changes in polymeric properties are characterized, their impact on the electrical properties of the insulating material must be established. The final appraisal of the cable's performance can only be or should be, based on these electrical properties which assure the cable's ability to deliver the required electric power or transmit a signal to the safety-related equipment. Thus, the chemical and physical degradation processes must be monitored first to identify incipient cable failures (i.e., those degradation processes that can lead to subsequent deterioration in electrical properties); significant research on this aspect was performed during the last decade. The second part, which involves correlating these degradation processes with the electrical properties has been given less attention by the researchers. Hence, conflicting conclusions are being considered for defining the threshold value of these polymeric materials which can assure their survival in a LOCA environment. For example, a 50% elongation-at-break (absolute) was used as the threshold value for many cable materials, but how this relates to the electrical properties has not been discussed in the literature. On the contrary, embrittled cables have successfully passed the LOCA tests, justifying a qualified cable for application in a nuclear power plant.

Oxidation, crosslinking, chain scission, hydroperoxide breakdown, and other chemical and molecular changes in polymers first occur under the influence of an inside-containment environment (Ref. 6.20). The presence of oxygen plays an important role in these processes. The physical parameters which are affected by these chemical structural changes (or are important for monitoring their influences) typically are recognized as:

Molecular Weight or Density  
Glass Transition or Melting Point Temperature  
Oxygen Consumption (amount and rate).

It is desirable to characterize polymers by molecular weight, but the presence of filler materials in cables make it difficult. For basic polymers, typical methods used to determine this include measuring the osmotic pressures, the light scattering, and the viscosity of dilute solutions. These methods may not be suitable for cross-linked or other cable insulation and jacket materials.

The dimensions of the crystals in polymeric materials are small compared to the average length of the polymer molecules. The crystallites are regular arrays of segments of polymer chains. Individual polymer molecules thread their way through many crystallite and amorphous regions. Crystallinity has an important effect on mechanical properties. Several methods devised for measuring the amount of crystallinity include light

scattering, density or specific-volume measurements, X-ray diffraction, refractive index, and infrared absorption peaks.

The chemical structure of polymers controls their stability both to chemical attack and to atmospheric aging. It is understood that radiation resistance does not correlate with resistance to chemical and thermal degradation. Furthermore, additives to improve physical properties may play a part in changes produced by radiation. Antioxidants are employed to reduce the attack by oxygen or ozone on the polymer molecules. These antioxidants are usually complex aromatic amines or phenols, and may react with radiation-produced molecular fragments to modify radiation effects. The effect of increasing plasticizer (a low-molecular-weight material) content in certain polymers (e.g., PVC) is to change a hard, rigid polymer first to a viscoelastic material, and then to a rubbery, flexible product. It has been hypothesized that during LOCA testing, embrittled insulating polymers can absorb water that act as a plasticizer (Refs. 6.16-6.18). The extent of this effect is roughly proportional to the amount of water absorbed.

Molecular-weight determinations can establish the extent of cross linking and chain scission in polymers under thermal and radiation environments. For thermoplastic materials such as PVC and PE, the gel point can be used to determine the inception of crosslinking (must differentiate between crosslinked and uncrosslinked materials). This gel point is a function of the molecular weight of the polymer. For degrees of cross linking higher than the gel point, the ratio of soluble to insoluble (known as gel-content) material can be measured. At high radiation doses, if scission and cross linking both occur, the soluble fraction decreases to an asymptotic value characteristic of the ratio of cross linking to scission. When cross linking has progressed to the point of complete insolubility, its extent can be determined by the equilibrium swelling of the polymer in a solvent.

Thus, cross linking increases the molecular weight of the polymer, decreases its solubility, decreases oxygen absorption, and increases the softening temperature. Cross linking draws the molecules closer together and, therefore, decreases the specific volume (low-molecular-weight materials are vaporized) and increases the density. The influence of scission is just the opposite. Crystallinity can be increased in polymers that undergo scission because there is less restraint on the shortened molecules. An increase in crystallinity will cause an increase in density (cross linking also increases the density, but for a different reason discussed above).

Table 6.1 lists several methods that have been used to monitor various parameters of polymer degradation in thermal and/or radiation environments. Except the first three methods, other methods may use only a few milligrams of specimen shaved from the cable's insulation and the tests are conducted in the laboratory. The first three methods are performed on actual cable samples. These methods can diagnose the early stage of polymer degradation and are useful for correlation studies with other methods which monitor the physical and electrical properties of cables.

Table 6.2 lists test methods which measure or monitor the physical properties (or the physical condition) of the cable materials. Some of these methods are currently used in the laboratory to investigate the degree of various degradation processes discussed in section 4.0. Except the Indenter Modulus test method, all other methods are destructive and need cable samples of various sizes. The first two methods require the removal of copper conductors from the specimens which should be shaped and sized as dumbbell/tubes tensile specimens. The use of the Indenter Modulus method has been demonstrated as an in situ test and the results can be trended to indicate aging in the cable's insulation and jacket materials. All of these methods still measure local conditions along a cable's length, and therefore, require tests at several local points to assess the overall condition of the cable.



**Table 6.1 Methods to Assess Material Degradation Caused by Chemical Processes**

Testing Method	Degradation Caused by the Environment(s)	Degradation Process Being Monitored	Materials Applicable
Near Infrared Reflectance(NIR)	Thermal and Radiation	Oxidation	PVC, EPR, PE
Computed Tomography (CT)*	Thermal and Radiation	Cross-link Density Gradient	EPR, PE
Sonic Velocity	Thermal and Radiation	Density Changes	PVC, EPR, PE
Fourier Transform Infra-red Spectroscopy (FTIR)	Thermal and Radiation	Oxidation(Carbonyl Peaks)	EPR, PE
Solubility - Gel Fraction	Thermal and Radiation	Cross-linking and Scission	All
- Swelling Ratio	Thermal and Radiation	Cross-linking and Scission	All
Oxidation Induction Time (OIT)	Thermal and Radiation	Depletion of Antioxidants	EPR, PE
Oxidation Induction Temperature**	Thermal and Radiation	Depletion of Antioxidants	Rubber, CSPE
Plasticizer Content	Thermal	Depletion of Plasticizer	PVC
Differential Scanning Calorimetry	Thermal	Glass Transition Temperature	Semicrystalline Products
		Crystal Melting Behavior	
		Degree of Crystallinity	
Thermomechanical Analysis(TMA)	Thermal and Radiation	Hardness	Elastomers, PVC
Thermogravimetric Analysis(TGA)	Thermal	Weight Losses	Elastomers, PVC

\* Not considered a chemical method.

\*\* Performed under pressure.

**Figure 6.2 Methods to Monitor Physical Properties of Polymeric Materials**

Testing Method	Physical Properties Being Monitored	Comments on Material Types Affected
Elongation-at-Break(EAB)	Tensile (Absolute/Relative)	All
Tensile Strength (TS)	Tensile (Absolute/Relative)	All
Indenter Modulus	Compression Elasticity	All (Tefzel possible)
Torque Tester	Torque Modulus	Not Known
Flexure Test	Bending Strength	All
Profiling - Modulus	Heterogeneous Degradation	All
- Density	Heterogeneous Degradation	All
- Hardness	Heterogeneous Degradation	All
Cross-Sectional Polishing	Chemical Degradation Profiles	All
Hardness Test	Hardness	All
Density Measurement	Density	All (Silicone possible)
Dynamic Mechanical Analysis (DMA)	Flexure, Hysteresis of Stress-Strain Relationship	Rubbers, PVC

Elongation-at-break has been the conventional method used for measuring embrittlement in polymers. Traditionally, a value of 50% absolute elongation was considered as the threshold value for aged specimens. It is assumed that this value will provide sufficient margin for the insulation to function without cracking.

Unlike the methods in Tables 6.1 and 6.2, electrical tests monitor the condition of the entire length of the cable included in an electrical circuit. One problem with these tests is that by the time any degradation is indicated by abnormal results, the cable is embrittled and may contain cracks. Again, many of these electrical methods require a well-defined, continuous ground plane to measure the electrical properties of the insulating system and this often raises more questions than answers on the effectiveness of the procedure. Theoretically, any electrical test will be insensitive to anything but gross changes in the dielectric. Table 6.3 lists several electrical tests which are being used in the field today to monitor the conditions of cables in nuclear power plants.

**Table 6.3 Electrical Test Methods Monitoring the Cable Performance**

<b>Test Method</b>	<b>Measuring Parameter</b>	<b>Comments on Applications</b>
DC Tests	Insulation Resistance	Go/No Go, Humidity
	Polarization Index(PI)	Go/No Go, Humidity
AC Impedance Tests	Capacitance	Dielectric Capacity
	Dissipation Factor (DF)	Dielectric Loss
Stepped Voltage Test	Leakage Current	Gross Insulation Failures
High Potential Test	Leakage Current	Gross Insulation Failures
Partial Discharge Test	Inception Voltage	Corona, Ionization
Voltage Withstand Test	Voltage Capacity	Withstand Voltage
Time Domain Reflectometry(TDR)	TDR Signature	Fault Detection
Dielectric Loss Measurements	Loss Factor ( $\tan \delta$ )	Dielectric Loss

There is no evidence that electrical tests are sensitive to morphological changes in the aged insulation, i.e., to the chemical and physical deterioration that takes place during thermal and radiation exposures. Embrittlement ultimately causes cables to crack and fail. But how to relate this to these electrical-test parameters has been a challenge to many researchers. Moreover, in situ measurements also critically depend on the level and type of electrical noise interfering with the measurement system. Connecting test equipment to electrical terminals may require disconnecting installed interfaces. The testing also may require disconnecting all equipment (or electrical loads) connected to the circuit under study. These intrusive requirements are disruptive, and the utilities have serious reservations about including them in their maintenance program.

## **6.2 Methods for Monitoring Chemical Degradation**

When earlier plants were constructed, the cable insulating materials used were butyl rubber for high-voltage, and styrene butadiene rubber and PVC for low-voltage applications. The jacket materials were predominantly Neoprene and PVC. In the early 1970s, the insulation was mostly XLPE, PE or PVC with Hypalon or PVC jackets. Cables in newer plants typically are insulated with fire-retardant EPDM or XLPE and jacketed with improved fire-retardant Neoprene or Hypalon. Table 6.4 shows the qualitative, general physical characteristics of these cable materials which might help in understanding the limitations in using the various CM methods in Table 6.1 for studying chemical degradation under different stresses. This qualitative assessment may vary for similar materials from different manufacturers.

The NIR, CT, and sonic velocity methods are being developed. FTIR has been proven to be a useful method for identifying various functional groups that are formed due to oxidation, but this requires a skilled effort to understand the interferences caused by the presence of antioxidants, and other filler materials. Solubility measurements are easier to perform and the results provide information about whether the degradation is due to thermal or radiation stress. Based on the sample's gel content and plasticizer content, the type of degradation can be identified from the amount of cross linking (thermal or radiation) and scission (radiation). The OIT is not suitable for silicone rubber materials; however, oxygen induction temperature under pressure is useful for these materials (including Hypalon). Plasticizer content is used only for PVC material. The TMA has been good for elastomers and PVC. However, both TMA and TGA methods are not widely used for monitoring the conditions of cable materials.

**Table 6.4 Cable Material Characteristics Sensitive to Aging**

Basic Cable Material	Material Type	Melting Point Transition Temp. (°C)**	Crystallinity	Degradation Under		
				Thermal	Radiation	Steam/Humidity
PE	Xlinked	90-130	Semicrystalline	N	N	N
	Low Density	90-130	Semicrystalline	S	N	S
	Chlorinated	90-130	Semicrystalline	S	S	S
EPR	Xlinked	60-90	Semicrystalline	N	N	N
	EPDM (Xlinked)	60-90	Semicrystalline	N	N	N
SR	Elastomer(Xlinked)	N/A	N/A	N	S(DR)	N
Tefzel	Thermoplastic	>200	Noncrystalline	N	S(DR)	N
SBR or BR	Elastomer(Xlinked)	N/A	N/A	S	S	S
PVC	-	~120	Noncrystalline	N	S(DR)	N
Hypalon(CSPE)*	Elastomer (Xlinked)	N/A	N/A	S	S(DR)	S
Neoprene/ Chloroprene	Elastomer (Xlinked)	95-100	Semicrystalline	S	S	S

Notes: N/A= Not Available; N=Normal (Average); S=Sensitive(more than Average); DR=Dose Rate Effect.

\* Better than Neoprene.

\*\* All values are approximate and vary with the polymer's formulations.

### 6.2.1 Near Infra-red Reflectance (NIR)

NIR spectroscopy (Ref. 6.21) has been applied to the characterization of polymers as a result of light absorption of organic molecules. NIR spectra arise from overtones or combinations of overtones of the fundamental vibrations that occur in the near infra-red regions of the spectrum, and hence, the technique is complementary to infra-red (IR) and Raman spectroscopy and has found some limited applications for polymer analysis. NIR has the advantage of relatively simple sample preparation. Glass has a low absorption in the near infra-red region, so glass sample holders may be used (e.g., optical fibre probes can be used for in situ samples). Much thicker samples, up to about 10 mm, also may be used. In addition, since most of the spectral lines detectable in the NIR arise from vibrations of hydrogen-containing bonds, hydrogen-free solvents such as CCl<sub>4</sub> may be employed without difficulty. NIR is sensitive to subtle changes and easily reproduced spectra contribute to the analysis of large numbers of components simultaneously. This feature makes NIR attractive for cable insulation systems which contain several additives in the polymer's formulation. The IR peaks are narrower than those in NIR, so that the FTIR's are designed with narrow band passes to give high-resolution discrimination of wavelengths. The tradeoff in the case of NIR is lowered resolution in the absorbance spectra.

The interrelationship of various side-groups with the main structural backbone of the substance can provide a better correlation with changes in physical properties than can the vibration of the mid-IR range. As with FTIR, strong NIR absorbers include species such as C-H, O-H, N-H, C=O, =C-H, COOH, and aromatic C-H groups. Some of these functional groups, namely, C=O, O=H, and COOH are formed as components of cable insulation and jackets age. For the NIR technique to be effective, an equation to predict chemical degradation involving single and multiple variable analysis must be run on a set of well-characterized calibration samples having accurately known aging periods. The NIR reflectance equipment can be made portable using a fibre-optic probe, and lends itself to in situ cable monitoring.

This CM technique (with the potential of future use in situ) is in its development stage at Ontario Hydro (Ref. 6.22). A Quantum 1200 NIR analyzer configured for the NIR region (1200-2400 nm) equipped with a fiber optic reflectance probe and Spectra Metrix software routines was used to study nine PVC jacketed cables aged at 110°C from 28 to 138 days. Each sample was scanned at three locations by pressing the fiber-optic probe against the jacket surface. The transmittance spectra were obtained using the Quantum 1200 NIR analyzer, and the values converted to absorbance spectra by taking the negative logarithm shown in Figure 6.1. To




Figure 6.1 Typical variation in infrared absorbance with wavelength for cable jacket (Ref. 6.22)  
Reproduced with permission from Mr. D.J.R. Dodd, Ontario Hydro Technologies, Canada.




Figure 6.2 First derivative of absorbance plotted as a function of wavelength (Ref. 6.22)  
Reproduced with permission from Mr. D.J.R. Dodd, Ontario Hydro Technologies, Canada.

remove the effects of a constant baseline shift, the first derivative (slope) of the absorbance spectra is plotted as a function of wavelength, as illustrated in Figure 6.2.

Various regions of the spectrum correlated well with aging time. Specifically, the region between 1640 and 1650 nm experienced a distinct change in absorbance values with aging rates. Figure 6.3 illustrates the relationship between wavelength and the first derivative of absorbance with aging. Figure 6.4 compares the resulting correlation between this first derivative of absorbance in the above wavelength region with percent elongation for various aging times. The accuracy of the calibration curve was evaluated using two aged cable samples. For these two unknown samples, NIR analysis predicted 28-38 days and 120-141 days of aging, compared with actual durations of 40 and 124 days, respectively. These results indicate that the NIR technique can indicate the extent of PVC jacket aging.

The IR reflectance spectrum obtained is only from a thin surface layer of the cable material, which may not be representative of the state of degradation of the bulk of the material. Also, data are limited to the immediate area of the probe. The technique is not likely to be sensitive to the cable's geometry. Construction calibration curves would be required for each material in the cable.

### 6.2.2 Computed Tomography (CT)

Computed tomography (also known as computed X-ray tomography or computer-assisted tomography(CAT)) has been used almost exclusively for medical purposes. It is a non-destructive examination (NDE) which can detect and locate defects, the presence of which might have a deleterious effect on the service life of the cable. The technique also can monitor density changes (or cross-link density gradients) in both insulation and jacket materials. The measurements can be quantified in terms of the Hounsfield CT number which is proportional to the X-ray attenuation through an object. The CT number is represented by the gray scale of an X-ray image. For organic and polymeric materials, there is an approximate linear relationship between the CT number and the material's density.

Thermo-oxidative degradation of thick-walled rubber materials has been studied by researchers at the Royal Institute of Technology in Sweden (Ref. 6.23) who compared results obtained from the CT, IR, and Swelling measurement techniques to understand diffusion-controlled oxidation, embrittlement of the exposed surface, and anaerobic aging of the interior of the rubber. Both CT and IR spectroscopy successfully revealed oxidative aging in the surface; however, they did not show thermal degradation in the bulk. Also, it was difficult to measure the degree of oxidation from swelling, due to the appearance of both oxidative crosslinking and oxidative scission. However, swelling successfully indicated thermal degradation.

The CT method also was used by the same group to detect imperfections and to measure cross-link density gradients in polymeric products, such as airplane tires, and rubber shock-absorbers (Ref. 6.24). Figure 6.5 shows the relationship between bulk density and cross-link density. These results are in good agreement with the results obtained using wet chemical methods (based on the well-known fact that cross-linked rubber material does not dissolve but swells to different degrees in different solvents, such as hexane, heptane, toluene, and methylene chloride). When the CT numbers of the different test pieces were measured with a Siemens Somatom DR CT scanner, the results plotted in Figure 6.6 show a direct correlation between the CT number and the bulk density.




Figure 6.3 Variation in first derivative of absorbance with different aging (Ref. 6.22)  
 Reproduced with permission from Mr. D.J.R. Dodd, Ontario Hydro Technologies, Canada.






Figure 6.4 Correlation of first derivative of absorbance with elongation (Ref. 6.22)  
 Reproduced with permission from Mr. D.J.R. Dodd, Ontario Hydro Technologies, Canada.



**Figure 6.5 Bulk density vs cross-link density for peroxide-cured synthetic natural rubber (Ref. 6.24 Redrawn for clarity)**  
 Reproduced with permission from Mr. Ghassan Rassam, Director of Publications, Optical Society of America.



**Figure 6.6 Bulk density measured by CT scanning (Ref. 6.24: Redrawn for clarity)**  
 Reproduced with permission from Mr. Ghassan Rassam, Director of Publications, Optical Society of America.

Work on density and modulus-profiling for EPR-2 material using this method showed excellent similarity with SNL's profiling techniques (Ref. 6.25). Figure 6.7 illustrates the density profiles of this material, and Figure 6.8 shows the good correlation of the density measurements with CT numbers. Comparing this sensitivity to the approximate correlations found between density changes and elongation changes indicates that CT techniques may be a viable non destructive approach for monitoring power-plant cables. At this time, this methodology has not received attention among U.S. researchers, and further studies are necessary before it can be used on cables in plants. Since this method requires an X-ray source and a detector, currently it is used as a laboratory tool.

### 6.2.3 Sonic Velocity

This technique is based on the principle that the speed of sound through a solid medium (metals, polymers, composites) is related to both density and elastic modulus:

$$C^2 = E/\rho$$

where, C = Sonic velocity

E = Elastic modulus


$\rho$  = Polymer density.

Since both modulus and density can change as cable material age, changes in sonic velocity also would be expected to occur. At Ontario Hydro, sonic velocities are measured using an H.M. Morgan PPR-5M Dynamic Modulus Tester (Ref. 6.22). The instrument uses "transmit" and "receive" piezoelectric transducers which are placed in contact with the surface of the cable's jacket at various distances apart. A microsecond timing circuit, gated in parallel with the transducers, measures the time required for a continuous series of recurring 20 KHz pulses to travel along the jacket's length between the probes. Signal transit times are displayed on a TEKTRONIX 221A digital oscilloscope as a displacement on the time axis between peaks associated with the "emitted" and "receive" signals. The transit time subsequently is plotted as a function of transducer separation distance (incremented successively by 1 cm) to obtain the slope which represents velocity.

This technique is at its early stage of development at Ontario Hydro. Measurements have been made on a series of PVC-jacketed cables and on strips of jacket material cut from the cables. Figure 6.9 shows the longitudinal sonic velocity obtained on them as a function of aging time. Comparison between the data showed that the technique depends on the cable's geometry and adjacent shielding and insulation components (see Figure 6.10a). The magnitude of the sonic velocity also varies considerably with different formulations of PVC. Therefore, base-line data would be required for each type of cable. Similar results are obtained when the sonic velocity data are plotted against the density (Figure 6.10b). When plotted against the jacket modulus in Figure 6.10c, the results are independent of jacket's formulations.


The sonic-velocity test measures the properties of the cable jacket over a small volume between the transducer probes. At present, the technique is more suited to laboratory evaluation than field use, but its high sensitivity to aging degradation indicates that it has potential for in situ application. However, the rate of change with age in the material may not be sufficient to monitor degradation.








**Figure 6.7 Density profiles of EPR-2 (Ref. 6.25)**

Copyright © 1993. Electric Power Research Institute. EPRI TR-102399. *Proceedings: 1993 EPRI Workshop on Power Plant Cable Condition Monitoring*. Reprinted with Permission.



**Figure 6.8 CT profiles of EPR-2 (Ref. 6.25)**

Copyright © 1993. Electric Power Research Institute. EPRI TR-102399. *Proceedings: 1993 EPRI Workshop on Power Plant Cable Condition Monitoring*. Reprinted with Permission.



▲ JACKET STRIP + FULL CABLE \* ELONGATION

Figure 6.9 Sonic velocity as a function of aging (Ref. 6.22)  
 Reproduced with permission from Mr. D.J.R. Dodd, Ontario Hydro Technologies, Canada.




Figure 6.10 Correlation of sonic velocity with elongation, density and modulus (Ref. 6.22)  
 Reproduced with permission from Mr. D.J.R. Dodd, Ontario Hydro Technologies, Canada.

#### 6.2.4 Fourier Transform Infra-red (FTIR) Spectroscopy

As discussed under NIR spectroscopy, changes in the infra-red spectrum of polymers are known to occur with aging, primarily in functional groups such as carbonyl ( $\text{C}=\text{O}$ ), hydroxyl ( $\text{O}=\text{H}$ ), and carboxyl ( $\text{COOH}$ ). An alternative to reflectance measurements in-plant is to take samples from the cable's material and measure the IR spectrum in the laboratory. Such samples usually would be scrapings or slivers of material cut from the surface, but sufficiently small to not affect the operation of the cable. When polymers like XLPE and EPR are oxidized (thermally or irradiation), a strong carbonyl peak becomes evident at about  $1720\text{ cm}^{-1}$  in the IR spectrum; therefore, its appearance can indicate deterioration of the insulation. However, detecting the carbonyl groups generated due to oxidation aging is not a simple procedure as unaged materials also can display absorption peaks in the  $1700\text{--}1750\text{ cm}^{-1}$  region. These peaks have been attributed to the presence of antioxidant additives, such as Irganox and Thio esters, which exhibit a strong ester band at  $1742\text{ cm}^{-1}$ . The by-products from high-temperature crosslinking reactions with dicumyl peroxide exhibit peaks at  $1724$  and  $1710\text{ cm}^{-1}$  which also can interfere.


Figure 6.11 shows the FTIR spectra for FRXLPE specimens irradiated to different doses (Ref. 6.26). Peaks centered at  $1740\text{ cm}^{-1}$  and  $1720\text{ cm}^{-1}$  were typical of the irradiated specimens. Variation of the intensity ratio is plotted in Figure 6.12 as a function of dose rate, for specimens irradiated in air. Figure 6.13 gives similar results (Ref. 6.27) on thermal aging of this material. A long induction time for the formation carbonyl groups was observed. It is evident that an increase of  $10^\circ\text{C}$  in the aging temperature reduces the induction time by 50%. This method has successfully indicated similar spectra (with long induction period) for SBR and polypropylene materials. For EPR, the results show changes in the carbonyl region only for specimens irradiated above 100 Mrad, regardless of the irradiation environment or dose rate. Therefore, it does not appear to be sensitive in detecting oxidation of stabilized FREPR insulation materials irradiated to less than 100 Mrad. Similarly, the PVC samples irradiated to 100 Mrad did not have any distinguishable differences in the FTIR spectrum compared with the unaged specimen.

IR spectra taken from samples are limited to the surface layers of the cable jacket unless exposed insulation is accessible. The depth of material sampled is greater than that for in-plant IR reflectance measurements, but may still not be representative of the bulk material. The technique is limited to those parts of the cables that are accessible for sampling and is not very sensitive to the later stages of degradation. Furthermore, a skilled engineer must interpret and evaluate the FTIR spectra.


#### 6.2.5 Solubility Measurements (Gel Content and Swelling Ratio)

Solubility (gel content) and swelling measurements can indicate whether a polymer has undergone chemical reactions (chain scission or cross linking). In a cross-linked system, when a polymer undergoes additional crosslinking, the gel content increases and swelling ratio decreases. Chain scission has the opposite effects. In an uncrosslinked system, the initial soluble polymer will become less soluble in the presence of an oxidative cross-linking reaction.


These methods typically are used in various laboratory studies on polymer degradation (ASTM D2765). About 100 mg of material is exposed to boiling solvent for 12 hours in these tests; the solvents used are Xylene for XLPE, Toluene for EPR, SBR, and BR, and Tetrahydrofuran (THF) for PVC. After extracting the insoluble fraction in the solvents, excess solvent is removed from the surface, and the insoluble part is weighed at room temperature. Then, the sample is dried and weighed again. Gel content and swelling ratio are calculated.




**Figure 6.11** FTIR spectra for XLPE (a) unaged; irradiated at 60 °C at dose rate 0.6 Mrad/hr to (b)15, (c) 30, (d) 60, and (e) 120 Mrad (Ref. 6.26)  
 Reproduced with permission from Mr. D.J.R. Dodd, Ontario Hydro Technologies, Canada.



**Figure 6.12** Carbonyl absorbance vs radiation dose for XLPE (Ref. 6.26)  
 Reproduced with permission from Mr. D.J.R. Dodd, Ontario Hydro Technologies, Canada.



**Figure 6.13 Relative absorbance with thermal aging for XLPE (Ref. 6.27)**  
 Reproduced with permission from Mr. D.J.R. Dodd, Ontario Hydro Technologies, Canada.



**Figure 6.14 Swelling ratio for FREPR (Ref. 6.26)**  
 Reproduced with permission from Mr. D.J.R. Dodd, Ontario Hydro Technologies, Canada.

The swelling ratio of FRXLPE and FREPR can be used to determine whether chain scission or crosslinking has occurred (Ref. 6.26); chain scission increases the swelling ratio, and crosslinking reduces it. Figure 6.14 shows the swelling ratio versus radiation dose for the FREPR specimens. On irradiation, under 300 psi (in oxygen atmosphere) the swelling ratios increased from 300%, indicating that chain scission had occurred. Irradiation in air at 0.7 Mrad/hr lowered the swelling ratio for both these materials, indicating that the predominant degradation mechanism was crosslinking.


The gel content of XLPE specimens as a function of aging and temperature is shown in Figure 6.15 (Ref. 6.27). The results follow the same pattern as the carbonyl absorbance values in Figure 6.13. There was an induction period followed by a sharp increase in values. The increase in the gel content during the auto-oxidation period reveals that crosslinking was occurring. For EPR specimens, the gel content remained unchanged at 83% during aging suggesting that it is not a sensitive indicator of thermal aging. This also is true for XLPE and SBR, which originally have gel contents in excess of 80%. In these systems, only measurements of the swelling ratio show changes with aging.

PVC specimens irradiated in an oxygen atmosphere were completely soluble in THF indicating there was no crosslinking (Ref. 6.26). However, specimens irradiated in air became more insoluble with increased dose rate and total dose (see Figure 6.16). The gel fraction or crosslinking of specimen irradiated at 0.02 Mrad/hr increased at a very low rate, reaching 5% at the total dose at 80 Mrad. At the higher dose rates of 0.1 and 0.7 Mrad/hr in air, crosslinking was the predominant reaction, and its extent increased with increasing dose rate.


#### 6.2.6 Oxidation Induction Time (OIT)/ Temperature Under Pressure

Using a differential scanning calorimeter (DSC), the time taken to the onset of exothermic oxidation at constant temperature can be monitored. In an OIT test, a small sample (~2-10 mg) of material is placed in a DSC and exposed to a constant temperature in the region 180-215°C in an oxygen atmosphere until an exothermic reaction occurs. This oxidation-induction time indicates the oxidative stability of the polymer and decreases as the antioxidants in the polymer are depleted. OIT values decrease rapidly with increasing radiation dose as well as increasing thermal aging, showing that OIT measurements are sensitive to both thermal and radiation-induced oxidative degradation.

At Ontario Hydro, this technique was used for thermally aged specimens of XLPE and EPR samples (Ref. 6.27). Figures 6.17 and 6.18 compare the OIT values at 200°C, after aging at the temperatures shown. For unaged XLPE and EPR, the OITs were 65 min and 45 min, respectively. The figures show that the induction period decreased rapidly during the initial aging period before falling more regularly. It was concluded that the OIT measurement is the most sensitive indicator of oxidative degradation during the induction period. The technique also was used for radiation aging samples and similar trends were exhibited in the OIT values. The study also claims that a good correlation was found between elongation values and OIT values for several XLPE and EPR insulations obtained from different manufacturers.




**Figure 6.15 Gel fraction vs. aging for XLPE (Ref. 6.27)**  
 Reproduced with permission from Mr. D.J.R. Dodd, Ontario Hydro Technologies, Canada.




**Figure 6.16 Gel fraction for PVC in air (Ref. 6.26)**  
 Reproduced with permission from Mr. D.J.R. Dodd, Ontario Hydro Technologies, Canada.





**Figure 6.17 OIT at 200°C for XLPE (Ref. 6.27)**  
 Reproduced with permission from Mr. D.J.R. Dodd, Ontario Hydro Technologies, Canada.



**Figure 6.18 OIT at 200°C for EPR (Ref. 6.27)**  
 Reproduced with permission from Mr. D.J.R. Dodd, Ontario Hydro Technologies, Canada.

At the University of Virginia, this technique was used for the same two materials under radiation aging conditions (Refs. 6.28 and 6.29). Figures 6.19 and 6.20 show the observed variations of normalized OIT (i.e., ratio of aged and unaged OIT values) with radiation dose. The study also correlated OIT with antioxidant concentration. The variation of antioxidant concentration with a constant dose rate was linear, consistent with oxidation reaction kinetics. At present, the work is being continued to standardize the methodology for field application, to correlate the OIT values with other measurable parameters, and to investigate the effects of thermal degradation.

A variant on the OIT technique is to use oxidation-induction temperature (instead of time) (Refs. 6.30 and 6.31). This temperature is that at which exothermic reactions start as the temperature of a sample is raised in a constant atmosphere of oxygen. This method is more useful than OIT for elastomeric insulations, such as SBR and butyl rubber. Figure 6.21 compares the temperature values with the tensile properties of a SBR sample, showing that there is an excellent correlation between them.

As with any microsampling technique, only the properties of the surface layer samples are measured which may not be representative of the bulk material. Further studies on other jacket materials are needed to assess its effectiveness on all cable materials.


#### **6.2.7 Plasticizer Content**

This is a useful technique for assessing the degradation of PVC material exposed to thermal aging. The plasticizer content is an important factor in determining the usability of PVC insulations, and the volatility rate of the plasticizer governs its longevity. The plasticizer content of PVC insulations is generally between 20-30%, by mass; a content below 15% indicates that the cable has undergone thermal degradation. Figure 6.22 gives the plasticizer content (Ref. 6.30), obtained 100-200mg specimens in boiling ethyl ether, for a typical PVC insulation as a function of aging at 120°C, and compares the results with the tensile properties of the same material. During the early stages of the aging, both are directly correlated. In the final stage, the plasticizer content basically remained unchanged, whereas elongation decreases further. This behavior indicates that during the later stages, the degradation mechanism is probably controlled by oxidation and dehydrochlorination rather than loss of plasticizer.

Ontario Hydro has used this technique extensively with good results to assess field service cables. By contrast, for radiation exposure, there was no direct relationship between plasticizer content and physical degradation.


#### **6.2.8 Differential Scanning Calorimetry**

Experience has shown that one common mode of failure of cable insulation in nuclear power plants is thermally induced oxidation degradation which embrittles the insulation, leading to cracking and loss of dielectric strength. Use of a differential scanning calorimeter (DSC) to measure OIT and other indicators (such as melting point, crystallinity, and glass transition temperature) has yielded useful results for monitoring as well as understanding the polymer behavior under thermal conditions. Ontario Hydro and University of Tennessee have studied some interesting characteristics of polymer behavior and have detected changes in certain physical parameters.




**Figure 6.19 OIT as a function of radiation dose for EPR (Ref. 6.28)**

Copyright © 1993. Electric Power Research Institute. EPRI TR-102399. *Proceedings: 1993 EPRI Workshop on Power Plant Cable Condition Monitoring*. Reprinted with Permission.




**Figure 6.20 OIT as a function of radiation dose for XLPE (Ref. 6.28)**

Copyright © 1993. Electric Power Research Institute. EPRI TR-102399. *Proceedings: 1993 EPRI Workshop on Power Plant Cable Condition Monitoring*. Reprinted with Permission.



**Figure 6.21 Correlation between OIT and elongation-at-break for SBR at 120°C (Ref. 6.31)**  
 Reproduced with permission from Mr. D.J.R. Dodd, Ontario Hydro Technologies, Canada.



**Figure 6.22 Correlation between plasticizer content and elongation-at-break for PVC (Ref. 6.31)**  
 Reproduced with permission from Mr. D.J.R. Dodd, Ontario Hydro Technologies, Canada.

### *Degree of Crystallinity*

Figure 6.23 shows the crystallinity index of XLPE samples obtained from heat-of-fusion measurements (Ref. 6.27). The original index of 33 % increased slightly during the induction period for samples aged at 120°C and 130°C, and then decreased steeply. The initial increase can be attributed to the alignment of the lamellae crystallites by an annealing (i.e., aging) process. During auto-oxidation, the lamellae crystallite regions are disrupted and the crystallinity index decreases. These results show that the degree of XLPE thermal aging can be estimated on the basis of changes in the degree of crystallinity. For EPR, the degree of crystallinity was very low (5-10%) and did not change with aging, and consequently, cannot be used as an indicator of degradation.

### *Melting Behavior*


Melting endotherm curves of aged and unaged XLPE specimens are shown in Figure 6.24 (Ref. 6.27). For unaged XLPE, (Figure 6.24a) there is a major broad endotherm at 120°C. For the sample aged at 130°C for 71 days (Figure 6.24b), a new high-temperature, minor endotherm at 133°C is apparent. For the sample aged at 130°C for 102 days (Figure 6.24c), the major endotherm originally at 120°C has shifted to a lower temperature.

The peak melting temperatures are plotted against time in Figure 6.25. The position of the high-temperature minor endotherm peak gradually increases during the induction period, and during auto-oxidation it increases by another 5°C-10°C for samples aged at 120°C and 130°C. At aging temperatures (i.e., 130°C) above the melting point of 120°C, the minor endotherm was not evident initially but appeared after 35 days. Aging at 140°C did not produce a minor endotherm.


Throughout the aging period at 120°C and after 5 weeks at 130°C (Figure 6.25a), the appearance of the high-temperature minor endotherm peak suggests that a soluble, low-molecular-weight fraction crystallized and formed thicker crystals that melted at elevated temperatures. During auto-oxidation, the low-molecular-weight fraction phase appears to separate from the crosslinked network and form further perfect crystals that melted at a slightly higher (5-10°C) temperature.

An important feature of the melting behavior is reflected in the variation of the melting temperature of the major endotherm at 120°C (Figure 6.25b). This peak remains essentially unchanged during the induction period at all three aging temperatures. Since the melting temperature of a crystalline polymer is an index of the lattice perfection, the decrease in the melting temperature and crystalline index during the auto-oxidation period is due to the destruction of crystalline lamellae as a result of increased crosslinking of the polymer. The study concluded that the systematic appearance of the high-temperature minor endotherm peak and its dependence on the aging temperature (below 140°C) indicate that the maximum temperature to which an XLPE insulated cable has been exposed during service can be determined.

The formation of a minor endothermic peak depended on the aging temperature. Exposing the XLPE to at least 20°C above its melting temperature of 120°C destroys the thermal history, thereby eliminating the minor endotherm peak. Quenching the sample in cold water brings the polymer to its original crystalline structure, i.e., the structure of an unaged sample. The same applied to EPR, which has a melting point between 60-90°C. A detailed study on several aged cable materials (which had not reached the auto-oxidation stages) was made at the University of Tennessee and is discussed next.



**Figure 6.23 Crystallinity of XLPE as a function of age (Ref. 6.27)**  
 Reproduced with permission from Mr. D.J.R. Dodd, Ontario Hydro Technologies, Canada.



**Figure 6.24 DSC curves for XLPE (a) unaged, (b) aged at 130°C for 71 days, (c) aged at 130°C for 102 days (Ref. 6.27)**  
 Reproduced with permission from Mr. D.J.R. Dodd, Ontario Hydro Technologies, Canada.


### *Fingerprinting the Thermal History*

The presence of a crystalline phase in the insulation renders the material sensitive to changes in temperature, and the effects of such changes are recorded in the crystal (Ref. 6.32). Hence, a simple study of the crystalline phase (e.g., melting) permits the annealing information to be retrieved. Unlike metals and pure organic compounds of low molecular weight, polymers tend to exhibit melting ranges rather than single melting points. Consequently, the temperature reached during the manufacture of cable, or the temperatures during storage and service leave a fingerprint on the melting range. This thermal fingerprint can be exploited to estimate the temperature history of a cable in a power plant, and to a certain extent, the amount of time at particular temperatures. The only necessity is that one of the components of the polymeric insulation or jacket material is semicrystalline; hence, the technique can be applied to most cables. The major limitation of the method is that polymer retains the thermal history of its last maximum temperature excursion, together with all subsequent events in descending order of environmental temperature, but not any earlier events involving temperatures lower than the maximum excursion.


The melting curves for several cable materials received from SNL and the University of Connecticut (UConn) were studied by University of Tennessee using a Perkin Elmer DSC7 calorimeter. Figure 6.26 is a typical melting curve of an XLPE material exposed for 142 hours at 50°C. Compared to its unaged curve, a new peak has appeared at about 65°C, which contains information on the temperature reached and the dwell time there. The size and location of the new peak depend on this dwell time. Figure 6.27a shows the curve which resulted from subtracting the unaged material from that of the curve of the annealed (or aged) material. Figure 6.27b is the derivative of the subtraction plot (these operations typically are carried out by the DSC unit's internal computer program). Figure 6.28 illustrates various characteristics of these curves.

It is apparent that this information can be obtained through a simple program of heating and cooling in a DSC. The procedure is: (a) the weighed (5-10mg) specimen is heated at 10°C/min up to 150°C to obtain its melting curve; (b) the melted specimen is cooled at 40°C/min to -20°C to quench-crystallize; (c) the specimen is reheated at 10°C/min to determine the melting curve of the quenched specimen; (d) curve (c) from curve (a) is subtracted; and (e) the derivative of the subtracted curve is obtained. The data from these curves are further used to develop empirical mathematical analyses of the kinetics of the annealing processes in all of the materials studied. The technique was applied to a number of XLPE and EPR samples from the University of Connecticut and the results were compared with the UConn findings; there was a good correlation between the two different assessments of thermal properties.

Most cables are made from three basic classes of polyolefins, namely polyethylene (PE), ethylene-propylene copolymers (EPR), and ethylene-propylene terpolymers (EPDM). The common polyethylene (high density or linear, and low density) have been studied fairly thoroughly in both their original and crosslinked forms. The melting behavior of XLPE is well known, and ranges from 0°C to 106°C. The EPR comes as either amorphous or 20% crystalline with melting points between 50°C-60°C. Because of this lower melting range, it is more likely to suffer thermal aging at the temperatures normally encountered in power plants. In EPDM formulations, some are totally noncrystalline and others have different levels of crystallinity. Their melting characteristics are similar to that of EPR. This study also included the crystallization behavior of EPR and EPDM. Although many polymers are blended with others and additional ingredients, such as fillers, and then crosslinked, it was found that the basic annealing behavior was not substantially altered by blending, and essentially, a rule of mixtures approach could be used.



**Figure 6.25** Peak melting temperatures as a function of aging for XLPE (Ref. 6.27)  
 Reproduced with permission from Mr. D.J.R. Dodd, Ontario Hydro Technologies, Canada.



**Figure 6.26** Melting curve of XLPE following 142hr at 50°C (Ref. 6.32)  
 Copyright © 1992. Electric Power Research Institute. EPRI TR-101205. *Fingerprinting the Thermal History of Polymeric Materials*. Reprinted with Permission.







Figure 6.27 (a) Subtraction curve (b) Derivative of the subtraction curve (Ref. 6.32)  
Copyright © 1992. Electric Power Research Institute. EPRI TR-101205. *Fingerprinting the Thermal History of Polymeric Materials*. Reprinted with Permission.



#### GENERAL FEATURES OF THE SUBTRACTION CURVE

- 45° C Annealing generates shoulder on DSC endotherm
- Aloss represents material "lost from the first ramp"
- Again represents melting of new crystals generated by annealing
- Td remains fairly constant with annealing time
- Tp and Tb show logarithmic time dependence

Figure 6.28 Nomenclature used in describing the subtraction curve (Ref. 6.32)  
Copyright © 1992. Electric Power Research Institute. EPRI TR-101205. *Fingerprinting the Thermal History of Polymeric Materials*. Reprinted with Permission.

Table 6.5 summarizes the results which show the usefulness of the technique when there is no prior knowledge of the thermal history of cable materials. When the technique was applied to the jacket materials of all samples, the only ones that indicated some crystallinity were the three Eaton and one Okonite cables. These jacket materials had melting peaks between 45°C-60°C.

**Table 6.5 Thermal Behavior of Some Cable Insulation Materials (Ref. 6.32)**

Manufacturer	Descriptions	Major Endotherm Peaks		Minor Endotherm Peaks		Comments
		Aged °C	Unaged °C	Aged °C	Unaged °C	
Eaton	Dekoron Polyset					Blend of 2 or more Polyolefins
(Samuel Moore)	Triple Strand w/Jacket	70, 90, 48(J)	80, 68(J)	40, 60	None	
Eaton	Dekoron 2/C 600V					Xlinked LDPE plus Minor EPR/EPDM
(Samuel Moore)	Double Strand w/Jacket	110, 44(J)	110, 68(J)	40, 70	None	
Eaton	Dekoron 2/CD 600V					
(Samuel Moore)	Triple Strand w/Jacket	110, 54(J)	110	None	None	
Rockbestos	3/C 600V Firewall III					Xlinked LDPE and HDPE
	Triple Strand w/Jacket	122	106, 120	75, 105, 115	None	
BIW	600V 2/C EPR/HYP					EPR + LDPE(hyp)
	Double Strand w/Jacket	84	86	40, 60	None	
BIW	Tefzel					
	Single Strand w/Jacket	N/A	N/A	N/A	N/A	Noncrystalline
Anaconda	Flame Guard 1kV					
	Triple Strand w/Jacket	90	91	30, 70	25	
Anaconda	M Durashield EP 600V					
	Single Strand w/Jacket	90	91	30, 70	25	
Okonite	PLT Okolon C/T 600V					
	Single Strand w/Jacket	N/A, 61&50(J)	N/A	N/A	N/A	Noncrystalline
Okonite	EPR Okoprene 2000V					
	Single Strand No Jacket	N/A	N/A	N/A	N/A	Noncrystalline
Okonite	FMR					
	Single Strand No Jacket	57, 90	None	40	None	

NOTES: N/A=Not Applicable, J = Jacket Material Behavior

### 6.2.9 Thermomechanical Analysis (TMA)/ Thermogravimetric Analysis (TGA)

The TMA method measures the thermal expansion coefficient, and is sometimes used to determine the location of the glass-transition temperature. Ontario Hydro used this technique to measure relative hardness in terms of TMA penetration distance into the cable's insulation and jacket materials (Ref. 6.27).

In Figure 6.29, the relative hardness values, measured in terms of TMA penetration distance, are plotted as a function of aging time for EPR samples aged at 145°C, 130°C, and 115°C. The penetration distance initially decreased slowly, falling approximately 25% after aging for 50 days at 145°C, 173 days at 130°C, and about 500 days at 115°C. Further aging caused a dramatic drop over a shorter period. This steep change can be related to the effects of thermal degradation on other properties, such as carbonyl index and OIT. The technique also was valuable for thermally aged PVC; however, it did not show significant differences for the XLPE specimens. The study developed a criterion of a 40% reduction in the initial penetration distance (i.e., 60 µm) as the end of life for the cable materials tested; this correlates well with 50% absolute elongation.

With the TGA, the mass of the sample is recorded continuously while the temperature is raised at a constant rate. Weight losses occur when volatiles absorbed by the polymer are driven off, and at the higher temperatures when degradation of the polymer occurs with the formation of volatile products. The design of the equipment is most exacting, not only because the weight losses to be measured are very small, demanding a precision weighing mechanism, but also because of the need to avoid convective forces within the heating chamber and because of the changes in the density of the gaseous environment. It is important to ensure that volatiles do not condense on the weighing apparatus, and also to control the atmosphere when this affects the process of degradation.

At JAERI, small amounts of samples (usually 4-5 mg) were used in their TGA experiments (Ref. 6.33). The thermal decomposition temperatures of unirradiated and irradiated PVC samples were measured in an gas atmosphere at a temperature rise of 10°C-20°C/min. Figure 6.30 shows the thermal decomposition behavior of the unirradiated (original) and irradiated (aged) samples. A significant change in TG curve was observed between 200°C-300°C, and irradiation causes the starting point of thermal decomposition to shift to a lower temperature. Temperature at which weight decreases by 5% (expressed as T5%) significantly changes with irradiation. Figure 6.31 shows the linear relationship of this data to the elongation properties, which suggests that radiation degradation in PVC is primarily due to a change in chemical structure.

### **6.3 Methods for Monitoring Physical Properties**

The physical (and mechanical) properties of the insulation and jacket materials used in constructing cables change with age in nuclear power plants. These changes are manifested by the chemical degradation discussed in the previous section and are directly due to the environmental influences. Also, physical abuse during transportation, installation, and maintenance can often reduce the condition of cables. However, monitoring these abuses requires an effective quality assurance program rather than a test program, although often, the physical deterioration of cable materials is accelerated by environmental influences when there are pre-existing conditions (e.g., cuts, sharp bends, contamination).

Traditionally, tensile properties such as elongation and tensile strength, have been used to assess the embrittlement of polymers under thermal and radiation conditions. Several other methods, including compression, bending, twisting, hardness, and elasticity, yield parameters which can be trended with age of the polymers. Since one of the modes of polymer degradation includes a physical process (i.e., diffusion-limited oxidation), several profiling and polishing techniques are discussed to determine the heterogeneity in tensile or density properties across a specimen's cross-section. Table 6.2 lists all the test methods that are used in various researches related to measuring the physical condition of cables. The following section discusses the merits and demerits of several procedures used in the power industry.

#### **6.3.1 Tensile Property (Elongation-at-Break and Tensile Strength) Measurements**

Tensile strength and elongation tests are performed in accordance with ASTM D2633-82, using a tensile testing machine (e.g., Instron Model 1130) equipped with pneumatic grips and having an extensometer clamped to the sample. Special tensile specimens (dumbbells for larger cables or cylinders for smaller cables) of the insulation or jacket materials without the copper conductor are needed for these tests. Because of the difficulties in removing these conductors from an aged cable, samples of the polymeric material alone typically are obtained directly from the manufacturers or they are prepared before exposing them to thermal or radiation conditions. Sometimes these samples are installed in plant's known hot spots to monitor the aging of neighboring cables. These tests are destructive, and therefore, many samples are required if tests are

conducted regularly. Furthermore, for statistical purposes 3-5 samples often are tested at each time to obtain an average value.

Figure 6.32 illustrates the results of ultimate tensile elongation for thermal and irradiation conditions (Ref. 6.30). Under thermal aging, the insulation exhibited a long induction period (Figure 6.32a), during which the elongation remained almost unchanged, followed by a sharp decrease. The results for PE, SBR, and EPR were very similar. By contrast, Figure 6.32b showed a gradual decrease in values with irradiation dose for XLPE. The aging performance of butyl rubber differed substantially (Figure 6.33a) from that of other polymers. Within 40 days of aging at 105°C, butyl rubber lost 40% of its original elongation. During the next 400 days, the elongation value remained nearly constant, but then was followed by a rapid decline, presumably when rubber started to depolymerize. Thus, elongation is not a good aging indicator for this elastomer. However, the tensile strength showed a gradual decrease to zero after 390 days (Figure 6.33b). Similarly, the elongation of PVC had no induction period but steadily decreased with time.

Diffusion-limited oxidation in certain elastomers has caused difficulties in interpreting the tensile properties in terms of Arrhenius plots (Ref. 6.34). The elongation data confirm this finding, while the tensile strength data show clearly a non-Arrhenius behavior. Further investigations indicated that the heterogeneity in modulus profiling caused this discrepancy even both elongation and tensile strength data were taken from the same experiment.

### 6.3.2 Indenter Modulus

The Indenter is a non-destructive device that measures the compressive modulus of jacket and insulation materials of electric cables (Refs. 6.35-6.37). The modulus is determined by pressing a probe of known shape against the wall of the cable at a fixed velocity (0.5 in/min) while measuring the force. The test is terminated when a preset force limit (generally 2 lbs) is reached. The modulus is calculated by dividing the change in force by the change in position during the inward motion of the probe. The indenter is limited to measurements on jackets except where the insulation is exposed (e.g., panels).

Measurements of the compressive modulus can be used for tracking the aging of materials in which this property changes in proportion to the cumulative effects of thermal and radiation stress. This method was effective for EPR, CSPE, PVC, Neoprene, butyl rubber, and silicone rubber. For XLPE, this method is less useful. However, a recent Swedish study (Ref. 6.38) developing a methodology of manipulating experimental data (including indenter modulus data) to derive the activation energy for degradation gave some good indenter data for Rockbestos XLPE and EPR insulation material. If a jacket is used, the Indenter value must be related to degradation of the insulation.

Figure 6.34 shows typical results of measuring the thermal aging Indenter modulus for the jacket of the Okonite Okolon. The modulus values measured with the portable indenter must be corrected for temperature to obtain comparable data to plant environment. The amount of correction required varies with the aging of the cable material (Figure 6.35). In situ tests of the unit in a nuclear power plant demonstrated that it can be used in plants to test cables in trays, panels, and junction boxes, provided that about 3 inches of exposed cable are accessible. The method has yielded good results on cables degraded under radiation (Ref. 6.39).




Figure 6.29 Relative hardness in terms of TMA penetration for EPR (Ref. 6.27)  
Reproduced with permission from Mr. D.J.R. Dodd, Ontario Hydro Technologies, Canada.




Figure 6.30 Thermal decomposition behaviors of PVC (Ref. 6.33)




Figure 6.31 Elongation vs. thermal decomposition temperature by 5% weight loss for PVC (Ref. 6.33)






Figure 6.32 Elongation-at-break for XLPE (Ref. 6.30)  
Reproduced with permission from Mr. D.J.R. Dodd, Ontario Hydro Technologies, Canada.



**Figure 6.33 Tensile elongation and strength change for butyl insulation (Ref. 6.30)**  
 Reproduced with permission from Mr. D.J.R. Dodd, Ontario Hydro Technologies, Canada.



**Figure 6.34 Okonite Okolon jacket moduli (Ref. 6.36)**  
 Copyright © 1993. Electric Power Research Institute. EPRI TR-102399. *Proceedings: 1993 EPRI Workshop on Power Plant Cable Condition Monitoring*. Reprinted with Permission.

The Indenter can only measure the properties of the cable over a limited area in the vicinity of the probe. The indenter modulus shows marked variation if the thickness of the jacket is variable, increasing as the thickness decreases. Extensive baseline data would be required to cover the range of cable materials and constructions used in nuclear power plants. Since the jacket materials tend to degrade more rapidly than the insulation, indenter measurements can give an early warning of a cable's deterioration.

### 6.3.3 Torque Tester

The degradation of jacket materials also can be determined using a torque-strain response method (Ref. 6.33). A pair of chucks are used to grip the outside of the cable, and a small-angle torque, in the range  $\pm 5$  to  $\pm 10^\circ$ , is applied to one of the chucks at up to 2 Hz. A prototype apparatus for such measurements was developed in Japan. Preliminary data on the behavior of XLPE insulation with PVC jacketed (known as CV) cables was used to study the test parameters from this equipment. In both as-received and aged cables, the torque values increased linearly with the applied torque angle up to  $10^\circ$  (Figure 6.36). At higher torque angles, components other than the jacket material will significantly contribute to the values. For non-destructive purposes, a maximum of  $10^\circ$  torque angle was recommended. The effect of the length of the cable between the chucks also was investigated. The optimum length between chucks is 50 mm for PVC cables. At shorter lengths, the measured response strongly depends on the insulation, conductors and any shielding components, whereas with increases in cable length, the sensitivity of the torque-strain response decreases.

There is a strong correlation between the torque values measured using the prototype tester and elongation at break, both for thermally aged materials and for cables subject to sequential radiation and thermal aging (Figure 6.37). A linear relationship between elongation and torque was found over a wide range of elongation values. Deviations from this linear relationship were observed when heterogeneous oxidation occurred in the accelerated tests. The torsion test is a measure of the bulk properties of the jacket material, whereas elongation-at-break is determined by initiation of cracks in the more highly oxidized surface layer in the jacket material. In most cable applications in nuclear power plant, homogeneous oxidation is likely to occur.

JAERI in Japan is developing a portable version of the torque tester which could be clamped onto sections of a cable and would enable data to be taken non-destructively on accessible lengths of cable in situ. Since torque values will be significantly affected by differences in a cable's construction and geometry, baseline data for a wide range of cable types are needed. If the environmental conditions in a plant cause heterogeneous oxidation, the technique would underestimate the degradation of the jacket material.

### 6.3.4 Flexure Tests

In flexure test, the cable is physically bent by hand to examine its flexibility visually. A cable that flexes easily probably is fine. Cracking of the jacket does not necessarily imply that all such cables would fail. This method probably reflects a qualitative assessment of the cable's insulating system. No studies correlating flexure data with other parameters were found.



### 6.3.5 Profiling and Polishing Methods

SNL used the elastic modulus, density, and hardness-profiling methods, as well as polishing the cross-section of a specimen to study the uniformity of the aging process within cable materials. The results from any of the profiling methodologies show the distribution of the parameter (elastic modulus, density, or hardness) across the cross-section of the specimen. This distribution indicates that the values of these physical parameters can be heterogeneous under diffusion-limited oxygen degradation. By polishing a cross section, the variations in oxidation can be examined visually, from the end exposed to oxygen environment to the other. These techniques are not easy to carry out and require sophisticated instruments to slice the cable samples and then test each slice under mechanical testing equipment. Nevertheless, the results can provide a wealth of information for research, and their usefulness is discussed in greater detail in section 4. Alternatively, the computed tomography (CT) technique recently proved to yield similar profiling results.

Figure 6.38 (Ref. 6.40) shows photographs of a series of samples from the same material cut from a square sheet, which were irradiated, and then cross-sectioned and polished. The appearance of distinct optical bands (or rings) suggests strongly heterogeneous degradation for samples irradiated in air at the highest dose rate. Thus, rings are observable for samples B and C, which were irradiated at 0.67 Mrad/hr to 165 and 297 Mrads, respectively. In contrast, samples A, D, and E do not exhibit oxidative rings. A was an unaged sample, D was irradiated at a lower dose rate (i.e., 0.11 Mrad/hr to 175 Mrad), and E was irradiated in an inert atmosphere.

Figure 6.39A shows probe penetration profiles showing the changes in relative hardness on cross-sectioned samples of the EPR material. For unirradiated material, the profile is essentially flat (solid squares). For the samples irradiated at 0.67 Mrad/hr to a dose of 297 Mrad, a distinct flat-bottomed, U-shaped profile is seen (open circles). The boundary position between optical bands (Figure 6.38, exhibit C) corresponds to the steep part of the profile. The irradiated material has become significantly harder (i.e., increased modulus), with the largest increase occurring at the interior portion where oxygen is absent. Figure 6.39B shows data for an EPR sample irradiated at same dose rate to a total dose of 165 Mrad. A somewhat shallower profile was obtained, but with no significant change in the oxygen penetration distance (squares). For a sample irradiated at a lower dose rate (0.11 Mrad/hr to 175 Mrad), the profile becomes homogeneous showing only a slight, shallow curvature (triangles). Similar profiles were obtained by this study when the density gradient data were plotted for the same materials under similar conditions.

### 6.3.6 Hardness Test and Density Measurements

Hardness is a material's resistance to local penetration. One device used for such measurements is the Shore Durometer Type A2. SNL used this method for hardness profiling, and considers that field measurements of this parameter have some correlation to polymer degradation. Figure 6.40 demonstrates the increasing trend in hardness of CSPE jacket that was irradiated (Ref. 6.16).

Density measurements (ASTM D1505: using density gradient column with water and isopropyl alcohol; ASTM D792: using displacement method) showed that the density of insulation tends to increase with age due to oxidation. Thus, as for modulus, the material may be subject to gradients resulting from oxygen diffusion effects. SNL measured bulk density, along with modulus profiling, to examine the effects of oxygen diffusion in the samples (Ref. 6.41). Figure 6.41 illustrates the density changes of the same CSPE sample as that

shown in Figure 6.40 with radiation dose. Ontario Hydro used the former method for XLPE, and latter method on butyl rubber, EPR, and PVC (Ref. 6.31). For most insulations, there was a nearly linear increase in density as a function of radiation dose. An initial increase, followed by a decrease in density has been observed for irradiated XLPE. The increase was attributed to a combination of weight increase by covalently bound oxygen, and a decrease in volume due to the release of gases. Even small changes in density were readily detectable, and a change of only 1-2% was significant in terms of degradation. The density results for XLPE appear to be somewhat more sensitive than elongation (Figure 6.42).

The density values for PVC are plotted in Figure 6.43. It is evident that the change in density differs for PVC compared to XLPE; no induction period was observed. Similar trends were observed for EPR and butyl rubber. The density increase in butyl rubber appears to be caused by simple oxidation. For PVC, the initial increase in density resulted from plasticizer loss. The increase of density in EPR seems to be induced by a combination of oxidation and depletion of low-molecular-weight additives. The TGA results confirmed the presence of low-molecular-weight additives that evolved at accelerated aging temperatures. The results indicate a density change in the region of 0.10 g/cc in PVC, and 0.05 g/cc in EPR is a suitable criterion for detecting degradation, which corresponds to a reduction of 50% in elongation-at-break data.

### 6.3.7 Dynamic Mechanical Analysis (DMA)<sup>2</sup>

In dynamic mechanical analysis, the sample is deformed cyclically, usually under forced vibrations. By monitoring the stress-strain relationship while changing the temperature, information can be obtained about the relaxation behavior of the material. Many modes of vibration are possible, but the most popular are reverse bending (i.e., the double cantilever), axial tension, torsion, and shear. The vibration chosen usually is sinusoidal, simulating the conditions of terminal cables connected to heavy rotary machines in a plant causing this part of the cable to harden with age.

Exploratory experiments were carried out using viscoelastic analysis to diagnose the state of degradation of XLPE, EPR, and PVC insulation material. The dynamic properties of primary interest were storage modulus ( $E'$ ), loss modulus ( $E''$ ), and loss tangent ( $\tan \delta$ ).  $E'$  is a measure of the elastic deformation of a polymer network, while  $E''$  reflects its viscosity. The elastic modulus  $E'$  is expected to be sensitive to crosslinking, and the loss of modulus  $E''$  is more sensitive to scission.  $\tan \delta (=E''/E')$  maxima indicate regions of high energy loss and thereby reflect the motions of various molecular species. By analyzing the temperature dependence of the viscoelastic loss factor ( $\tan \delta$ ), the elastic moduli ( $E'$ ) and the shift in the glass transition temperature ( $T_g$ ), radiation induced damage can be assessed.

---

<sup>2</sup> Private Communication with Mr. D.J. Stonkus, DJS Associates. Reference report may be available directly from Ontario Hydro, Canada. Anandakumaran, K. and Stonkus, D.J., *Assessing Radiation Induced Degradation at High and Low Dose Rates*, Ontario Hydro Technologies Report 91-50-K, 1991. Figures 6.44, 6.45, and 6.46 are reproduced with permission.





Figure 6.37 Correlation of torque value with elongation (Ref. 6.33)



A: Unirradiated material.  
 B:  $6.7 \times 10^5$  rad/h (in air) to 165 Mrad.  
 C:  $6.7 \times 10^5$  rad/h (in air) to 297 Mrad.  
 D:  $1.1 \times 10^5$  rad/h (in air) to 175 Mrad.  
 E:  $1.1 \times 10^6$  rad/h (in vacuum) to 253 Mrad.  
 All irradiations carried out at 70°C. Actual sample thickness = 3.15 mm.

Figure 6.38 Polished samples of irradiated EPR (Ref. 6.40)




Figure 6.39 Relative hardness profiles for irradiated EPR (Ref. 6.40)




Figure 6.40 Hardness of Brand Rex jacket (Ref. 6.16)




Figure 6.41 Density of Brand Rex jacket (Ref. 6.16)




Figure 6.42 Relationship between density and elongation for XLPE (Ref. 6.30)  
Reproduced with permission from Mr. D.J.R. Dodd, Ontario Hydro Technologies, Canada.

Figures 6.44 and 6.45 illustrate the temperature-dependence of  $\tan \delta$  for unaged FREPR and for specimens irradiated to 20, 60, and 100 Mrad at 0.02 Mrad/hr both in air and oxygen. The changes in the dynamic storage moduli as a function of temperature are shown in Figure 4.46 for specimens irradiated to 100 Mrad. The  $\tan \delta$  spectra exhibits a well-resolved peak in the region of  $-50^{\circ}\text{C}$  to  $0^{\circ}\text{C}$ , attributable to glass-transition relaxation, and the position of the  $T_g$  peak shifts to higher temperatures on exposure to radiation. Corresponding shifts in this region also were evident from the modulus plots which, in addition to glass transition, exhibit the crystalline melting region ( $20^{\circ}\text{C}$  to  $90^{\circ}\text{C}$ ). By analyzing these plots, the chemical changes (crosslinking or scission) which contributed to the ultimate degradation of the insulation material can be postulated. For example, samples irradiated in oxygen at 0.02 Mrad/hr (Figure 6.46) showed no measurable modulus above  $80^{\circ}\text{C}$  as the samples melted (above the crystalline melting point), thereby indicating that chain scission had occurred.


The study had found no noticeable changes in properties for XLPE and PVC using DMA. The glass-transition temperature of PVC and the melting temperature of XLPE remained unchanged. However, above these temperatures, these two materials showed a difference in storage modulus, indicative of their degradation mechanisms.

#### 6.4 Methods for Monitoring Electrical Properties


On-site testing of the condition of safety-related cables in nuclear power plants is required to ensure their continued reliability. Several proven conventional or newly developed methods are available to assess the condition of shielded cables. Such methods are based on applying ac or dc voltages which can cause breakdown at a relatively low level only in defective cables, leaving non-defective cables unharmed. Other methods are based on detecting and locating partial discharge sites upon applying of ac voltages at levels which are below the cable's rating. Other methods, intended to evaluate the dielectric characteristics of the cable insulation, such as resistivity, dielectric loss angle ( $\tan \delta$ ) or permittivity, also are readily available and use relatively low voltages, generally much below the cable's rating.

For non-shielded cables, the electric field is not uniform because of the lack of grounded outer electrode (shield). In a metal conduit configuration, for instance, the insulating layer surrounding each conductor is much thinner than the surrounding air and has a relative permittivity (dielectric constant) of 2.3 or more. Thus, when a voltage is applied between the conductor and the conduit, most of the voltage is impressed across the air rather than the cable insulation. Moreover, the portion of the total voltage shared by the cable insulation can vary according to the angular position of the surface of the insulation, and the radial position of the cable within the conduit. Efforts are being made to create a uniform conducting surface around non-shielded cables.


Table 6.3 lists several conventional dielectric tests which include dc tests, high-voltage-power frequency tests, low-voltage swept-frequency tests, and low-voltage impulse or step voltage tests. All these techniques are well understood by insulation researchers, and, at least, laboratory-grade instrumentation is available for these tests. Studies to improve the test configurations to obtain a well-defined ground plane, to correlate the electrical properties with the morphological changes in the insulation properties, and to detect faults in the electrical circuits are among some of the electrical tests discussed below.




**Figure 6.43 Density of PVC jacket for thermal aging at 120°C (Ref. 6.30)**  
 Reproduced with permission from Mr. D.J.R. Dodd, Ontario Hydro Technologies, Canada.



**Figure 6.44 Effect of radiation on loss tangent for FREPR (a) unaged; irradiated in air at 0.02 Mrad/hr to a total dose of (b) 20, (c) 60, and (d) 100 Mrad (See footnote on page 6.39)**  
 Reproduced with permission from Mr. D.J.R. Dodd, Ontario Hydro Technologies, Canada.



**Figure 6.45 Effect of radiation on loss tangent for FREPR (for legend see Figure 6.44: Except samples irradiated under 300 psi oxygen) (See footnote on page 6.39)**  
 Reproduced with permission from Mr. D.J.R. Dodd, Ontario Hydro Technologies, Canada.



**Figure 6.46 Storage modulus of irradiated FREPR (a) unaged; (b) 100 Mrad at 0.02 Mrad/hr in 300 psi Oxygen; (c) at 0.7 Mrad/hr in Air (See footnote on page 6.39)**  
 Reproduced with permission from Mr. D.J.R. Dodd, Ontario Hydro Technologies, Canada.



#### 6.4.1 DC Tests (Insulation Resistance and Polarization Index Tests)

Measurement of DC insulation resistance is one of the commonest electrical tests performed on cables at the time of installation and periodically thereafter. The largest contributors to the initial total current are capacitance-charging current and dielectric-absorption current; these result from the flow of charged atoms (ions), and the rotation of molecular dipoles in the material. The ions are trapped on the surface of the material and contribute to its capacitance but cannot flow out as electrons. Insulations with ionic impurities or with a molecular structure having polar structural groups will have large absorption or capacitance currents. The leakage current, which includes the conduction current and the surface leakage current, predominates after the other two components have become insignificant. This leakage current, which is the electrical current that passes through the insulation, is of particular interest when evaluating the condition of the insulation.

With age and subsequent oxidation, the chemical structure of the polymer insulation can be altered so that its dielectric properties may change. For example, PE essentially is a non-polar material. However, oxidation produces relatively large polar side groups in the polymer chains, which can contribute to the loss of dielectric absorption.

The polarization index (PI) test measures the insulation resistances at one minute and ten minutes after dc voltage is applied. If the ratio of the readings at ten minutes to one minute (i.e., PI) is less than one, it means that the volumetric leakage current through the insulation is high. The insulation commonly is cleaned or dried after low readings. To overcome the strong temperature dependence of the resistance values, PI is generally used, along with the measurements of insulation resistance.

Ontario Hydro used these methods for aged samples of SBR, PVC, butyl rubber, PE and EPR (Ref. 6.30). All these materials were so brittle that they could crack if not handled extremely carefully. The researchers concluded that both insulation resistance and PI values were totally insensitive to the very advanced deterioration of the thermally aged insulation.

SNL used these measurements in their recent LOCA testing of a large number of cable materials for life-extension studies (Refs. 6.42 and 6.43). They performed these tests between the conductor and ground, with all other conductors connected to ground. Measurements were taken at 3 voltages, 50, 100, and 250 V. They found the results were independent of the test voltage, similar to many other researchers using these methods. The study used the variations in insulation resistance measurements (in terms of order of magnitude changes) in their aging assessment of various insulation materials. Figures 6.47 and 6.48 illustrate the insulation resistance and PI values for the Brand Rex cable during various aging conditions, respectively. However, they did not evaluate these measurements as effective condition-monitoring methods during pre-aging.




Figure 6.47 250 V insulation resistance of Brand Rex cable (Ref. 6.16)




Figure 6.48 250 V PI (5min/30s) of Brand Rex cable (Ref. 6.16)

## 6.4.2 AC Impedance Tests (Capacitance and Dissipation Factors)

AC impedance tests are performed with standard electrical equipment available for ac tests on electrical devices such as motors, and transformers. The transfer function obtained indicates the variation of dielectric impedance (principally due to the bulk cable capacitance and conductance) as a function of frequency. The imaginary component indicates the dielectric charge/voltage characteristics at a given frequency, and the phase angle between the real and imaginary components indicates of the dielectric losses as a function of frequency. The tangent of the phase angle  $\delta$  commonly is referred to as the dissipation factor (DF) and is often measured only at a single discrete frequency. The dissipation factor also gives the power factor (PF) since the two are related as  $PF = DF / (1 + DF^2)$ . Since  $\delta$  is a small angle in most instances, the PF is approximately equal to the DF.

**Table 6.6 Diagnostic Test Results for the Lakeview TGS Cables (Ref. 6.44)**

Reproduced with permission from Dr. J.M. Braun, Ontario Hydro, Canada.

Cable	Phase	IR 1 min 10 <sup>12</sup> $\Omega$	DF @ 2.3 kV (%)	Capacitance @ 2.3kV (nF)	PD Inception (kV)	Unshielded BD (kV)		Shielded BD (kV)	
						AC	DC	AC	DC
BF-PM	R	1.5	2.9	1.9	no PD	80		FO86	
	W	0.2	2.9	1.9	no PD	85		FO70	
	B	0.2	2.8	1.9	no PD	75		76	
C-PM	R	0.001	13.3	3.1	5.4		WS	85	
	W	0.001	13.3	3.1	5.8		WS	80	WS
	B	0.001	12.8	3.0	5.2		WS	80	
CCW-PM	R	0.002	7.0	4.1	6.0	40		BD	BD
	W	0.002	6.9	4.1	5.6	BD			32
	B	0.002	6.6	4.1	5.4	BD		40	
	R	0.070	1.9	4.6	no PD			65	
	W	0.002	-	-	4.7			65	WS
	B	0.040	2.4	4.5	no PD			75	
ID-FM	R	0.001	1.6	4.4	5.4	45		BD	BD
	W	0.001	1.7	4.5	4.8	BD			43
	B	0.001	1.5	4.4	5.2	BD		40	

WS=withstood(to 150 kVdc); FO=flashover; BD=damaged by adjacent breakdown; PD=partial discharge; IR=insulation resistance (dc); DF=dissipation factor. Note that CCW-PM cable was tested in two sections.

A study by Ontario Hydro included dielectric testing of a number of 5 kV (triplexed butyl rubber insulated) cables in service for 25 years in an old thermal plant (Ref. 6.44). The cables were routed in both tray and/or underground in conduit to each motor. Non-destructive tests included measurements of partial discharge (PD) insulation resistance and capacitance (C) and dissipation factor (DF). The destructive tests consisted of breaking the cables down with high ac and dc voltage. In laboratory tests, the same measurements were repeated. However, the jacket of the unshielded cables was wrapped in aluminum foil, and then tested in a grounded cable-tray.

Table 6.6 presents the results. The study concluded that there was good agreement between both sets of breakdown voltage data for shielded and unshielded configurations. The results for in situ and laboratory testing were quite consistent. These results further confirm the validity, for suitable cable configurations, of performing conductor-to-conductor tests. While the in situ tests were made on an unshielded configuration, the breakdown data are remarkably similar in both cases.

From the corresponding results of non-destructive diagnostic tests, the study concluded that there is no correlation between any of the diagnostic quantities and the condition of the cable. However, critics of the paper find the basis of this conclusion from limited data is unfounded<sup>3</sup>. Thus, comparing the results for two sections of the CCW-PM cables, the first section with higher DF and lower capacitance values indicate partial discharge, while the second section with opposite test data had no partial discharge. Therefore, there seems to be a strong correlation between capacitance/DF and partial discharge.

Figures 6.49 and 6.50 illustrate the capacitance and DF values versus frequency for Rockbestos conductor tested at SNL (Ref. 6.16). Here, the capacitance values increase with the age at all frequency ranges considered. On the other hand, the dissipation factor values show no significant difference with age at frequencies above 10 Hz, and decrease (except the unaged) with age at lower frequency ranges. The study concluded that none of the electrical tests were effective for monitoring the residual life of cables.

### 6.4.3 Stepped Voltage and High Potential Tests

The stepped voltage tests and high potential tests are high voltage ac/dc tests and are quite similar to those discussed in the previous two category of tests (sections 6.4.1 and 6.4.2). For stepped voltage tests, the voltage is applied in steps up to a maximum voltage, while, in high potential tests, the maximum voltage is applied directly. Typically, in ac tests, the maximum test voltage is twice the rated voltage plus 1000 volts, and for aged components lower values may be used. Both ac and dc tests generally are conducted on a withstand basis, with voltage applied for one minute. If no failure or sign of undue stress (e.g., rapid lowering of insulation resistance) is observed, the insulation is considered as having passed the test. Insulation characteristics (i.e., resistance, capacitance, dissipation factor, leakage currents) can be measured in conjunction with these tests. These values are helpful in interpreting the results of periodic tests. Voltages for routine maintenance tests generally range from 125 to 150% rated voltage for ac tests, and 1.7 times this value for dc tests. The 1.7 factor is an attempt to provide a direct potential corresponding to the peak alternating value.

### 6.4.4 Partial Discharge Test

Measurements of partial discharge (PD) are used to detect defects such as voids, cracks, or sharp conducting protrusions in a cable's insulating system. Such defects can produce discharges in the presence of an applied electrical stress, and are primarily of interest for high voltage cables. The technique applies a variable voltage ac source across the insulation. This excitation voltage is increased until partial discharge arises, producing a signal in the form of a short duration pulse. The pulse is detected both as a direct signal and after reflection from the end of the cable. The principle of the technique as it applies to cables, and the sequence of pulses obtained from a single defect site were studied extensively at the University of Connecticut (Ref. 6.45).

---

<sup>3</sup>Letter from R.D. Meininger to J.A. Tanaka, editor of the IEEE Electrical Insulation Magazine.




Figure 6.49 Capacitance versus frequency for Rockbestos conductor #14 (Ref. 6.16)




Figure 6.50 Dissipation factor versus frequency for Rockbestos conductor #14 (Ref. 6.16)

Although the technique is simple in principle, there are several practical problems associated with simulating an effective ground plane for unshielded cables, filtering other electromagnetic disturbances in a plant, and application to low voltage cables. The instrument developed at UConn uses state-of-the-art electronic hardware and advanced digital processing techniques. The partial discharge signals are reconstructed using cable traveling-wave characteristics (transfer function), and noise is reduced through a judicious choice of hardware and by modern signal enhancements.

The instrument can locate not only PD sites but also faults in the cable. If the faults are of the high impedance type, PD signals may be generated upon applying a moderately high excitation voltage. However, with low impedance faults (extensively charred insulation), a pulse voltage capable of creating an electric arc across the fault can be applied. Most studies have applied the technique in the laboratory. However, for application to field cables, the technique needs improvement; efforts are continuing at UConn. So far, the technique is applicable to shielded cables where a continuous ground plane exists.



### *Ground Plane Simulations Using Ionized Gas*

If a uniform conducting surface could be created around non-shielded cables, even temporarily, this would effectively change them into shielded cables. EPRI conjectured that one such means was to blanket the non-shielded cables with a gas that could be ionized at a relatively low voltage stress. The use of high frequency ac voltage was examined first, and it was found that a high-frequency, high-voltage source could act both as an ionizing and a breakdown source that could distinguish between cables with physically undamaged and damaged insulation. This finding led to the initiation of two programs, one at SNL and the other at UConn, to study the feasibility of a preionized gas method for such cables.

SNL conducted breakdown voltage tests on several undamaged, non-shielded, brands and sizes of cable, housed within metal conduits of various sizes (Ref. 6.46). The position and numbers of cables used were varied, as was the type of gas surrounding them. Specifically, the cases of a cable resting against the conduit wall, and that of a cable centered in the conduit were investigated. The cable was immersed in air, argon, helium, or water. Breakdown voltages were recorded upon applying a 60 Hz ac voltage increasing at a uniform rate. Plots of the ac (rms) current versus voltage characterized the onset of departure from linearity, shown as corona inception. This test was repeated with dc excitation to compare the ionization propensity of the gases as a function of the type of excitation voltage.

Figure 6.51 illustrates results for Brand Rex cable. Most breakdowns in this study resulted from an electrical puncture of the cable's insulation. From these results, ac testing appeared preferable to dc testing because of the variability noted in the dc results. Other conclusions reached by SNL include:

- (a) The ac breakdown voltage for undamaged cable in a conduit containing argon is independent of the cable's location, even when the cable rests on the conduit. Moreover, these breakdown voltages are comparable to those necessary to cause breakdown of the cable immersed in tap water.
- (b) The ac breakdown voltage for undamaged cable in air increased with distance of the cable from the conduit wall, suggesting that ionized air surrounding the cable is much thinner than the surrounding ionized argon.



**Figure 6.51 Peak AC/DC breakdown voltages (Ref. 6.46)**  
 Copyright © 1993. Electric Power Research Institute. EPRI TR-102399. *Proceedings: 1993 EPRI Workshop on Power Plant Cable Condition Monitoring.* Reprinted with Permission.

- (c) Detection of a through-wall cable defect occurs at voltages comparable to the inception of ionization voltages.
- (d) Argon reduces by a factor of 2-3 the voltage necessary for gas ionization or detection of a through-wall damage compared to air. Helium reduces it even more. The peak of the ac voltage is in the range of the dc test voltage necessary to start ionization.
- (e) The rapid rise in ac voltage breakdown of non-shielded cables varies widely, depending on type of insulation and cable's geometry. Breakdown occurs at about the same voltage as for immersion in water.
- (f) Breakdown tests of a bundle of non-shielded cables in a conduit can discriminate between damaged and undamaged cables both in air and in argon.
- (g) For the same cable, the breakdown voltage decreases significantly as the thickness of the insulation is reduced, but remains substantially higher than the breakdown corresponding to through-wall damage to the insulation.

At UConn, the effectiveness of the ionizable gas blanket in creating a conducting surface at ground potential (shield) around the non-shielded cables was investigated using a potentiometric probe method (Ref. 6.47). Gas ionization created a conducting space around the cables, but it failed to move the ground plane all the way to the immediate surface of the cable insulation. However, compared to air, argon provided a considerably larger voltage window above its ionization inception potential before total breakdown occurred. Unlike the SNL results, blanketing the non-shielded cable with inert gas caused sparkover without puncturing the cable's insulation. The study concluded that owing to the considerable breakdown voltage difference between that in air and in inert gases, the method offered an unambiguous means to discriminate between undamaged and defective cables in cases where the defect allows gas to escape. Further studies are necessary before a practical field method can be developed.

Ontario Hydro carried out experiments using their system on a 265 m length of XLPE, 600V triplex control cable (Ref. 6.48). The technique detected partial discharge and located it with good probability on unshielded 5 kV class cables in which adjacent conductors were grounded. However, for low voltage cables, although there was no problem in detecting PD, it was not possible to define the source of the discharge; that is, there appeared to be a multiplicity of sites along the length of the cable, unrelated to the position of an artificial defect. To simplify the problem a 10 m section was tested; Figure 6.52 illustrates the low probability of reliably locating the defect. It was concluded that the reason that the technique was successful with 5 kV cable, but not with 600V cable was related to the cable's geometry. Work has been continuing to solve this problem.

This technique is limited in practice to shielded high-voltage power cables and can only detect defects such as cracks or pin-holes. The technique is not suitable for detecting the gradual changes in a cable's properties which occur with aging.



#### 6.4.5 Voltage Withstand Test

Voltage Withstand testing is similar to high potential testing, discussed earlier. This is a withstand testing of cables, and typically used for post-LOCA mandrel testing. Cables are wrapped on a mandrel, and immersed in tap water at room temperature. While still immersed, these specimens are required to withstand a voltage test for five minutes at a potential of 80 V/mil ac or 240 V/mil dc. Like high potential tests, these methods use high voltages so there are concerns that an undamaged cable may be damaged.


SNL used this method to assess the survivability of aged and artificially damaged cables under LOCA accidents (Refs. 6.49-6.51). Three cables were chosen: Okonite Okolon - EPDM/CSPE. Rockbestos SR with fiberglass jacket, and BrandRex XLPE insulation. In first phase, the method was used as aging method by subjecting the cables to 24 cycles of 240 Vdc/mil (80 Vac/mil for Brand Rex), each cycle consisting of five minutes on and five minutes off, giving a total of 120 minutes energized and 120 minutes de-energized. The objective was to assess whether 240 Vdc/mil high-potential testing of cables immersed in water could damage them; high potential testing did not damage the three types used. Also, based on the limited set of specimens, no effects on length were noted.

In later phases, this method was used to define the minimum thickness required to survive a LOCA after pre-aging the samples with artificial defects. Based on the results, Brand Rex XLPE single conductors with 8 mils of insulation or more remaining are likely to survive in an accident after thermal and radiation aging under the conditions defined in the program. Rockbestos SR single conductors with as little as 4 mils of insulation remaining have a reasonable probability of surviving a similar condition. Thermal aging may have been a significant factor in causing two failures in the Rockbestos SR cables. All of the intentionally damaged Okonite EPDM/CSPE single conductors with less than 15 mils of insulation remaining failed before aging was complete. The one undamaged conductor and the one that had 15 mils of insulation remaining both failed during LOCA simulation shortly after the test chamber became saturated steam. The major causes of the Okonite failures are the extent of the thermal aging and the presence of a bonded CSPE jacket that ages more rapidly than the underlying insulation.


This method was also used in the post-LOCA testing (mandrel bend and hipot) of all cable types in SNL's life-extension study (Ref. 6.51). For XLPE and miscellaneous cables this high potential test itself did not induce any failures (assuming that the cable did not crack during the mandrel bend). However, the post-LOCA testing was very severe for many of the EPR cables, and otherwise functional cables failed.

#### 6.4.6 Time Domain Reflectometry (TDR)

The TDR technique is based on sending a low voltage waveform with a fast transition time down a cable and looking for reflection of the waveform at discontinuities in the cable impedance. The time difference between the initial and reflected pulses indicates the distance from the end of the cable to the discontinuities. The technique does not differentiate between discontinuities arising from different artifacts (e.g., cable splices and connections, and damage areas). Therefore, it is necessary to generate TDR signatures for each cable of interest in a plant to compare with later measurements. The technique is of most use in troubleshooting where its ability to locate the position of the discontinuity is very valuable. TDR is sensitive to damaged cable, i.e., abraded or cracked insulation, but is not good at detecting the more subtle changes arising from degradation. The method was used in assessing cables inside the reactor after the TMI accident (Ref. 6.52).



**Figure 6.52 Spatial distribution of discharge pulse along cable length (Ref. 6.48)**  
 Copyright © 1993. Electric Power Research Institute. EPRI TR-102399. *Proceedings: 1993 EPRI Workshop on Power Plant Cable Condition Monitoring.* Reprinted with Permission.



**Figure 6.53 Surge impedance of 4 kV cables**  
 Reproduced with permission from Mr. Richard Meininger, President of CHAR Services Inc., P.O. Box 119, Lebanon, PA 17042.

As a troubleshooting tool, the TDR technique has been developed into a commercial system (Ref. 6.53), which combines it with traditional measurements of capacitance, dissipation factor, and insulation resistance. An example of a problem was given that identified a wet conductor where the TDR signature before and after the conductor was exposed to wet condition indicated that the wet conductor was located at an RTD. The system can be used on a wide range of cable types and attached apparatus, and is used in power plants. CHAR Services Inc. currently provides services on their test equipment which use this technique. Figure 6.53 illustrates the output of a CHAR system and represents the measurements of the surge impedance of two different cables.


TDR cannot readily detect changes in the cable arising from aging degradation and its resolution for damage is limited, particularly in long cables length ( $> 20$  meters). The technique relies on having signature files for every cable in a power plant. On unshielded cables, this is complicated by the need to repeat the signatures every time a cable is moved. The sensitivity of the TDR technique is limited by the degradation of the waveform over long cables and cannot detect very localized damage.

At UConn, the TDR technique was used to locate partial discharge (PD) in an installed underground shielded cable (Ref. 6.54). The paper described a commercially exploitable instrument capable of locating PD of the order of 1 pC in a high noise environment. Several techniques for signal analysis also were developed by these researchers. The method is adaptive, as it allows the characteristics of the selected cable to be adapted to the real environment.


#### 6.4.7 Dielectric Loss Measurements

Under the influence of the electric field, a reorientation of the electric charges inherent to the material occurs at the electronic, atomic, molecular, and crystalline levels, and migration of free charges (ions and electrons) takes place (Ref. 6.56). The dielectric constant (permittivity) of the material is a function of the various polarization processes (Figure 6.54). These processes are manifested within a typical frequency ranges. If the excitation voltage produces a sinusoidal electric field, the dipoles and free charges tend to move in sympathy with the field, i.e., the dipoles tend to orient themselves parallel to  $E$  (Figure 6.54), the positive free charges move in the direction of  $E$  and because of the viscosity of the dielectric material, a lag develops between the forcing function,  $E$ , and the response of the dipoles and the free charges. As a result, the permittivity assumes a complex form with a real part,  $E'$ , and an imaginary part,  $E''$ , and the energy required to move or reorient the charges becomes a function of frequency. The energy thus expended is known as the dielectric loss, a direct function of the ratio  $E''/E'$ , also referred to as  $\tan \delta$ .

If the loss factor,  $\tan \delta$ , of the cable insulation is plotted versus frequency, it shows typical relaxation peaks which occur within certain frequency ranges. The relaxation peaks corresponding to electronic and atomic polarizations occur at extremely high frequencies ( $> 10^{12}$ ) and, therefore, are of no interest for the Time Domain Spectrometry (TDS) method. However, dipolar and interfacial relaxations as well as increased  $\tan \delta$  due to conduction, occur at the lower end of the frequency spectrum (Figure 6.55), and fall within the measuring capability of the instrumentation used for TDS. As a result of chemical changes in polymers, free radicals (ionic species) are released and polar molecules formed. The  $\tan \delta$  spectrum of the aged materials is expected to gradually increase as the frequency decreases below 1 Hz.



**Figure 6.54 Polarization processes in a typical cable insulation (Ref. 6.56)**  
 Copyright © 1993. Electric Power Research Institute. EPRI TR-102399. *Proceedings: 1993 EPRI Workshop on Power Plant Cable Condition Monitoring.* Reprinted with Permission.



**Figure 6.55 Typical loss factor vs frequency behavior of a cable insulation (Ref. 6.56)**  
 Copyright © 1993. Electric Power Research Institute. EPRI TR-102399. *Proceedings: 1993 EPRI Workshop on Power Plant Cable Condition Monitoring.* Reprinted with Permission.

TDS is a technique for determining the frequency spectrum of the dielectric loss of a cable material from its response to a step voltage excitation. The instrument used for TDS measurements is manufactured and sold by IMASS, and based on the system developed by the NIST (Ref. 6.55). A semiconducting splicing tape is tightly wrapped around the portion of the cable to be tested and surrounded with a metal braid electrode; a grounded guard circuit is added at each of its ends. Several other electrode configurations were tried at UConn (Ref. 6.56), including conducting tape and metallized tape. This particular configuration was selected because of its consistent performance.

A  $\pm 100$  V step voltage is applied across the combined test sample and a reference capacitor. The resulting current, integrated with time, is filtered, amplified, digitized, and subjected to a Fast Fourier analysis to yield the real and imaginary components of the sample's capacitance as a function of frequency. These values, in turn, are used to compute the real and imaginary components,  $E'$  and  $E''$ , and the  $\tan \delta$  ( $=E''/E'$ ), of the cable's insulation. Although this entire information is recorded, only the loss factor,  $\tan \delta$ , is presented in most studies. The frequency range capability of the instrument is  $10^{-4}$  to  $10^4$  Hz, and at the lower frequencies, processing times are longer.


Ontario Hydro (Ref. 6.30), UConn (Ref. 6.56), and Quebec Hydro (Ref. 6.57) have used TDS measurements to study the insulation properties under aging conditions. Figures 6.56 and 6.57 show some examples of their results. Figure 6.56 shows the effect of aging in a mineral environment, while Figure 6.57 illustrates the results for EPR and XLPE in water. At present, TDS measurements are restricted to the laboratory but suitable instrumentation is being developed to use in a plant.

In Britain, researchers have used a video bridge to generate signals of a fixed frequency over the range 20 Hz to 20 kHz, and claim that the dielectric loss spectrum can be developed on long lengths of cable in-plant (Ref. 6.5). The signal is applied to adjacent conductors in multiconductor cables or between conductor and shield in shielded cables. Since no external electrode is used, the loss in the whole cable is determined from measurements made at one end of the cable. The technique is less sensitive than the TDS measurements. However, the equipment is portable and its ease of use on long cables make it practical for assessing cable degradation. It is necessary to disconnect any load from the cable before using this technique. So far, the technique cannot be used on single conductor unshielded cables.


## 6.5 Summary

Since the first EPRI workshop in 1988 on condition monitoring methods for cables, significant advances have been made nationally and internationally in the search for an effective program to assess the condition of cables in nuclear power plants. However, no simple formula has been found, which can provide all the information to characterize the aging of cables and to assure their survivability in accidents. The complexities involved in defining an effective condition monitoring program are so great that one simple method may not provide the solutions needed. This area has the greatest potential for future research that could produce useful results.

EPRI has sponsored several research programs at its member utilities, several universities, and test laboratories such as FRC, University of Virginia and Ontario Hydro to develop methods to monitor the condition of cables inside the containment of nuclear power plants. SNL has tried several methods in their LOCA testing programs and concluded that elongation-at-break is the only one which provides a reliable indication of aging. Japan developed a torque tester, similar in principle to Indenter, and had some promising



**Figure 6.56 TDS results for unaged and aged samples in oil environment (Ref. 6.56)**  
 Copyright © 1993. Electric Power Research Institute. EPRI TR-102399. *Proceedings: 1993 EPRI Workshop on Power Plant Cable Condition Monitoring.* Reprinted with Permission.



**Figure 6.57 TDS results on aged wet at 90°C for 180 days (Ref. 6.56)**  
 Copyright © 1993. Electric Power Research Institute. EPRI TR-102399. *Proceedings: 1993 EPRI Workshop on Power Plant Cable Condition Monitoring.* Reprinted with Permission.

results. CM research in other countries of the Western world has gained interests in recent years and the IEC standards organization and the IAEA have intensified their search for a guideline delineating several CM methods that have some promise. No study has correlated the condition of the jacket material with that of the underlying insulating material. Since the jacket is more accessible for testing than the insulation, a study relating the conditions of these cable materials is warranted.

This section has discussed all published CM methods that have been used or have the potential for monitoring a cable's condition, specifically degradation of the insulation and jacket materials. The methods are discussed in three specific categories: chemical, physical, and electrical. Some of these methods are suitable for laboratory use, and others have some potential to be used in situ. Not all attributes of an effective CM technique can be satisfied by any one method, but a combination of several methods may provide adequate information to characterize the condition of cable materials. Some methods are unlikely to be useful. Table 6.7 summarizes the preliminary findings on the results and the status of the research on these CM methods.

**Table 6.7 Summary of Research on Condition Monitoring Methods**

Number Section	CM Method(s)	Parameter(s) Monitored	Reference(s)	Remarks (see NOTES)
1 6.2.1	Near Infra-Red Reflectance (NIR)	Identifies functional groups that are formed due to oxidation.	6.21 & 6.22	Being studied at Ontario Hydro on PVC jackets. Has some potential for in situ application.
2 6.2.2	Computed Tomography (CT)	Develops profiles of density changes across the specimen thickness.	6.23 - 6.25	Has been used in medical applications. Being studied in Sweden for cables. Recently, Sandia has studied on EPR. Used as a laboratory tool.
3 6.2.3	Sonic Velocity	Measures sonic velocity in the cable jacket.	6.22	Being developed at Ontario Hydro on PVC-jacketed cables. Preliminary results show good correlation with elongation, density, and modulus properties. Because of its portability this has the potential for in situ application.
4 6.2.4	Fourier Transform Infra-Red (FTIR) Spectroscopy	Identifies carbonyl peaks that are formed due to oxidation.	6.26 & 6.27	Has been used as a laboratory tool and has demonstrated good results for XLPE, EPR, and SBR. Not effective for PVC samples.
5 6.2.5	Solubility Measurements (Gel Content & Swelling Ratio)	Indicates chemical degradation (chain scission, crosslinking).	6.26 & 6.27	Demonstrated promising results for EPR, XLPE, SBR, and PVC. Being studied at Ontario Hydro as a laboratory tool.
6 6.2.6	Oxidation Induction Time (OIT)/Temperature under pressure	Measures the amount of antioxidants remaining in the specimen.	6.27 - 6.31	Demonstrated as a good indicator for early stage of degradation for XLPE, EPR, and SBR. Improvements for field application are being studied at Univ. of Virginia under EPRI funding.
7 6.2.7	Plasticizer Content	Measures loss in plasticizer indicating thermal degradation of PVC.	6.30	Ontario Hydro used this technique to assess degradation in field samples of PVC and to differentiate between thermal and irradiation degradation. Has shown good results for field application.
8 6.2.8	Differential Scanning Calorimetry (DSC)	Develops melting endotherms indicating melting points, crystallinity, and glass transition temperature. (Also used for OIT measurements).	6.27 & 6.32	Ontario Hydro has used to study crystallinity and melting endotherms for XLPE. Univ. of Tennessee used this to extract thermal history recorded in the material crystals. Still used as a good laboratory tool for thermal degradation.

Number Section	CM Method(s)	Parameter(s) Monitored	Reference(s)	Remarks (see NOTES)
9 6.2.9	Thermomechanical Analysis (TMA)/ Thermogravimetric Analysis (TGA)	TMA measures the relative hardness while TGA records the mass (or weight) changes with temperature.	6.21, 6.27, 6.33	Ontario Hydro used TMA for studying EPR and PVC. Japan has used TGA experiments at JAERI on PVC samples. Still used as a good laboratory tool.
10 6.3.1	Tensile Tests	Measures tensile strength (TS) and elongation-at-break (EAB).	6.30 & 6.34	Has been proven to be the best indicator of embrittlement (or degradation) for all types of polymers used in cable construction. Widely used as the benchmark for other CM tests. Ontario Hydro suggests 50% absolute elongation as approaching end of life.
11 6.3.2	Indenter Modulus	Measures the compressive modulus.	6.35 - 6.39	Developed by Franklin Research Center under EPRI funding. Commercial units are used by utilities for in-service (or in situ) cable monitoring. Less effective for XLPE.
12 6.3.3	Torque Tester	Measures torque as a function of torsion angle.	6.33	Developed by Japan and found good correlation with other indicators for XLPE and PVC. Still at developing stage for its field application capability. No up to date information available.
13 6.3.4	Flexure Test	Physically bends cable to observe if it flexes and if cracks develop.	6.16 - 6.18	Used as a qualitative measurement of cable's insulation and jacket conditions.
14 6.3.5	Profiling and Polishing Methods	Develops profiles of elastic modulus, density, and hardness across the specimen thickness.	6.16 - 6.18, 6.40	Used as a laboratory tool for examining the variations in physical properties across thickness. Sandia used for detecting heterogeneous degradation in polymers.
15 6.3.6	Hardness and Density Measurements	Measures hardness (as resistance to penetration) and bulk density.	6.16 - 6.18, 6.31	Sandia has used as laboratory tools in their studies for all cable materials.
16 6.3.7	Dynamic Mechanical Analysis (DMA)	Monitors the stress-strain behavior and loss tangent.	Private contact with Mr. D.J. Stonkus.	Ontario Hydro has been studying this technique for XLPE, EPR, and PVC. Still in development stage as a laboratory tool.
17 6.4.1	DC Tests	Measure insulation resistance, leakage current, and polarization index (PI).	6.16 - 6.18, 6.30	All test parameters are insensitive to aging of cable polymers, specifically under dry condition. However, during LOCA testing, the resistance value can vary orders of magnitude due to high temperature and wet condition. Used as an electrical diagnostic tool in maintenance.
18 6.4.2	AC Impedance Tests	Measure transfer function (resistance, capacitance, and inductance), dissipation factor (DF), and power factor (PF) as function of frequency.	6.16 - 6.18, 6.44	Difficult to relate electrical values to cable embrittlement. However, they provide data which are important for assessing the integrities of electrical circuits and wiring systems.
19 6.4.3	Stepped Voltage and High Potential Tests (AC or DC HiPot)	Measure resistance, capacitance, leakage current, and dissipation factor (in dry condition).	6.44	Since these tests may involve higher voltage levels than the rated value for the circuit or equipment, gross degradation in the circuits and wiring systems can be assessed from the test parameters. Currently used in maintenance activities in power industry to assess insulation integrity of the cable system.



Number Section	CM Method(s)	Parameter(s) Monitored	Reference(s)	Remarks (see NOTES)
20 6.4.4	Partial Discharge (PD) Test	Measures inception voltage at which discharge due to ionization occur at cable defects (e.g. voids, cracks).	6.45 - 6.48	Univ. of Connecticut has been developing test equipment for tests in field conditions. Both Sandia and UCONN performed studies for simulating ground planes using inert gases in nonshielded cables. Ontario Hydro also has used this to assess conditions of field cables.
21 6.4.5	Voltage Withstand Test	Based on the breakdown of insulation, this test measures the insulation capacity (in V/mil) by subjecting to high voltages while immersed in water.	6.49 - 6.51	Used as pre- and post-LOCA tests as demonstration of an adequate margins of safety. Cables are wrapped on a mandrel demonstrating mechanical durability. Used more for establishing cable capacity than condition monitoring.
22 6.4.6	Time Domain Reflectometry (TDR)	Compares initial with reflected pulses indicating the distance from the discontinuities in a circuit or wiring system.	6.52 - 6.54	Portable commercial units are used in plants for troubleshooting circuits and wiring systems. Also, impedance tests for monitoring changes in electrical parameters. Used in evaluating circuit faults after TMI accident.
23 6.4.7	Dielectric Loss Measurements (Time Domain Spectrometry/ Video Bridge)	Measures dielectric loss as a function of frequency.	6.5, 6.30, 6.55 - 6.57	TDS was originally developed at NIST and commercial units are now available by IMASS. Technique being studied in laboratory by UCONN, Ontario Hydro, and Quebec Hydro. Britain has been developing this technique using a portable video bridge.

NOTES: All electrical tests require a uniform and continuous ground plane around cables, specifically for nonshielded cables.

In situ application: Testing performed in plant on installed cables. Field application: Testing performed in laboratory on field samples to assess their conditions. Laboratory tool: Testing performed in laboratory on pre-conditioned samples as a research tool.

Most physical and chemical test methods are specific to certain polymeric material, and it is difficult to generalize a method which can be used for all the insulation and jacket materials used by the cable industry. On the other hand, some electrical tests strongly depend on the availability of a reliable and continuous ground plane along the length of the cable; this is very critical for unshielded cables, which is true for most low-voltage power cables.

## 6.6 References

- 6.1 Lofaro, R.J., Gunther, W.E., Villaran, M., et al., "Workshop on Environmental Qualification of Electric Equipment," NUREG/CP-0135, BNL-NUREG-52409, 1994.
- 6.2 "Proceedings: Workshop on Power Plant Cable Condition Monitoring," EPRI EL/NP/CS-5914-SR, 1988.
- 6.3 "Proceedings: 1993 EPRI Workshop on Power Plant Cable Condition Monitoring," EPRI TR-102399, 1993.
- 6.4 Martzloff, F.D., "A Review of Candidate Methods for Detecting Incipient Defects due to Aging of Installed Cables in Nuclear Power Plants," 1988 EPRI Workshop on Cable Condition Monitoring, EPRI EL/NP/CS-5914-SR, 1988.
- 6.5 Burnay, S.G., "Guide for In-Service Monitoring of Radiation Ageing of Insulating Materials," IEC SC15B WG2, 15B (Sec)140-Issue 2, Draft, 1993.
- 6.6 Burnay, S.G. and Hitchon, J.W., "Time-Temperature Superposition in Accelerated Radiation Aging of Elastomers," Trans. of 1984 ANS Meeting, New Orleans, Vol.46, 1984.
- 6.7 Prottas, R.D., Shaw, M.T., and Johnson, J.F., "Analysis of Extruded Cable Dielectrics by GPC, LC, and FTIR," Trans. of 1984 ANS Meeting, New Orleans, Vol.46, 1984.
- 6.8 Osawa, Z., Tsurumi, K., and Konoma, F., "Chemiluminescence of the Thermo-Oxidative Degradation of Polyolefins," Intl. Symp. on Radiation Degradation of Polymers and the Radiation Resistant Materials, Japan, 1989.
- 6.9 Grzybowski, S., Rakowska, A., and Thompson, J.E., "Aging of Polyethylene for Cable Insulation," IEEE Trans. on Electrical Insulation, Vol. EI-22, No. 6, 1987.
- 6.10 Burnay, S.G., "Modelling of Radiation Degradation in Polymeric Cable Materials," IAEA Meeting on Management of Ageing of In-containment I&C Cables, Vienna, 1993.
- 6.11 Stonkus, D.J., "Physical Degradation Assessment of Generator Station Cables," 1988 EPRI Workshop on Cable Condition Monitoring, EPRI EL/NP/CS-5914-SR, 1988.
- 6.12 Jacobus, M.J., "Condition Monitoring and Aging Assessment for Class 1E Cables," OPERA '89, Lyon, France, 1989.
- 6.13 Jacobus, M.J., "Aging, Condition Monitoring, and Loss-of-Coolant Accident (LOCA) Tests of Class 1E Electrical Cables: Summary of Results," SAND91-1397C, Nineteenth Water Reactor Safety Information Meeting, Oct. 28-30, NUREG/CP-0119, Vol.1, 1992.
- 6.14 Gardner, J.B., "Cable Condition Monitoring: the Challenge Before Us," 1993 EPRI Workshop on Cable Condition Monitoring, EPRI TR-102399, 1993.
- 6.15 "IEEE Standard for Type Test of Class 1E Electric Cables, Field Splices, and Connections for Nuclear Power Generating Stations," IEEE Std 383-1974, ANSI N41.10-1975, 1974.
- 6.16 Jacobus, M.J., "Aging, Condition Monitoring, and Loss-of-Coolant Accident (LOCA) Tests of Class 1E Electrical Cables: Crosslinked Polyolefin Cables," NUREG/CR-5772, SAND91-1766/1, Vol.1, 1992.
- 6.17 Jacobus, M.J., "Aging, Condition Monitoring, and Loss-of-Coolant Accident (LOCA) Tests of Class 1E Electrical Cables: Ethylene Propylene Rubber Cables," NUREG/CR-5772, SAND91-1766/2, Vol.2, 1992.
- 6.18 Jacobus, M.J., "Aging, Condition Monitoring, and Loss-of-Coolant Accident (LOCA) Tests of Class 1E Electrical Cables: Miscellaneous Cable Types," NUREG/CR-5772, SAND91-1766/3, Vol.3, 1992.
- 6.19 Jellinek, H.H.G., Aspects of Degradation and Stabilization of Polymers, Elsevier, New York, 1978.
- 6.20 Bolt, R.O. and Carroll, J.G., Radiation Effects on Organic Materials, Academic Press, New York, 1963.

- 6.21 Campbell, D. and White, J.R., Polymer Characterization - Physical Techniques, Chapman and Hall, New York, 1989.
- 6.22 Stonkus, D.J., Lehouckey, E.M., Azizian, H., and Anandakumaran, K., "In Situ Diagnostic Monitoring of Power Plant Cables", 1993 EPRI Workshop on Cable Condition Monitoring, EPRI TR-102399, 1993.
- 6.23 Mattson, B., Stenberg, B., Persson, S., and Ostman, E., "Thermo-Oxidative Degradation of Thick-Walled Rubber Materials Studied by IR-Technique and Computed X-ray Tomography Scanning," Rubber Chemistry and Technology, Vol. 63, pp. 23-31, 1989.
- 6.24 Persson, S. and Ostman, E., "Use of Computed Tomography in Nondestructive Testing of Polymeric Materials," Applied Optics, Vol. 24, No. 23, pp. 4095-4104, 1985.
- 6.25 Gillen, K.T., Clough, R.L., Mattson, B., Stenberg, B., and Ostman, E., "Potential Technique for Non-Destructive Evaluation of Cable Materials," 1993 EPRI Workshop on Cable Condition Monitoring, EPRI TR-102399, 1993.
- 6.26 Anandakumaran, K. and Stonkus, D.J., "Assessing Radiation Induced Degradation at Low and High Dose Rates," IAEA Advisory Group Meeting on Stabilization of Polymers and Organic Materials in Radiation Field, College Park, Maryland, 1991.
- 6.27 Anandakumaran, K. and Stonkus, D.J., "Assessment of Oxidative Thermal Degradation of Crosslinked Polyethylene and Ethylene Propylene Rubber Cable Insulation," Polymer Engineering and Science, Vol.32, No.18, pp. 1386-1393, 1992.
- 6.28 Reynolds, A.B., Mason, L.R., and Doyle, T.E., "OIT Testing as a Life-Assessment Technique for Cable," 1993 EPRI Workshop on Cable Condition Monitoring, EPRI TR-102399, 1993.
- 6.29 Mason, L.R., Doyle, T.E., and Reynolds, A.B., "Effect of Antioxidant Concentration and Radiation Dose on Oxidation Induction Time," IEEE International Symposium on Electrical Insulation, Baltimore, MD., 1992.
- 6.30 Anandakumaran, K., Braun, J.M., Morra, R., and Stonkus, D.J., "Characterization of Aged Station Cable Insulations Comparison of Electrical and Physical Tests," 1993 EPRI Workshop on Cable Condition Monitoring, EPRI TR-102399, 1993.
- 6.31 Anandakumaran, K. and Stonkus, D.J., "Aging Assessment of Nuclear Generating Station Cables," Second International Conference on CANDU Maintenance, Toronto, 1992.
- 6.32 Phillips, P.J., "Fingerprinting the Thermal History of Polymeric Materials," EPRI TR-101205, 1992.
- 6.33 Kusama, Y., Toshiaki, Y., Morita, Y., Kamimura, S., and Yagyu, H., "New Method for Detecting Degradation in Installed Cables in Nuclear Power Plants," 19th Water Reactor Safety Information Meeting, NUREG/CP-0119, Vol.1, p.261, 1991.
- 6.34 Gillen, K.T., Clough, R.L., and Wise, J., "Extrapolating Accelerated Thermal Aging Results: A Critical Look at the Arrhenius Method," Polymers, Vol.34, No.2, 1993.
- 6.35 Shook, T.A. and Gardner, J.B., "Cable Indenter Aging Monitor," EPRI NP-5920, 1988.
- 6.36 Toman, G.J., Hunsader, S., and Peters, D., "In-Plant Indenter Use at Commonwealth Edison Plants," 1993 EPRI Workshop on Cable Condition Monitoring, EPRI TR-102399, 1993.
- 6.37 Carfagno, S.P., Shook, T.A., Gardner, J.B., and Sliter, G., "Development of a Cable Indenter to Monitor Cable Aging In-Situ," OPERA '89, Lyon, France, 1989.
- 6.38 Spang, K., "Methodology for Artificial Aging of Electrical Components in Nuclear Power Plants. Results of Experimental Studies," SKI Technical Report 93:39, Sweden, 1993.
- 6.39 Jacobus, M.J., "Aging and Condition Monitoring of Class 1E Cables," 1993 EPRI Workshop on Cable Condition Monitoring, EPRI TR-102399, 1993.
- 6.40 Clough, R.L., Gillen, K.T., and Quintana, C.A., "Heterogeneous Oxidative Degradation in Irradiated Polymers," NUREG/CR-3643, SAND83-2493, 1984.
- 6.41 Gillen, K.T., Clough, R.L., and Dhooze, N.J., "Applications of Density Profiling to Equipment Qualification Issues," NUREG/CR-4358, SAND85-1557, 1985.

- 6.42 Jacobus, M.J., "Condition Monitoring and Aging Assessment of Class 1E Cables," SAND88-2151C, 1988.
- 6.43 Jacobus, M.J., "Condition Monitoring Methods Applied to Class 1E Cables," Nuclear Engineering and Design, 118, pp. 497-503, 1990.
- 6.44 Braun, J.M., "Condition Assessment of Unshielded Aged Power and Control Cables by Electrical Techniques," IEEE Electrical Insulation Magazine, Vol.8, No.5, 1992.
- 6.45 Mashikian, M.S., Bansal, R., and Northrop, R.B., "Location and Characterization of Partial Discharge Sites in Shielded Power Cables," IEEE Transactions on Power Delivery, Vol.5, No.2, 1990.
- 6.46 Vigil, R.A. and Jacobus, M.J., "Detecting Damaged Cables Using a Preionized Gas Technique," 1993 EPRI Workshop on Cable Condition Monitoring, EPRI TR-102399, 1993.
- 6.47 Mashikian, M.S., Wen, Y., and Dima, A., "Using an Ionizable Gas to Troubleshoot Nonshielded Electric Cables," EPRI TR-101273, 1992.
- 6.48 Braun, J.M., Ford, G.L., Levine, J.P., Maureira, H.A., and Sedding, H.G., "Partial Discharge Assessment of Shielded and Unshielded Cables," 1993 EPRI Workshop on Cable Condition Monitoring, EPRI TR-102399, 1993.
- 6.49 Vigil, R.A. and Jacobus, M.J., "Aging, Loss-of-Coolant Accident (LOCA), and High Potential Testing of Damaged Cables," NUREG/CR-6095, SAND93-1803, 1993.
- 6.50 Vigil, R.A. and Jacobus, M.J., "LOCA Testing of Damaged Cables," 1993 EPRI Workshop on Cable Condition Monitoring, EPRI TR-102399, 1993.
- 6.51 Jacobus, M.J., Zigler, G.L., and Bustard, L.D., "Cable Condition Monitoring Research Activities at Sandia National Laboratories," SAND88-0293C, 1988 EPRI Workshop on Cable Condition Monitoring, EPRI EL/NP/CS-5914-SR, 1988.
- 6.52 Meininger, R.D., Dinsel, M.R., and Soberano, F.T., "Three Mile Island Techniques to Detect Degradation in Electrical Measurement and Control Circuits," International Conference on Nuclear Power Plant Aging, Availability Factor and Reliability Analysis, San Diego, CA., 1985.
- 6.53 Meininger, R.D., "Electronic Characterization and Diagnostics," 1988 EPRI Workshop on Cable Condition Monitoring, EPRI EL/NP/CS-5914-SR, 1988.
- 6.54 Mashikian, M.S., Palmieri, F., Bansal, R., and Northrop, R.B., "Location of Partial Discharges in Shielded Cables in the Presence of High Noise," IEEE Transactions on Electrical Insulation, Vol.27, No.1, 1992.
- 6.55 Mopsik, F.I., "Precision Time-Domain Dielectric Spectrometer," Review Scientific Instruments, 55, pp. 79-87, 1984.
- 6.56 Mashikian, M.S. and Lebow, M., "Signature Files and Instrumentation for the Evaluation of Power Plant Cables by Time-Domain Dielectric Spectroscopy," 1993 EPRI Workshop on Cable Condition Monitoring, EPRI TR-102399, 1993.
- 6.57 Parpal, J.-L., David, E., Seguin, J.-N., and Crine, J.-P., "Characterization of Cable Insulation After Electrical Aging," 1993 EPRI Workshop on Cable Condition Monitoring, EPRI TR-102399, 1993.

## 7. SUMMARY AND CONCLUSIONS

This report summarizes results from a review of published literature on environmental qualification (EQ) of safety-related electric cables used in nuclear power plants. The studies performed by other researchers are discussed in three basic areas; aging characterization, LOCA testing, and condition monitoring methods. The former two areas are directly related to the EQ process of cables for nuclear application. Significant studies addressing various aspects of the EQ requirements have been undertaken at SNL under NRC sponsorship since 1975 (Refs. 7.1 and 7.2). France and Japan also have carried out research to understand the effect of EQ requirements on their cable products. Compared to LOCA testing, aging studies on polymers, typically used for the cable's insulation and jacket materials, have received most attention by the researchers not only in the United States, but also several foreign countries with nuclear programs.

During the last decade, research on the condition monitoring (CM) of cables has attracted interest among the electric utilities and affiliated industries. Significant advancements were made by EPRI who sponsored several programs at various U.S. universities, power plants of its member utilities, and the cable industry (Ref. 7.3 and 7.4). Cooperative programs with individual utilities, foreign agencies (specifically with Ontario Hydro in Canada), and NRC were formed to identify the most effective monitoring methods. Recently, Japan, Great Britain, and Sweden have been developing CM methods. Despite this recent surge, a definite CM method has not been found and work in this area remains very active.

The results from a large number of studies performed by the cable manufacturers on their own products at their own testing facilities were not available for review. Unlike the authors of published studies, these manufacturers have the advantage of knowing the actual composition and formulation of polymeric materials that were used to construct the cables. Because this information is proprietary, most publications do not identify the polymer data, and as a result, the same group of polymeric materials from different manufacturers (in some cases even from the same manufacturer) behave differently under pre-aging and LOCA simulation testing. For the same reason, studies performed in Great Britain and Germany were not readily available for this review.

### 7.1 Summary of Results

There are approximately 60 operating reactors in U.S. with the oldest EQ requirements, DOR Guidelines, 24 with NUREG-0588, Category II requirements, and another 24 with NUREG-0588, Category I requirements. The reactor units using cables satisfying the former two guidelines have less stringent EQ requirements in areas such as qualification by testing, application margins, and consideration of aging and synergistic effects<sup>1</sup>. Although almost all safety-related cables were qualified by testing in which specimens were pre-aged before they were exposed to a LOCA environment, uncertainties associated with various EQ requirements, inconsistent behavior of similar insulating materials from different cable manufacturers, and the presence of hot spots (higher than design basis temperature and radiation conditions) inside the containment, have raised concerns on their reliability. During the last two decades, research in aging and LOCA testing has produced much information, but no quantitative analyses of the adequacy of various aging methods and LOCA profiles in EQ, the influences of margins, presence of hot spots or weak links, test duration, LOCA acceleration, and PRA input. Moreover, the recent failure of certain types of cable (e.g., Okonite) during

---

<sup>1</sup> In some ways, however, early cable qualification programs, in which the duration of LOCA steam/chemical spray exposures was 30 days or longer, were more severe than recent programs. In recent programs, a questionable method (using Arrhenius equation) has been adopted to reduce the duration to 10 days or less.

LOCA tests at SNL (Ref. 7.5 to 7.8) has added further concerns on survivability of in-service cables under postulated design-basis accidents. The conclusions on Okonite Okolon cables derived from these tests are failure-based. Additional studies to identify root causes of such failures could have justified limiting their applicability under high thermal conditions.

The EQ research on cables has produced a massive amount of data on a variety of topics associated with their qualification. The following summarizes findings that are important for the objectives of this literature review.

### *Aging Characterization*

The following summarizes the results obtained from procedures that can simulate conditions representing aged cables in a plant environment:

- (1) The actual environmental conditions (i.e., radiation dose rate and temperature) inside the containment of a plant have been difficult to define in the EQ process. All hot spot locations and cables subject to adverse conditions (i.e., leaky valves) can accelerate degradation more rapidly than anticipated during qualification. During the November 1993 NRC EQ workshop, sharp differences in defining these parameters at different plants were discussed. The radiation dose rate and temperature levels can degrade the cable materials significantly. The current EPRI effort at the University of Connecticut may provide valuable information on the actual in-containment conditions exposed to cables in service; each of the monitoring locations chosen represents a worst-case scenario. Based on the limited information, typical inside-containment environment has a temperature range from 75°F-125°F (25°C-55°C) and a total integrated dose of 10 Mrad of radiation (@ a dose rate of 25-30 rad/hr) for a 40-year design life. These conditions may vary from one plant design to another and do not include hot spot locations which can have temperatures as high as 150°F (65°C) and a total radiation dose as high as 60 Mrad (@ 175 rad/hr). Design considerations during cable installation should eliminate such abnormal conditions by routing cables through a path with a less hostile environment<sup>2</sup>.
- (2) The Arrhenius method may erroneously predict the life of insulation materials (and hence the cable's life), unless appropriate measures are taken in understanding non-Arrhenius behavior at elevated temperatures, in extrapolating the elevated temperature data to actual plant conditions, and in estimating the correct activation energy values. When the range of experimental temperatures encompasses a physical transition of the polymeric material (e.g., crystalline melting point), the degradation process may change within the material, and hence, the activation energy and the Arrhenius behavior. Studies have shown that EPR and XLPO are semicrystalline under typical operating conditions, forcing extrapolations to be made across crystalline melting regions (i.e., 87°C-126°C). The situation is even more complicated for commercial materials, since diluents and plasticizers can lower the melting temperature, and crystalline additives can give peaks of their own.

Since oxidative degradation takes place in the amorphous regions of semicrystalline polymers, extrapolations through the melting temperature of aging results taken above this temperature supposedly would be conservative. Unfortunately, several Japanese studies have shown that an

---

<sup>2</sup> When this is not feasible, it may be necessary to re-evaluate the qualified life of cables in hot spot areas, where the service conditions are more severe than those assumed in the EQ process.

increase in material crystallinity enhances oxidative degradation rates in a gamma-radiation environment, further complicating the extrapolation of the accelerated aging data to the plant environment.

- (3) Effects of dose rates, presence of oxygen, and other factors (e.g., additives) are recognized by majority of studies. If the dose rate can be lowered to a point suitable for the material under consideration, physical degradation caused by diffusion-limited oxidation can be eliminated. However, this effect should be investigated on commercial cable materials with thicker specimens than the materials used in SNL studies. Also, other chemical effects on these specimens need to be better understood.
- (4) Figure 4.13 for XLPO, Table 4.10 for EPR, and Table 4.17 for EPR and XLPE indicate that under combined radiation and thermal environments these insulation materials mechanically degrade faster at room temperature than they do at elevated temperatures. Research on this phenomenon is ongoing at Sandia. If this behavior can impact the overall aging characteristics that have been seen in the accelerated aging procedures, the qualification of these insulating materials may require further scrutiny.
- (5) Some insulating materials are sensitive to the ordering sequence of the environment when compared to the results from the simultaneous environment conditions. Some studies have shown significant synergistic effects among the individual effects from each environmental condition. Most of these studies were performed at elevated temperatures and high radiation dose rates. Comparison with the actual plant environmental conditions needs to be made so that these synergistic or ordering effects can be taken into account in simulating the actual aging conditions.
- (6) The time-temperature-dose rate superposition method seems to predict the actual life estimates, provided that the underlying causes of the degradation processes at such elevated conditions are known. Additional applications of this methodology and comparisons with actual plant aging-data should be made. Methods developed by others should be considered.
- (7) Several studies on aging used small laboratory samples (with all additives, different formulations, and thinner specimens). The validity of these results to actual cables needs further assessment.
- (8) Based on accelerated testing, most jacket materials lost their elongation-at-break values by the time they were exposed to 40 Mrad radiation, while most insulating materials possess only 30% of their original elongation after being irradiated to 50 Mrad and 0% after 130 Mrad. Some of these materials may degrade even further under low dose rates. Before exposing to steam and chemical spray conditions, most cable qualification tests have used 200 Mrad of irradiation which includes 50 Mrad for preaging and 150 Mrad accident radiation. Evaluation of a threshold elongation value for a reasonable assurance of LOCA survivability must consider this intrinsic aging behavior of cable polymers. In view of this, the temperature/radiation sequence or simultaneity may be of secondary importance.
- (9) Cable materials exposed to actual plant environments (i.e., 50°C-65°C and ~5-10Mrad) have indicated degradation in their elongation-at-break (i.e., 0-50% decrease for insulation) after 5-9 years of service. Some EPR and XLPO insulations exposed to normal plant conditions exhibited very little (0-10%) change in their elongation properties. Comparison of these characteristics with accelerated aging test results of similar materials could be beneficial.

## **LOCA Testing**

The following summary covers the research on the LOCA simulations for cables in the environmental qualification process. These topics include polymer behavior and monitoring its physical parameters during the LOCA testing, the effect of different constructions of cables including insulation and jacket materials and conductors, the effect of the simulated environmental conditions, the effects of pre- and post-accident conditions, and the results from post-accident tests.

- (1) Under long-term radiation and high thermal conditions, embrittlement is the predominant aging degradation of a cable's polymeric materials. The physical parameter, elongation-at-break, has been universally accepted to be the most consistent and reliable way to monitor this degradation. However, during LOCA testing, the high dose of radiation in relatively short duration and the hot steam can degrade the already deteriorated insulating system to a zero elongation value. Still, the cable can pass electrical tests indicating its survivability during and after a LOCA event. Many researchers have chosen other physical parameters, such as weight, and tensile strength, to monitor the insulation's condition during such tests. A completely embrittled insulation or jacket is vulnerable to mishandling or mechanical damage (including impingement of the steam). Monitoring service environments to identify hot spots and inspecting cables so that embrittlement, if it occurs, is observed, can assure LOCA survivability.
- (2) The response to LOCA conditions of cable insulation and jacket materials depends on material types, manufacturing processes, and the formulation of chemicals, including additives. In some cases, interaction of the insulation material with the jacket material has exposed bare conductors to the LOCA environment. Sometimes, the cables performed well during accident transient period, but showed signs of failure during the less severe post-transient environment.
- (3) Failure of Kapton cable products during LOCA testing often is related to mishandling the specimens. This problem should be investigated further to understand the reasons and appropriate measures should be identified to supplement the existing qualification procedures.
- (4) Multiconductor cables seem to respond more poorly to LOCA conditions than a single conductor counterpart. Sandia researchers suggested several reasons for the longitudinal cracks in the CSPE and Neoprene jackets. Similarly, the behaviors of coaxial cables and cables with bonded jackets require further characterization during LOCA exposures.
- (5) Based on this literature review, pre-aging has a significant effect on the final response of a cable during LOCA simulations. Extensive results indicate that the cable's responses vary, not only from one aging simulation technique to another, but also from material to material, and with their chemical composition.
- (6) Since the duration of the transient part of an accident is limited, the amount of oxygen or ozone available during this period can significantly affect the overall degradation of cable materials. Therefore, the amount of oxygen that should be included in simulations can be a large factor in selecting the LOCA environments for testing.
- (7) The cable's responses to LOCA conditions do not significantly depend on the steam conditions (superheated or saturated), the chemical spray, synergism between radiation and thermal conditions,



and the high radiation dose rates. Although studies on these issues are limited, compared to the effects of total radiation dose and the high temperature saturated steam conditions dominating the LOCA, these parameters can be considered marginal.

### ***Condition Monitoring***

Monitoring the physical and electrical properties of cables can adequately assure their performance during the design life of a nuclear power plant. Studies on CM methods are recent, and several methods currently being studied are summarized in this report. Some general observations from these studies are given below:

- (1) Chemical tests are useful in revealing the causes of polymer degradation under thermal and radiation environments. Most of these methods are suitable for determining the underlying cause of cable failures, rather than monitoring the condition of cables.
- (2) Physical methods are necessary to characterize the mechanical or physical strength of polymers and provide adequate information on the degradation process. Tests have indicated that cables with zero mechanical strength can survive a design basis accident and can perform their design function (i.e., delivering electric power and transmitting signals to and from connected safety equipment).
- (3) Electrical tests are very important to define the failure of cables under any environmental condition. Presently, most tests have significant limitations in application inside a plant.
- (4) Some efforts are being made to correlate data from chemical and physical tests, but there is little correlation of electrical data with other degradation parameters. This may be due to the fact that electrical tests may not be sensitive to morphological changes in the aged insulation. Nevertheless, morphological changes in the cable's insulation materials must be correlated to changes in electrical property to develop any criterion for its reliable function.
- (5) It is obvious that the jacket material degrades first before there is any sign of deterioration in the insulation. No studies relating the jacket's degradation to that of the insulation material were found.
- (6) Most research on CM methods focused on the technical aspects of the methods. Very few have attempted to establish threshold values or other relevant parameters which can assure the cables with certain aging conditions to survive an impending accident during the design life of a nuclear power plant.

## **7.2 Conclusions**

This literature review encompassed various aspects of the environmental qualification requirements applicable to cables and cable materials. The results presented may not have included all studies in any specific area, but the major concerns and findings affecting the issue are identified. To completely understand the problem, results from ongoing studies should be augmented. Based on the current state of the findings, programs to further clarify technical issues should be developed for future research. Elements that are important in formulating a future research program on the three general areas are discussed in this Section. Finally, some general aspects of the environmental qualification process for cables also are discussed.

### *Aging Characterization*

Using elevated temperatures and high dose-rates for accelerated aging simulation of a plant environment can yield erroneous cable conditions during qualification tests. For some insulation materials, these extreme conditions may not always simulate the worst aging condition at the end of their service life (Accelerated aging can either overshoot or undershoot the conditions reached in actual service). To properly achieve the pre-aging condition of cables before they are exposed to an accident, the following conditions should be considered:

- If the tensile property of the insulation and jacket materials is negligible after the cable is exposed to high accident radiation before exposing to LOCA steam conditions, then the sequence of aging simulation and dose rate effects can be of no significance.

If sequential testing for the environmental conditions is chosen, the ordering and synergistic effects for the material should be assessed. For simultaneous aging conditions, the underlying causes of the effects of different combinations of thermal and radiation conditions should be evaluated.

- The chosen elevated temperatures should be such that the extrapolation does not cross the materials' crystalline melting temperature. The causes of any non-Arrhenius behavior within the temperature range should be examined. The lowest elevated temperature should be close to the actual environmental temperature in the plant so that a different mechanism of degradation (i.e., activation energy) could not dominate in this range; in this way, confidence in the prediction can be high.
- If the material shows a strong dose-rate effect, the rate chosen for the accelerated aging should be as low as possible. The underlying causes for the dose-rate effects should be understood. The equal dose - equal damage criterion can be used only if the dose-rate effects are negligible for the material. Otherwise, time-temperature-dose rate superposition method or other available prediction models can be used.
- Since the presence of oxygen is an important factor affecting the aging of polymers, an adequate supply of air is needed during aging to properly simulate natural environments containing air or oxygen.

### *LOCA Testing*

Proper simulation of LOCA conditions during the qualification can avoid questionable responses. Parameters monitoring the cable's state during the LOCA testing can differ from those during the aging simulations. Moreover, post-LOCA tests (mandrel bend and dielectric withstand) can induce degradation of cables that are otherwise functional. The following suggestions may help formulating the future studies on the subject:

- Cables pre-aged prior to LOCA testing should be compared with naturally aged cables from a variety of in-plant configurations and locations (including bends, vertical runs, and high stress areas, such as thermal and radiation hot spots, high humidity areas, high vibration areas, water/liquid impingement, installation damage, and fire protection coatings) to gain confidence on the qualification process.

- Physical parameters that should monitor the overall state of cables during the test should be identified. Although insulation resistance and leakage currents typically are used, other physical parameters, such as weight change (or density), should be considered and their validity established.
- Defining the failure of a cable during LOCA testing (i.e., establishing acceptance criteria) is another unknown. SNL was using 1 amp fuses to monitor cable functionality. Simulating the performance of cables using actual electrical loads (e.g., power cables with small motors, control cables with SOVs, and instrument cables with transmitters or RTDs) and their ability to operate during the test can be more realistic. Cable application should be simulated and the installed conditions are represented in the LOCA simulation, with considerations for multiconductor, single conductor, and unique installations.
- Post-LOCA mandrel bend testing, in which cable is removed from one mandrel, straightened, and recoiled on another mandrel, imparts an unrealistic stress on the cable which induces failure of good cables. Since most cable materials are brittle at the end of a LOCA test, the use of the mandrel bend test (with a mandrel 40 times the cable diameter) should be evaluated further.
- No research has been undertaken on the adequacy of the LOCA profile, including double-peak versus single-peak profile, LOCA test duration, the influence of margins, and PRA considerations. Research evaluating these factors and the overall level of conservatism in LOCA test profiles would provide important contributions to the EQ process.

### *Condition Monitoring*

Research in developing condition monitoring methods for cables is the weakest compared to aging and LOCA studies. Although the direction of all efforts is indicative of some progress, it is still nowhere near finding the solution soon. However, by looking for all plausible methods that would define the conditions of polymeric materials (with similar formulation and manufacturing process) one at a time, then the chemical and physical degradation of this material can be better understood. Once the behavior of polymers under the influence of temperature, radiation, and humidity is understood, then its impact on electrical properties should be assessed. Correlation of the electrical characteristic with the physical/chemical deterioration of the insulation and jacket materials is an important element for the condition monitoring method. Several suggestions, given below, may enhance the CM research effort and help formulate a research program which can augment the ongoing studies.

- A correlation study of the aging effects on insulation and jacket materials may help in predicting the cable's life.
- Using test methods on naturally aged cables from known environmental conditions might enhance confidence in the test's parameters.
- Based on the aging monitoring data, a threshold value should be identified which will ensure the cable's survival in an accident. For this, reliability studies should be undertaken to develop confidence on the threshold parameter.
- CM techniques should be identified that can detect hot spots in a plant's environment, so that appropriate measures can be taken to minimize their effects on the degradation of cables.

## *Environmental Qualification of Cables*

Based on results presented in this literature review of published studies worldwide, the jacket and the insulation materials of low-voltage safety-related electric cables can lose their entire tensile properties, specifically elongation-at-break, after they are exposed, respectively, to total integrated doses (TIDs) of 50 Mrad of aging and 150 Mrad accident dose in a reactor environment. The qualification of most cables uses testing for a total dose of 200 Mrad first in a sequential method before they can be exposed to steam/chemical spray environment simulating an accident. Therefore, some cables which passed this qualification must have completely embrittled (i.e., zero elongation value) insulation/jacket materials by the end of the accident radiation exposure. Unfortunately, no qualification data on elongation of these cable polymers is available. However, all cables passed the insulation resistance (IR) tests indicating no gross failures or cracks in the insulating system. At least in the few reports available on early cable qualification tests, no voltage withstand test on a 20 times cable diameter mandrel was performed as required by IEEE Std 383-1974. Typically, cable specimens originally mounted on 20 times cable diameter mandrels during pre-aging and accident radiation exposure were directly taken into the steam chamber for steam/chemical spray test.

Furthermore, the tensile properties of embrittled cables without cracks or defects in the insulation materials can improve when exposed to steam. Although there were indications of lowering IR values during the steam test, no appreciable change in this electrical property was noted when the cables were dried after exposure. Almost all cables passed the voltage withstand test on a 40 times cable diameter mandrel after the LOCA test, since the water from the steam acted as a plasticizer, improving the tensile properties of embrittled cable insulations, and thus, providing the necessary flexibility for the mandrel bend. If this scenario is true, then cables now in service in nuclear power plant have the characteristics presented here. Therefore, concerns on various aging and accident simulation methods can be of no significance if the end point of all cables tested is governed by zero elongation-at-break before exposing cables to thermodynamic conditions. The key to maintaining the safety and reliability of the reactor for a safe operation and survival during a design-basis accident is that the embrittled cables are not subject to any mechanical abuse to cause cracks or damages which can be detrimental to their electrical performance.

The limited published data supports the fact that the total normal radiation dose of 10 Mrad (excluding hot spots) during a 40-year design life and another 15-20 Mrad of accident dose (as found in TMI) are more realistic values to which cables in a nuclear power plant can be exposed. The EQ radiation source term in the EQ risk-scoping study (Ref. 7.9) gives a total accident dose of 15 Mrad gamma accident exposure for cables installed in conduits. Cables without shielding could experience larger doses (the report does not mention any quantitative value). Also, depending on the location inside the containment these unshielded cables can be exposed to beta radiation (A typical one year beta dose could be approximately 220 Mrad. Note that the effect of beta radiation are limited to near the surface of insulation or the cable jackets. Metal is a very effective shield for beta radiation, and for cables inside conduits beta effects are not important). At this low dose level of gamma radiation, exposure of neither the jackets nor the insulations could reduce their tensile properties completely, thus assuring their physical integrity, and hence, their electrical reliability. An effective condition monitoring method can provide the necessary assurance on the physical condition of cable's jacket and insulation materials and therefore, can enhance the safety and reliability of this class of cables in nuclear power plants.

### 7.3 References

- 7.1 Holzman, P.M. and Sliter, G.E., "Nuclear Power Plant: Equipment Qualification Reference Manual," EPRI TR-100516, 1992.
- 7.2 Bonzon, L.L., Wyant, F.J., Bustard, L.D., and Gillen, K.T., "Status Report on Equipment Qualification Issues Research and Resolution," NUREG/CR-4301, SAND85-1309, 1986.
- 7.3 "Proceedings: Workshop on Power Plant Cable Condition Monitoring," EPRI EL/NP/CS-5914-SR, 1988.
- 7.4 "Proceedings: 1993 EPRI Workshop on Power Plant Cable Condition Monitoring," EPRI TR-102399, 1993.
- 7.5 Jacobus, M.J., "Aging, Condition Monitoring, and Loss-of-Coolant-Accident (LOCA) Tests of Class 1E Electrical Cables: Crosslinked Polyolefin Cables," NUREG/CR-5772, SAND91-1766/1, Vol.1, 1992.
- 7.6 Jacobus, M.J., "Aging, Condition Monitoring, and Loss-of-Coolant-Accident (LOCA) Tests of Class 1E Electrical Cables: Ethylene Propylene Rubber Cables," NUREG/CR-5772, SAND91-1766/2, Vol.2, 1992.
- 7.7 Jacobus, M.J., "Aging, Condition Monitoring, and Loss-of-Coolant-Accident (LOCA) Tests of Class 1E Electrical Cables: Miscellaneous Cable Types," NUREG/CR-5772, SAND91-1766/3, Vol.3, 1992.
- 7.8 Vigil, R.A. and Jacobus, M.J., "Aging, Loss-of-Coolant Accident (LOCA), and High Potential Testing of Damaged Cables," NUREG/CR-6095, SAND93-1803, 1993.
- 7.9 Bustard, L.D., Clark, J., Medfod, G.T., Kolaczowski, A.M., "Equipment Qualification (EQ) - Risk Scoping Study," NUREG/CR-5313, SAND88-3330, 1989.

**BIBLIOGRAPHIC DATA SHEET**

(See instructions on the reverse)

1. REPORT NUMBER  
(Assigned by NRC, Add Vol., Supp., Rev.,  
and Addendum Numbers, if any.)

NUREG/CR-6384  
BNL-NUREG-52480  
Vol. 1

2. TITLE AND SUBTITLE

Literature Review of Environmental Qualification of  
Safety-Related Electric Cables

Summary of Past Work

3. DATE REPORT PUBLISHED

MONTH YEAR

April 1996

4. FIN OR GRANT NUMBER

W6168/W6169

5. AUTHOR(S)

M. Subudhi

6. TYPE OF REPORT

7. PERIOD COVERED (Inclusive Dates)

8. PERFORMING ORGANIZATION - NAME AND ADDRESS (If NRC, provide Division, Office or Region, U.S. Nuclear Regulatory Commission, and mailing address; if contractor, provide name and mailing address.)

Brookhaven National Laboratory  
Upton, NY 11973-5000

9. SPONSORING ORGANIZATION - NAME AND ADDRESS (If NRC, type "Same as above"; if contractor, provide NRC Division, Office or Region, U.S. Nuclear Regulatory Commission, and mailing address.)

Division of Engineering Technology  
Office of Nuclear Regulatory Research  
U.S. Nuclear Regulatory Commission  
Washington, DC 20555-0001

10. SUPPLEMENTARY NOTES

S.K. Aggarwal, NRC Program Manager

11. ABSTRACT (200 words or less)

This report summarizes the findings from a review of published documents dealing with research on the environmental qualification of safety-related electric cables used in nuclear power plants. Simulations of accelerated aging and accident conditions are important considerations in qualifying the cables. Significant research in these two areas has been performed in the United States and abroad. The results from studies in France, Germany, and Japan are described in this report. In recent years, the development of methods to monitor the condition of cables has received special attention. Tests involving chemical and physical examination of cable's insulation and jacket materials, and electrical measurements of the insulation properties of cables are discussed. Although there have been significant advances in many areas, there is no single method which can provide the necessary information about the condition of a cable currently in service. However, it is possible that further research may identify a combination of several methods that can adequately characterize the cable's condition.

12. KEY WORDS/DESCRIPTORS (List words or phrases that will assist researchers in locating the report.)

electric cables, aging, performance testing, environmental effects,  
nuclear power plants, acceleration electrical equipment, electrical  
insulation, failures, materials testing, monitoring, quality  
assurance, reactor accidents, reviews, service life

13. AVAILABILITY STATEMENT

unlimited

14. SECURITY CLASSIFICATION

(This Page)

unclassified

(This Report)

unclassified

15. NUMBER OF PAGES

16. PRICE



**Federal Recycling Program**