



## TAYLOR & HAMMEL LLC

A LITIGATION AND ENVIRONMENTAL RESEARCH COMPANY

1240 N. PITT STREET, SUITE 200 ALEXANDRIA, VIRGINIA 22314  
TELEPHONE (703) 822-4658 FAX (703) 842-8656  
WEB: [www.taylorhammel.com](http://www.taylorhammel.com) EMAIL: [info@taylorhammel.com](mailto:info@taylorhammel.com)

CASE NO: 2017-0206  
DATE REC'D: 12/22/16  
SPECIALIST:  
RELATED CASE:

December 12, 2016

Freedom of Information Act and Privacy Act (FOIA/PA) Officer  
U.S. Nuclear Regulatory Commission  
Mail Stop T-5 F09  
Washington, DC 20555-0001

### VIA CERTIFIED MAIL

### RE: FREEDOM OF INFORMATION ACT REQUEST

To whom it may concern:

Pursuant to the Freedom of Information Act ("FOIA"), 5 U.S.C. § 552, Taylor & Hammel LLC ("T&H") hereby requests access to any and all correspondence, contracts (including amendments and modifications), reports, inventories, invoices, and other documentation or information in the possession, custody or control of the United States Nuclear Regulatory Commission ("NRC") and NRC contractors that have been collected, received, created, and/or maintained regarding Erico Products Inc. ("Erico") and the practice of cadwelding between 1963 and 1983. T&H understands that Erico produced cadweld rebar splicing kits at its facility in Solon, Ohio, for NRC contractors, which were used during construction of various nuclear facilities around the country and regulated by the NRC and its predecessor the U.S. Atomic Energy Commission ("AEC").

T&H researchers visited the NRC's Public Document Room in Rockville, Maryland, and reviewed the ADAMS database for all documentation on Erico, Cadweld splices, "cadwelding" and Cadweld. From these materials, T&H understands that Erico provided rebar splicing kits and supplied other equipment during the construction of NRC approved nuclear plants, including to the Tennessee Valley Authority. T&H is interested in any correspondence related to the NRC's oversight of these projects as well as any information related to the NRC's regulation of Cadweld Rebar Splices under the U.S. AEC Regulatory Guide 1.10. (see attached).

We recognize that the volume of records responsive to this request may be large. In the past, T&H has worked with government agencies to arrange a visit to review files referenced in our request. This approach allows our researchers to identify a limited number of responsive documents to be copied, thereby reducing the amount of time required by agency officials to review and process documents for release and avoiding an

item-by-item examination of the requested materials. Please contact me as soon as possible concerning the feasibility of this arrangement in this instance.

To the extent that any relevant documents have classification exemptions under FOIA, I request that you sanitize the documents for our review. If there are exempt documents that you will not release and/or sanitize, I request that you identify any and all such documents by listing date, author, recipient(s), page numbers, and subject matter. If any documents contain exemptions, please specify the exemptions claimed for each page or passage. In addition, please advise me of any destruction of relevant records and include the date of and authority for such destruction.

T&H agrees to pay all reasonable and standard processing fees authorized by 5 U.S.C. 552(a)(4)(A) and the applicable regulations up to \$250. If the fees will exceed this amount, please call me with an estimate of the costs so that I can specifically request authorization for expenditures beyond \$250.


If you have any questions, please contact me at 703-373-8137 or email me at [johtaylor@taylorhammel.com](mailto:johtaylor@taylorhammel.com).

Sincerely,



John Taylor  
President

Enclosures



U.S. ATOMIC ENERGY COMMISSION

Revision 1  
1/2/73

# REGULATORY GUIDE

DIRECTORATE OF REGULATORY STANDARDS

## REGULATORY GUIDE 1.10

### MECHANICAL (CADWELD) SPLICES IN REINFORCING BARS OF CATEGORY I CONCRETE STRUCTURES<sup>1</sup>

#### A. INTRODUCTION

General Design Criterion 1 of Appendix A to 10 CFR Part 50, "General Design Criteria for Nuclear Power Plants," requires that structures, systems and components important to safety be designed, fabricated, erected and tested to quality standards commensurate with the importance of the safety functions to be performed. This guide describes an acceptable method of implementing this criterion with regard to the testing and sampling of mechanical splices in reinforcing bars used on Category I concrete structures.<sup>2</sup> The Advisory Committee on Reactor Safeguards has been consulted concerning this guide and has concurred in the regulatory position.

#### B. DISCUSSION

Reinforcing bars for concrete structures are joined together either by lapping, welding, or mechanical splicing. The most common type of mechanical splice is called a Cadweld splice. The minimum requirements for lapping and welding splices are established by existing codes; however, the strength and testing requirements for mechanical splices are not specifically defined in such codes.

The mechanical (Cadweld) splice is used most frequently for #14 and #18 reinforcing bars because (1) the welding of these bars can be performed reliably only if the bar chemistry is controlled and the bar chemistry

is not normally controlled to an extent that would permit reliable welding, and (2) the lapping of these bars is prohibited by applicable codes (American Concrete Institute: Building Code Requirements for Reinforced Concrete, ACI 318-71).

Visual inspection of all the mechanical splices is the fundamental inspection technique, and it can reveal certain deficiencies. However, some splices that pass the visual inspections may not meet tensile test specifications. In order to provide a check on the visual inspections, and to detect symptomatic deficiencies, destructive testing of some splice samples is considered essential as a supplement to the visual inspections. A suitable destructive testing program would provide an adequate basis for assuring that mechanical splices made on in-place reinforcing bars achieve at least the load-carrying capability of the bars.

The testing program in this guide is generally based on present industry practice, and is directed at sampling typical, highly redundant bar-to-bar tensile mechanical splices.

#### C. REGULATORY POSITION

The following procedures should be used for the testing of reinforcing bar mechanical splices in Category I concrete structures:

1. **Crew Qualification:** Each member of the splicing crew (or each crew if the members work as a unit) should prepare two qualification splices for each of the splice positions (e.g., horizontal, vertical, diagonal) to be used. The qualification splices should meet the requirements specified by the designer of the structure and approved by the licensee, pass visual inspection as provided by paragraph 2 below, and meet the tensile tests as provided by paragraph 3 below.

<sup>1</sup> This guide is a revision of former Safety Guide 10. As such, it is applicable to water-cooled nuclear power plants.

<sup>2</sup> Structures, systems and components of a nuclear power plant are designated as Category I if they are designed to withstand the effects of the Safe Shutdown Earthquake (SSE) and remain functional. See Safety Guide 29, "Seismic Design Classification."

#### USAEC REGULATORY GUIDES

Regulatory Guides are issued to describe and make available to the public methods acceptable to the AEC Regulatory staff of implementing specific parts of the Commission's regulations, to delineate techniques used by the staff in evaluating specific problems or postulated accidents, or to provide guidance to applicants. Regulatory Guides are not substitutes for regulations and compliance with them is not required. Methods and solutions different from those set out in the guides will be acceptable if they provide a basis for the findings required to the issuance or continuance of a permit or license by the Commission.

Published guides will be revised periodically, as appropriate, to accommodate comments and to reflect new information or experience.

Copies of published guides may be obtained by request indicating the divisions desired to the U.S. Atomic Energy Commission, Washington, D.C. 20545, Attention: Director of Regulatory Standards. Comments and suggestions for improvements in these guides are encouraged and should be sent to the Secretary of the Commission, U.S. Atomic Energy Commission, Washington, D.C. 20545, Attention: Chief, Public Proceedings Staff.

The guides are issued in the following ten broad divisions:

- |                                  |                        |
|----------------------------------|------------------------|
| 1. Power Reactors                | 6. Products            |
| 2. Research and Test Reactors    | 7. Transportation      |
| 3. Fuel and Materials Facilities | 8. Occupational Health |
| 4. Environmental and Siting      | 9. Antitrust Review    |
| 5. Material and Plant Protection | 10. General            |

Each member of the splicing crew (or each crew of the members working as a unit) is subject to requalification if (1) the specific splice position (e.g., horizontal, vertical, diagonal) has not been used for a period of three months or more, or if (2) completed splices fail to pass the visual inspection set in paragraph 2 below, or fail to pass the tensile tests in paragraph 3 below, or if (3) there is another reason to question their ability. The requalification procedure should be identical to the original qualification procedure described above.

2. Visual Inspection: Each splice should be inspected prior to forcing its wires that all preparations required by the designer and the splice manufacturer have been properly carried out (e.g., cleaning, drying, alignment). All completed mechanical splices should be inspected at both ends of the splice and at the top hole in the center of the splice sleeve in accordance with the requirements specified by the designer of the structure and approved by the Bureau. All visual inspections on completed splices should be performed only after the splices have cooled to ambient temperature.

Among the items which should be included in the specifications are longitudinal cracking of sleeve on the splice ends, ultimate voids in filler metal, extent of lack of filler metal, permissible gap between wire ends, cartridge size, gas blow-out, amount of packing and slag at the top hole. Splices that fail to pass visual inspection should be discarded and replaced, and should not be used as tensile test samples.

3. Tensile Testing: Splice samples may be production splices (i.e., those cut directly from in-place reinforcing) or sister splices (i.e., those removable splices made in-place next to production splices and under the same conditions).

Since curved reinforcing bars will not tensile test accurately, production splice samples should not be removed from curved reinforcing bars for tensile testing. Straight sister splice samples should be made as testing substitutes for each of the required curved reinforcing bar production splices. The sampling frequency specified in paragraph 4b. should then be followed.

Production splice samples should not be cut from the structure where the mechanical splicing device is being welded or on reinforcement in a region of high stress concentration, and/or in a high-tight barrier (e.g., embedded structural steel sections or slurry walls). Representative sister splice samples should be used in such cases.

Splice samples should be subjected to tensile tests in accordance with the sampling frequency specified in paragraph 4a. or paragraph 4b. below, to determine conformance with the following acceptance standards:

a. The tensile strength of each sample tested should equal or exceed 121 percent of the minimum yield strength specified in the ASTM Standard

appropriate for the grade of reinforcing bar using loading rates set forth in ASTM A 370-65, "Standard Methods and Definitions for Mechanical Testing of Steel Products."

b. The average tensile strength of each group of 15 consecutive samples should equal or exceed the guaranteed minimum tensile strength specified for the reinforcing bar.

If any sample tested fails to meet the provisions of paragraph 3a. above, the procedure of paragraph 3b. below should be followed. If the average tensile strength of the 15 samples tested fails to meet the provisions of paragraph 3b. above, the procedure of paragraph 3c. below should be followed.

The locations of all reinforcing bar splices, including replacements for production test samples of mechanical splices should be shown on the submittal drawings which are kept for the plant lifetime. For one year after the commencement of commercial operations, additional records should be kept of all splice samples tested, showing the splice location and identification number, as well as whether the tested splice was a production or sister splice.

4. Tensile Test Frequency: Separate test cycles should be established for mechanical splices in horizontal, vertical, and diagonal bars, for each bar size, and for each splicing crew as follows:

a. Test Frequency for Production Splice Test Samples. (Program to be used where no curved bars are Castwelded). If only production splices are tested, the sample frequency should be:

- 1 of the first 10 splices
- 1 of the next 90 splices
- 2 of the next and subsequent units of 100 splices

b. Test Frequency for Combination of Production and Sister Splices. If production and sister splices are tested, the sample frequency should be:

- 1 production splice of the first 10 production splices
- 1 production and 1 sister splices, for the next 90 production splices
- 3 splices, either production or sister splices, for the next and subsequent units of 100 splices. At least one-fourth of the total number of splices tested should be production splices.

#### 5. Procedure for Substandard Tensile Test Results

a. If any production or sister splice tested fails to meet the tensile test specification of paragraph 3a.

\* Copies may be obtained from the American Society for Testing and Materials, 1714 Race Street, Philadelphia, Pa. 19103.



above, and the observed rate of splices that fail the tensile test at that time does not exceed 1 for each 15 consecutive test samples, the sampling procedure should be started anew.

If any production or sister splice used for testing fails to meet the tensile test specification in paragraph 3a. above, and the observed rate of splices that fail the tensile test exceeds 1 for each 15 consecutive test samples, mechanical splicing should be terminated. In addition, the adjacent production splices on each side of the last failed splice and four other splices distributed uniformly throughout the balance of the 100 production splices under investigation should be tested, and an independent laboratory analysis should be made to identify the cause of all failures. The results of these tests should be evaluated by the designer of the structure and the licensee to determine the required

corrective action. The designer and the licensee should specify the extent of repairs necessary and the actions required to prevent further failures from the identified causes.

If two or more splices from any of these six additional splice samples fail to meet the tensile test specification of paragraph 3a. above, the balance of the 100 production splices under investigation should be rejected and replaced.

When mechanical splicing is resumed, the sampling procedure should be started anew.

b. If the average tensile strength of the 15 consecutive samples fails to meet the provisions of paragraph 3b. above, the designer of the structure and the licensee should evaluate and assess the acceptability of the reduced average tensile strength with respect to the required strength at the location from which the samples were taken.