

ATTACHMENT 3 to AEP:NRC:1166G

PROPOSED REVISED TECHNICAL SPECIFICATIONS PAGES

9303160110 930310
PDR ADOCK 05000315
PDR

REACTOR COOLANT SYSTEM

SURVEILLANCE REQUIREMENTS (Continued)

2. Tubes in those areas where experience has indicated potential problems.
 3. A tube inspection (pursuant to Specification 4.4.5.4.a.8) shall be performed on each selected tube. If any selected tube does not permit the passage of the eddy current probe for a tube inspection, this shall be recorded and an adjacent tube shall be selected and subjected to a tube inspection.
- c. The tubes selected as the second and third samples (if required by Table 4.4-2) during each inservice inspection may be subjected to a partial tube inspection provided:
1. The tubes selected for the samples include the tubes from those areas of the tube sheet array where tubes with imperfections were previously found.
 2. The inspections include those portions of the tubes where imperfections were previously found.
- d. Implementation of the steam generator tube/tube support plate interim plugging criteria for one fuel cycle (Cycle 14) requires a 100% bobbin coil inspection for hot leg tube support plate intersections and cold leg intersections down to the lowest cold leg tube support plate with known outer diameter stress corrosion cracking (ODSCC) indications.

The results of each sample inspection shall be classified into one of the following three categories:

<u>Category</u>	<u>Inspection Results</u>
C-1	Less than 5% of the total tubes inspected are degraded tubes and none of the inspected tubes are defective.
C-2	One or more tubes, but not more than 1% of the total tubes inspected are defective, or between 5% and 10% of the total tubes inspected are degraded tubes.
C-3	More than 10% of the total tubes inspected are degraded tubes or more than 1% of the inspected tubes are defective.

REACTOR COOLANT SYSTEM

OPERATIONAL LEAKAGE

LIMITING CONDITION FOR OPERATION

3.4.6.2 Reactor Coolant System leakage shall be limited to:

- a. No PRESSURE BOUNDARY LEAKAGE,
- b. 1 GPM UNIDENTIFIED LEAKAGE,
- c. 600 gallons per day total primary-to-secondary leakage through all steam generators and 150 gallons per day through any one steam generator for Fuel Cycle 14.
- d. 10 GPM IDENTIFIED LEAKAGE from the Reactor Coolant System,
- e. Seal line resistance greater than or equal to $2.27E-1$ ft/gpm² and,
- f. 1 GPM leakage from any reactor coolant system pressure isolation valve specified in Table 3.4-0.

APPLICABILITY: MODES 1, 2, 3 and 4.**

ACTION:

- a. With any PRESSURE BOUNDARY LEAKAGE, be in at least HOT STANDBY within 6 hours and in COLD SHUTDOWN within the following 30 hours.
- b. With any Reactor Coolant System leakage greater than any one of the above limits, excluding PRESSURE BOUNDARY LEAKAGE, reduce the leakage rate to within limits within 4 hours or be in at least HOT STANDBY within the next 6 hours and in COLD SHUTDOWN within the following 30 hours.
- c. With any reactor coolant system pressure isolation valve(s) leakage greater than the above limit, except when:
 1. The leakage is less than or equal to 5.0 gpm, and
 2. The most recent measured leakage does not exceed the previous measured leakage* by an amount that reduces the

* To satisfy ALARA requirements, measured leakage may be measured indirectly (as from the performance of pressure indicators) if accomplished in accordance with approved procedures and supported by computations showing that the method is capable of demonstrating valve compliance with the leakage criteria.

** Specification 3.4.6.2.e is applicable with average pressure within 20 psi of the nominal full pressure value.

REACTOR COOLANT SYSTEM

BASES

3/4.4.5 STEAM GENERATORS TUBE INTEGRITY

The Surveillance Requirements for inspection of the steam generator tubes ensure that the structural integrity of this portion of the RCS will be maintained. The program for inservice inspection of steam generator tubes is based on a modification of Regulatory Guide 1.83, Revision 1. Inservice inspection of steam generator tubing is essential in order to maintain surveillance of the conditions of the tubes in the event that there is evidence of mechanical damage or progressive degradation due to design, manufacturing errors, or inservice conditions that lead to corrosion. Inservice inspection of steam generator tubing also provides a means of characterizing the nature and cause of any tube degradation so that corrective measures can be taken.

The plant is expected to be operated in a manner such that the secondary coolant will be maintained within those chemistry limits found to result in negligible corrosion of the steam generator tubes. If the secondary coolant chemistry is not maintained within these parameter limits, localized corrosion may likely result in stress corrosion cracking. The extent of cracking during plant operation would be limited by the limitation of steam generator tube leakage between the primary coolant system and the secondary coolant system. The allowable primary-to-secondary leak rate is 150 gallons per day per steam generator for one fuel cycle (Cycle 14). Axial or circumferentially oriented cracks having a primary-to-secondary leakage less than this limit during operation will have an adequate margin of safety to withstand the loads imposed during normal operation and by postulated accidents. Leakage in excess of this limit will require plant shutdown and an inspection, during which the leaking tubes will be located and plugged or repaired. A steam generator while undergoing crevice flushing in Mode 4 is available for decay heat removal and is operable/ operating upon reinstatement of auxiliary or main feed flow control and steam control.

Wastage-type defects are unlikely with the all volatile treatment (AVT) of secondary coolant. However, even if a defect of similar type should develop in service, it will be found during scheduled inservice steam generator tube examinations. Plugging or sleeving will be required for all tubes with imperfections exceeding the repair limit which is defined in Specification 4.4.5.4.a. Steam generator tube inspections of operating plants have demonstrated the capability to reliably detect degradation that has penetrated 20% of the original tube wall thickness.

Tubes experiencing outer diameter stress corrosion cracking within the thickness of the tube support are plugged or repaired by the criteria of 4.4.5.4.a.10.

REACTOR COOLANT SYSTEM

BASES

Maintaining an operating leakage limit of 150 gpd per steam generator (600 gpd total) for Fuel Cycle 14 will minimize the potential for a large leakage event during steam line break under LOCA conditions. Based on the NDE uncertainties, bobbin coil voltage distribution and crack growth rate from the previous inspection, the expected leak rate following a steam line rupture is limited to below 120 gpm in the faulted loop and 150 gpd per steam generator in the intact loops, which will limit offsite doses to within 10 percent of the 10 CFR 100 guidelines. If the projected end of cycle distribution of crack indications results in primary-to-secondary leakage greater than 120 gpm in the faulted loop during a postulated steam line break event, additional tubes must be removed from service in order to reduce the postulated primary-to-secondary steam line break leakage to below 120 gpm.

PRESSURE BOUNDARY LEAKAGE of any magnitude is unacceptable since it may be indicative of an impending gross failure of the pressure boundary. Should PRESSURE BOUNDARY LEAKAGE occur through a component which can be isolated from the balance of the Reactor Coolant System, plant operation may continue provided the leaking component is promptly isolated from the Reactor Coolant System since isolation removes the source of potential failure.

The Surveillance Requirements for RCS Pressure Isolation Valves provide added assurance of valve integrity thereby reducing the probability of gross valve failure and consequent intersystem LOCA. Leakage from the RCS Pressure Isolation Valves is IDENTIFIED LEAKAGE and will be considered as a portion of the allowed limit.

3/4.4.7 CHEMISTRY

The limitations on Reactor Coolant System chemistry ensure that corrosion of the Reactor Coolant System is minimized and reduces the potential for Reactor Coolant System leakage or failure due to stress corrosion. Maintaining the chemistry within the Steady State Limits provides adequate corrosion protection to ensure the structural integrity of the Reactor Coolant System over the life of the plant. The associated effects of exceeding the oxygen, chloride, and fluoride limits are time and temperature dependent. Corrosion studies show that operation may be continued with contaminant concentration levels in excess of the Steady State Limits, up to the Transient Limits, for the specified limited time intervals without having a significant effect on the structural integrity of the Reactor Coolant System. The time interval permitting continued operation within the restrictions of the Transient Limits provides time for taking corrective actions to restore the contaminant concentrations to within the Steady State Limits.

ATTACHMENT 4 to AEP:NRC:1166G

CURRENT PAGES MARKED-UP TO REFLECT PROPOSED CHANGES

REACTOR COOLANT SYSTEM

SURVEILLANCE REQUIREMENTS (Continued)

2. Tubes in those areas where experience has indicated potential problems.
 3. A tube inspection (pursuant to Specification 4.4.5.4.a.8) shall be performed on each selected tube. If any selected tube does not permit the passage of the eddy current probe for a tube inspection, this shall be recorded and an adjacent tube shall be selected and subjected to a tube inspection.
- c. The tubes selected as the second and third samples (if required by Table 4.4-2) during each inservice inspection may be subjected to a partial tube inspection provided:
1. The tubes selected for the samples include the tubes from those areas of the tube sheet array where tubes with imperfections were previously found.
 2. The inspections include those portions of the tubes where imperfections were previously found.
- d. Implementation of the steam generator tube/tube support plate interim plugging criteria for one fuel cycle (Cycle 14th) requires a 100% bobbin coil inspection for hot leg tube support plate intersections and cold leg intersections down to the lowest cold leg tube support plate with known outer diameter stress corrosion cracking (ODSCC) indications.

The results of each sample inspection shall be classified into one of the following three categories:

<u>Category</u>	<u>Inspection Results</u>
C-1	Less than 5% of the total tubes inspected are degraded tubes and none of the inspected tubes are defective.
C-2	One or more tubes, but not more than 1% of the total tubes inspected are defective, or between 5% and 10% of the total tubes inspected are degraded tubes.
C-3	More than 10% of the total tubes inspected are degraded tubes or more than 1% of the inspected tubes are defective.

REACTOR COOLANT SYSTEM

OPERATIONAL LEAKAGE

LIMITING CONDITION FOR OPERATION

3.4.6.2 Reactor Coolant System leakage shall be limited to:

- a. No PRESSURE BOUNDARY LEAKAGE,
- b. 1 GPM UNIDENTIFIED LEAKAGE,
- c. 600 gallons per day total primary-to-secondary leakage through all steam generators and 150 gallons per day through any one steam generator for Fuel Cycle 14.
- d. 10 GPM IDENTIFIED LEAKAGE from the Reactor Coolant System,
- e. Seal line resistance greater than or equal to $2.27E-1$ ft/gpm² and,
- f. 1 GPM leakage from any reactor coolant system pressure isolation valve specified in Table 3.4-0.

APPLICABILITY: MODES 1, 2, 3 and 4.**

ACTION:

- a. With any PRESSURE BOUNDARY LEAKAGE; be in at least HOT STANDBY within 6 hours and in COLD SHUTDOWN within the following 30 hours.
- b. With any Reactor Coolant System leakage greater than any one of the above limits, excluding PRESSURE BOUNDARY LEAKAGE, reduce the leakage rate to within limits within 4 hours or be in at least HOT STANDBY within the next 6 hours and in COLD SHUTDOWN within the following 30 hours.
- c. With any reactor coolant system pressure isolation valve(s) leakage greater than the above limit, except when:
 1. The leakage is less than or equal to 5.0 gpm, and
 2. The most recent measured leakage does not exceed the previous measured leakage* by an amount that reduces the

* To satisfy ALARA requirements, measured leakage may be measured indirectly (as from the performance of pressure indicators) if accomplished in accordance with approved procedures and supported by computations showing that the method is capable of demonstrating valve compliance with the leakage criteria.

** Specification 3.4.6.2.e is applicable with average pressure within 20 psi of the nominal full pressure value.

REACTOR COOLANT SYSTEM

BASES

3/4.4.5 STEAM GENERATORS TUBE INTEGRITY

The Surveillance Requirements for inspection of the steam generator tubes ensure that the structural integrity of this portion of the RCS will be maintained. The program for inservice inspection of steam generator tubes is based on a modification of Regulatory Guide 1.83, Revision 1. Inservice inspection of steam generator tubing is essential in order to maintain surveillance of the conditions of the tubes in the event that there is evidence of mechanical damage or progressive degradation due to design, manufacturing errors, or inservice conditions that lead to corrosion. Inservice inspection of steam generator tubing also provides a means of characterizing the nature and cause of any tube degradation so that corrective measures can be taken.

The plant is expected to be operated in a manner such that the secondary coolant will be maintained within those chemistry limits found to result in negligible corrosion of the steam generator tubes. If the secondary coolant chemistry is not maintained within these parameter limits, localized corrosion may likely result in stress corrosion cracking. The extent of cracking during plant operation would be limited by the limitation of steam generator tube leakage between the primary coolant system and the secondary coolant system. The allowable primary-to-secondary leak rate is 150 gallons per day per steam generator for one fuel cycle (Cycle 19). Axial or circumferentially oriented cracks having a primary-to-secondary leakage less than this limit during operation will have an adequate margin of safety to withstand the loads imposed during normal operation and by postulated accidents. Leakage in excess of this limit will require plant shutdown and an inspection, during which the leaking tubes will be located and plugged or repaired. A steam generator while undergoing crevice flushing in Mode 4 is available for decay heat removal and is operable/operating upon reinstatement of auxiliary or main feed flow control and steam control.

Wastage-type defects are unlikely with the all volatile treatment (AVT) of secondary coolant. However, even if a defect of similar type should develop in service, it will be found during scheduled inservice steam generator tube examinations. Plugging or sleeving will be required for all tubes with imperfections exceeding the repair limit which is defined in Specification 4.4.5.4.a. Steam generator tube inspections of operating plants have demonstrated the capability to reliably detect degradation that has penetrated 20% of the original tube wall thickness.

Tubes experiencing outer diameter stress corrosion cracking within the thickness of the tube support plates are plugged or repaired by the criteria of 4.4.5.4.a.10.

REACTOR COOLANT SYSTEM

BASES

14
Maintaining an operating leakage limit of 150 gpd per steam generator (600 gpd total) for Fuel Cycle 19 will minimize the potential for a large leakage event during steam line break under LOCA conditions. Based on the NDE uncertainties, bobbin coil voltage distribution and crack growth rate from the previous inspection, the expected leak rate following a steam line rupture is limited to below 120 gpm in the faulted loop and 150 gpd per steam generator in the intact loops, which will limit offsite doses to within 10 percent of the 10 CFR 100 guidelines. If the projected end of cycle distribution of crack indications results in primary-to-secondary leakage greater than 120 gpm in the faulted loop during a postulated steam line break event, additional tubes must be removed from service in order to reduce the postulated primary-to-secondary steam line break leakage to below 120 gpm.

PRESSURE BOUNDARY LEAKAGE of any magnitude is unacceptable since it may be indicative of an impending gross failure of the pressure boundary. Should PRESSURE BOUNDARY LEAKAGE occur through a component which can be isolated from the balance of the Reactor Coolant System, plant operation may continue provided the leaking component is promptly isolated from the Reactor Coolant System since isolation removes the source of potential failure.

The Surveillance Requirements for RCS Pressure Isolation Valves provide added assurance of valve integrity thereby reducing the probability of gross valve failure and consequent intersystem LOCA. Leakage from the RCS Pressure Isolation Valves is IDENTIFIED LEAKAGE and will be considered as a portion of the allowed limit.

3/4.4.7 CHEMISTRY

The limitations on Reactor Coolant System chemistry ensure that corrosion of the Reactor Coolant System is minimized and reduces the potential for Reactor Coolant System leakage or failure due to stress corrosion. Maintaining the chemistry within the Steady State Limits provides adequate corrosion protection to ensure the structural integrity of the Reactor Coolant System over the life of the plant. The associated effects of exceeding the oxygen, chloride, and fluoride limits are time and temperature dependent. Corrosion studies show that operation may be continued with contaminant concentration levels in excess of the Steady State Limits, up to the Transient Limits, for the specified limited time intervals without having a significant effect on the structural integrity of the Reactor Coolant System. The time interval permitting continued operation within the restrictions of the Transient Limits provides time for taking corrective actions to restore the contaminant concentrations to within the Steady State Limits.

12

13