

each inservice inspection shall include at least 3% of the total number of tubes in all steam generators; the tubes selected for these inspections shall be selected on a random basis except:

- a. The first sample of tubes selected for each inservice inspection (subsequent to the preservice inspection) of each steam generator shall include:
 1. All nonplugged tubes that previously had detectable wall penetrations (>20%).
 2. At least 50% of the tubes inspected shall be in those areas where experience has indicated potential problems.
 3. A tube inspection (pursuant to Specification 4.19.4.a.8) shall be performed on each selected tube. If any selected tube does not permit the passage of the eddy current probe for a tube inspection, this shall be recorded and an adjacent tube shall be selected and subjected to a tube inspection.
 4. Tubes in the following groups may be excluded from the first random sample if all tubes in a group in both steam generators are inspected. No credit will be taken for these tubes in meeting minimum sample size requirements.
 - (1) Group A-1: Tubes in rows 73 through 79 adjacent to the open inspection lane, and tubes between and on lines drawn from tube 66-1 to tube 75-15 and from 86-1 to 77-15.
 - (2) Group A-2: Tubes having a drilled opening in the 15th support plate.
- b. The tubes selected as the second and third samples (if required by Table 4.19.2) during each inservice inspection may be subjected to a partial tube inspection provided:
 1. The tubes selected for these second and third samples include the tubes from those areas of the tube sheet array where tubes with imperfections were previously found.
 2. The inspection includes those portions of the tubes where imperfections were previously found.

The results of each sample inspection shall be classified into one of the following three categories:

Category

Inspection Results

- | | |
|-----|--|
| C-1 | Less than 5% of the total tubes inspected in a steam generator are degraded tubes and none of the inspected tubes are defective. |
|-----|--|

C-2 One or more tubes, but not more than 1% of the total tubes inspected in a steam generator are defective, or between 5% and 10% of the total tubes inspected are degraded tubes.

C-3 More than 10% of the total tubes inspected in a steam generator are degraded tubes or more than 1% of the inspected tubes are defective.

NOTES: (1) In all inspections, previously degraded tubes must exhibit significant (>10%) further wall penetrations to be included in the above percentage calculations.

(2) Where special inspections are performed pursuant to 4.19.2.a.4, defective or degraded tubes found as a result of the inspection shall be included in determining the Inspection Results Category for that special inspection but need not be included in determining the Inspection Results Category for the general steam generator inspection.

4.19.3 Inspection Frequencies

The required inservice inspections of steam generator tubes shall be performed at the following frequencies:

- a. The first (baseline) inspection was performed after 6 effective full power months but within 24 calendar months of initial criticality. The subsequent inservice inspections shall be performed not more than 24 calendar months after the previous inspection. If the results of two consecutive inspections for a given group of tubes* encompassing not less than 18 calendar months all fall into the C-1 category or demonstrate that previously observed degradation has not continued and no additional degradation has occurred, the inspection interval for that group may be extended to a maximum of once per 40 months.
- b. If the results of the inservice inspection of a steam generator conducted in accordance with Table 4.19-2 at 40 month intervals for a given group of tubes* fall into Category C-3 the inspection frequency for that group shall be increased to at least once per 20 months. The increase in inspection frequency shall apply until the subsequent inspections satisfy the criteria of Specification 4.19.3.a; the interval may then be extended to a maximum of once per 40 months
- c. Additional, unscheduled inservice inspections shall be performed on each steam generator in accordance with the first sample inspection specified in Table 4.19-2 during the shutdown subsequent to any of the following conditions:

*A group of tubes means:

- (a) All tubes inspected pursuant to 4.19.2.a.4, or
- (b) All tubes in a steam generator less those inspected pursuant to 4.19.2.a.4

1. A seismic occurrence greater than the Operating Basis Earthquake.
2. A loss of coolant accident requiring actuation of engineering safeguards, or
3. A major main steam line or feedwater line break.
- d. After primary-to-secondary tube leakage (not including leaks originating from tube-to-tube sheet welds) in excess of the limits of Specification 3.1.6.3, an inspection of the affected steam generator will be performed in accordance with the following criteria:
 1. If the leak is above the 14th tube support plate in a Group as defined in Section 4.19.2.a.4(1) all of the tubes in this Group in the affected steam generator will be inspected above the 14th tube support plate. If the results of this inspection fall into the C-3 category, additional inspections will be performed in the same Group in the other steam generator.
 2. If the leaking tube is not as defined in Section 4.19.3.d.1, then an inspection will be performed on the affected steam generator(s) in accordance with Table 4.19-2.

4.19.4 Acceptance Criteria

a. As used in this Specification:

1. Imperfection means an exception to the dimensions, finish or contour of a tube from that required by fabrication drawing or specifications. Eddy current testing indications below 20% of the nominal tube wall thickness, if detectable, may be considered as imperfections.
2. Degradation means a service-induced cracking, wastage, wear or general corrosion occurring on either inside or outside of a tube.
3. Degraded Tube means a tube containing imperfections $\geq 20\%$ of the nominal wall thickness caused by degradation.
4. % Degradation means the percentage of the tube wall thickness affected or removed by degradation.
5. Defect means an imperfection of such severity that it exceeds the repair limit. A tube containing a defect is defective.

4.19.4 Acceptance Criteria (Continued)

6. Repair Limit means the extent of degradation at or beyond which the tube shall be repaired or removed from service because it may become unserviceable prior to the next inspection.

This limit is equal to 40% of the nominal tube wall thickness.

7. Unserviceable describes the condition of a tube if it leaks or contains a defect large enough to affect its structural integrity in the event of an Operating Basis Earthquake, a loss of coolant accident, or a steam line or feedwater line break as specified in 4.19.3.c., above.
8. Tube Inspection means an inspection of the steam generator tube from the bottom of the upper tubesheet completely to the top of the lower tubesheet, except as permitted by 4.19.2.b.2, above.

- b. The steam generator shall be determined OPERABLE after completing the corresponding actions (removal from service by plugging, or repair by kinetic expansion, sleeving, or other methods, of all tubes exceeding the repair limit and all tubes containing throughwall cracks) required by Table 4.19-2.

4.19.5 Reports

- a. Following the completion of each inservice inspection of steam generator tubes, the number of tubes repaired or removed from service in each steam generator shall be reported to the NRC within 15 days.
- b. The complete results of the steam generator tube inservice inspection shall be reported to the NRC within 3 months following completion of the inspection.

This report shall include:

1. Number and extent of tubes inspected.
2. Location and percent of wall-thickness penetration for each indication of an imperfection.
3. Identification of tubes repaired or removed from service.
- c. Results of steam generator tube inspections which fall into Category C-3 require notification in accordance with 10 CFR 50.72 prior to resumption of plant operation. The written followup of this report shall provide a description of investigations conducted to determine the cause of the tube degradation and corrective measures taken to prevent recurrence in accordance with 10 CFR 50.73.

Bases

The Surveillance Requirements for inspection of the steam generator tubes ensure that the structural integrity of this portion of the RCS will be maintained.

The program for inservice inspection of steam generator tubes is based on modification of Regulatory Guide 1.83, Revision 1. Inservice inspection of steam generator tubing is essential in order to maintain surveillance of the conditions of the tubes in the event that there is evidence of mechanical damage or progressive degradation due to design, manufacturing errors, or inservice conditions. Inservice inspection of steam generator tubing also provides a means of characterizing the nature and cause of any tube degradation so that corrective measures can be taken.

The Unit is expected to be operated in a manner such that the primary and secondary coolant will be maintained within those chemistry limits found to result in negligible corrosion of the steam generator tubes. If the primary or secondary coolant chemistry is not maintained within these chemistry limits, localized corrosion may likely result.

The extent of steam generator tube leakage due to cracking would be limited by the secondary coolant activity, Specification 3.1.6.3.

The extent of cracking during plant operation would be limited by the limitation of total steam generator tube leakage between the primary coolant system and the secondary coolant system (primary-to-secondary leakage = 1 gpm). Leakage in excess of this limit will require plant shutdown and an unscheduled inspection, during which the leaking tubes will be located and repaired or removed from service.

Wastage-type defects are unlikely with proper chemistry treatment of the primary or the secondary coolant. However, even if a defect would develop in service, it will be found during scheduled inservice steam generator tube examinations. Steam generator tube inspections of operating plants have demonstrated the capability to reliably detect degradation that has penetrated 20% of the original tube wall thickness.

Removal from service by plugging, or repair by kinetic expansion, sleeving, or other methods, will be required for degradation equal to or in excess of 40% of the tube nominal wall thickness.

Where experience in similar plants with similar water chemistry, as documented by USNRC Bulletins/Notices, indicate critical areas to be inspected, at least 50% of the tubes inspected should be from these critical areas. First sample inspections sample size may be modified subject to NRC review and approval.

UNITED STATES OF AMERICA
NUCLEAR REGULATORY COMMISSION

IN THE MATTER OF
GPU NUCLEAR CORPORATION

DOCKET NO. 50-289
LICENSE NO. DPR-50

CERTIFICATE OF SERVICE


This is to certify that a copy of Technical Specification Change Request No. 199 to Appendix A of the Operating License for Three Mile Island Nuclear Station Unit 1, has, on the date given below, been filed with executives of Londonderry Township, Dauphin County, Pennsylvania; Dauphin County, Pennsylvania; and the Pennsylvania Department of Environmental Resources, Bureau of Radiation Protection, by deposit in the United States mail, addressed as follows:

Mr. Kenneth E. Witmer, Chairman
Board of Supervisors of
Londonderry Township
25 Roslyn Road
Elizabethtown, PA 17022

Ms. Sally S. Klein, Chairman
Board of County Commissioners
of Dauphin County
Dauphin County Courthouse
Harrisburg, PA 17120

Mr. Thomas Gerusky, Director
PA. Dept. of Environmental Resources
Bureau of Radiation Protection
P.O. Box 2063
Harrisburg, PA 17120

GPU NUCLEAR CORPORATION.

BY: 
Vice President & Director, TMI-1

DATE: 3/12/90