

Table I
Extent of Eddy Current Examinations

| Examination Extent | S/G No. 11 | | S/G No. 12 | |
|--------------------|------------|------|------------|------|
| | Amount | % | Amount | % |
| Full Length | 3169 | 93.5 | 3199 | 94.4 |
| Around U-Bend | 188 | 5.5 | 186 | 5.5 |

Table II
Summary of Eddy Current Indications

| % of Wall Thinning | S/G No. 11 | S/G No. 12 |
|--------------------|------------|------------|
| < 20 | 85 | 29 |
| 20-29 | 12 | 2 |
| 30-39 | 7 | 3 |
| 40-49 | 0 | 0 |
| ≥ 50 | 0 | 0 |