



NUCON International, Inc.

P.O. BOX 29151 7000 HUNTLEY ROAD
COLUMBUS, OHIO 43229 U.S.A.

TELEPHONE: (614) 846-5710
OUTSIDE OHIO: 1-800-992-5192
TELEX: 6974415
FAX: (614) 431-0858

PYROLYSIS GAS CHROMATOGRAPHY

ANALYSIS OF 21 THERMO-LAG

FIRE BARRIER SAMPLES

Performed For:

**PECO Energy Company
2301 Market Street
P.O. Box 8699
Philadelphia, PA 19101-8699**

P.O. No. GN265985

28 June 1995

Distribution

PECO: George J. Siefert (1)

NEI: Biff Bradley (1)

**NUCON: 06PB847 Master File (1)
Lab (1)**

NUCON 06PB847/01

NUCON 06PB847/01

NUCON International, Inc.

P.O. BOX 29151 7000 HUNTLEY ROAD
COLUMBUS, OHIO 43229 U.S.A.

TELEPHONE: (614) 846-5710
OUTSIDE OHIO: 1-800-992-5192
TELEX: 6974415
FAX: (614) 431-0858

Prepared By

Reviewed By

Original Issue

W. P. Freeman

W. P. Freeman

30 June 95

Date

T. S. Keller

T. S. Keller

30 June 1995

Date

I. ABSTRACT

Inspection of the pyrograms of 21 Thermo-Lag fire barrier samples indicated that they are all similar in chemical composition.

II. OBJECTIVE

Pyrolysis Gas Chromatography (PGC) with Mass Selective Detection (MSD) was used to qualitatively compare twenty-one Thermo-Lag fire barrier samples.

III. DESCRIPTION OF METHOD

The samples were compared by pyrolysis gas chromatography using ASTM D3452 as a general guide. A Hewlett-Packard model 5890 series II gas chromatograph equipped with a Hewlett Packard model 5972 mass selective detector was used to generate chromatograms of the pyrolysis products. Pyrolysis of the Thermo-Lag samples were performed with a CDS pyroprobe mounted in an independently heated interface attached to the injection port of the GC. Analysis involved weighing 1-3 mgs. of sample in a quartz tube and placement of the tube in the platinum coil element of the probe. The probe is then placed in the interface and pyrolysed ballistically for 2 seconds. Pyrolytic products are then swept by the carrier gas onto the fused silica capillary column where they are separated and detected with a MSD. Chromatographic and pyrolysis conditions are shown in Table 1. Prior to each analysis, the column is heated to 250°C to elute any volatiles which were not entrained in the polymer.

IV. PRESENTATION OF RESULTS

The twenty-one pyrograms (total ion chromatograms) for each of the twenty-one Thermo-Lag samples are shown in Odd numbered Figures 1-41. The extracted ion chromatograms using the acrylate base ion m/e of 55 common to ethyl acrylate (EA) and m/e of 69 common to methyl methacrylate (MMA) for each sample are shown in even numbered Figures 2-42. The sample name at the top of each figure is the NUCON Log # I. D. Samples 0495-5A-F for Peach Bottom and 0495-6A-O for Limerick are further identified in Table 2 along with their respective EA/MMA area ratios and sample densities. Each set of figures is followed by a library search, which identifies some of the major peaks from each sample's pyrogram, and a summary area percent report.

V. DISCUSSION OF RESULTS

The average extracted ion area ratio of EA/MMA of 1.30 ± 0.10 ($\pm\sigma$) for the Peach Bottom samples, of 1.28 ± 0.05 ($\pm\sigma$) for the Limerick Unit 2 samples, of 1.28 ± 0.06 ($\pm\sigma$) for the Limerick Unit 1 samples, of 1.29 ± 0.07 ($\pm\sigma$) for the Limerick Control Building samples and of 1.29 ± 0.07 ($\pm\sigma$) for all twenty-one samples is consistent with average EA/MMA area ratio of 1.4 ± 0.1 ($\pm\sigma$) obtained from other Thermo-Lag samples tested under the NEI generic testing program.

The extracted ion chromatograms shown in Figure 2 for sample 0495-5A a 3 hour rated panel sample, have an EA/MMA of 1.35. Pyridine compounds identified in the pyrogram (Figure 2) are pyridine, 3-methyl pyridine, 3, 5-dimethyl pyridine, 2, 3, 5-trimethyl pyridine 3-ethyl-5-methyl pyridine and 5-ethenyl-2-methyl pyridine. Other key components identified are 2, 3, 4, 5-tetramethyl-1H-pyrrole, pentanedioic acid diethyl ester (visual inspection), triphenyl phosphate, octicizer and tris (methylphenyl) phosphate.

The extracted ion chromatograms shown in Figure 4 for sample 0495-5B, a trowel grade sample, have an EA/MMA ratio of 1.25. Pyridine compounds identified in the pyrogram (Figure 3) are pyridine, 3-methyl pyridine and 2, 5-dimethyl pyridine. Other key components identified are 2, 3, 4, 5-tetramethyl-1H-pyrrole, pentanedioic acid diethyl ester, triphenyl phosphate, octicizer and tris (methylphenyl) phosphate.

The extracted ion chromatograms shown in Figure 6 for sample 0495-5C, a 3 hour rated panel sample, have an EA/MMA ratio of 1.43. Pyridine compounds identified in the pyrogram (Figure 5) are 3-methyl pyridine, 2, 5-dimethyl pyridine, 3-ethyl pyridine, 3-ethenyl-pyridine, 3, 5-dimethyl pyridine, 2, 3, 5-trimethyl pyridine, 3-ethyl-5-methyl pyridine and 5-ethenyl-2-methyl pyridine. Other key components identified are 2, 3, 4, 5-tetramethyl-1H-pyrrole, pentanedioic acid diethyl ester, triphenyl phosphate, octicizer and tris (methylphenyl) phosphate.

The extracted ion chromatograms shown in Figure 8 for sample 0495-5D have an EA/MMA ratio of 1.26. Pyridine compounds identified in the pyrogram (Figure 7) are pyridine, 3-methyl pyridine, 3, 5-dimethyl pyridine, 2, 3, 5-trimethyl pyridine, 3-ethyl-5-methyl pyridine and 5-ethenyl-2-methyl pyridine. Other key components identified are 2, 3, 4, 5-tetramethyl-1H-pyrrole, pentanedioic acid diethyl ester, triphenyl phosphate, octicizer and tris (methylphenyl) phosphate.

The extracted ion chromatograms shown in Figure 10 for sample 0495-5E, have an EA/MMA ratio of 1.15. Pyridine compounds identified in the pyrogram (Figure 10) are 3-methyl pyridine and 3, 5-dimethyl pyridine. Other key components identified are 2, 3, 4, 5-tetramethyl-1H-pyrrole, pentanedioic acid diethyl ester, triphenyl phosphate, octicizer and tris (methylphenyl) phosphate.

The extracted ion chromatograms shown in Figure 12 for sample 0495-5F, a trowel grade sample, have an EA/MMA ratio of 1.38. Pyridine compounds identified in the pyrogram (Figure 11) are pyridine, 3-methyl pyridine, 3, 5-dimethyl pyridine, 2, 3, 5-trimethyl pyridine and 5-ethyl-2-methyl pyridine. Other key components identified are 2, 3, 4, 5-tetramethyl-1H-pyrrole, pentanedioic acid diethyl ester, octicizer, triphenyl phosphate and tris (methylphenyl) phosphate.

The extracted ion chromatograms shown in Figure 14 for sample 0495-6A, a trowel grade sample, have an EA/MMA ratio of 1.30. Pyridine compounds identified in the pyrogram (Figure 13) are pyridine, 3-methyl pyridine, 3, 5-dimethyl pyridine, 2, 3, 5-trimethyl pyridine and 5-ethenyl-2-methyl pyridine. Other key components identified are 2, 3, 4, 5-tetramethyl-1H-pyrrole, pentanedioic acid diethyl ester, triphenyl phosphate, octicizer, and tris (methylphenyl) phosphate.

The extracted ion chromatograms shown in Figure 16 for sample 0495-6B, a 3 hour rated panel sample, have an EA/MMA ratio of 1.27. Pyridine compounds identified in the pyrogram (Figure 15) are 3-methyl pyridine, 2, 5-dimethyl pyridine, and 3-ethenyl-2-methyl pyridine. Other key components identified are 2, 3, 4, 5-tetramethyl-1H-pyrrole, pentanedioic acid diethyl ester, tris (methylphenyl) phosphate and octicizer.

The extracted ion chromatograms shown in Figure 18 for sample 0495-6C, a 3 hour rated conduit sample, have an EA/MMA ratio of 1.20. Pyridine compounds identified in the pyrogram (Figure 17) are 3-methyl pyridine. Other key components identified are 2, 3, 4, 5-tetramethyl-1H-pyrrole, pentanedioic diethyl ester, octicizer and tris (methylphenyl) phosphate.

The extracted ion chromatograms shown in Figure 20 for sample 0495-6D, a 1 hour rated panel sample, have an EA/MMA ratio of 1.34. Pyridine compounds identified in the pyrogram (Figure 19) are pyridine 3-methyl pyridine, 3, 5-dimethyl pyridine, 2-ethyl-6-methyl pyridine, 2, 3, 5-trimethyl pyridine, 3-ethyl-5-methyl pyridine and 5-ethenyl-2-methyl pyridine. Other key components identified are 2, 3, 4, 5-tetramethyl-1H-pyrrole, pentanedioic acid, diethyl ester, tris (methylphenyl) phosphate, and octicizer.

The extracted ion chromatograms shown in Figure 22 for sample 0495-6E, a 1 hour rated conduit sample, have an EA/MMA ratio of 1.30. Pyridine compounds identified in the pyrogram (Figure 21) are pyridine, 3-methyl pyridine, 3, 5-dimethyl pyridine, 2, 3, 5-trimethyl pyridine and 3-ethyl-5-methyl pyridine. Other key components identified are 2, 3, 4, 5-tetramethyl-1H-pyrrole, pentanedioic acid diethyl ester, octicizer and tris (methylphenyl) phosphate.

The extracted ion chromatograms shown in Figure 24 for sample 0495-6F, a trowel grade sample, have an EA/MMA ratio of 1.28. Pyridine compounds identified in the pyrogram (Figure 23) are 3-methyl pyridine, 2, 4-dimethyl pyridine, 2, 3, 5-trimethyl pyridine, 3-ethyl-5-methyl pyridine and 5-ethenyl-2-methyl pyridine. Other key components identified are 2, 3, 4, 5-tetramethyl-1H-pyrrole, pentanedioic acid diethyl ester, octicizer and tris (methylphenyl) phosphate.

The extracted ion chromatograms shown in Figure 26 for sample 0495-6G, a 1 hour rated panel sample, have an EA/MMA ratio of 1.30. Pyridine compounds identified in the pyrogram (Figure 25) are 3-methyl pyridine (visual inspection). Other key components identified are 2, 3, 4, 5-tetramethyl-1H-pyrrole, pentanedioic acid diethyl ester, octicizer and tris (methylphenyl) phosphate.

The extracted ion chromatograms shown in Figure 28 for sample 0495-6H, a 1 hour rated conduit sample, have an EA/MMA ratio of 1.31. Pyridine compounds identified in the pyrogram (Figure 27) are 3-methyl pyridine, 3, 5-dimethyl pyridine and 2, 3, 5-trimethyl pyridine. Other key components identified are 2, 3, 4, 5-tetramethyl-1H-pyrrole, pentanedioic acid diethyl ester, octicizer and tris (methylphenyl) phosphate.

The extracted ion chromatograms shown in Figure 30 for sample 0495-6I, a 3 hour rated panel sample, have an EA/MMA ratio of 1.19. Pyridine compounds identified in the pyrogram (Figure 29) are pyridine, 3-methyl pyridine, 2-methyl pyridine and 3, 5-dimethyl pyridine. Other key components identified are pentanedioic acid diethyl ester, octicizer and tris (methylphenyl) phosphate.

The extracted ion chromatograms shown in Figure 32 for sample 0495-6J, a 3 hour rated conduit sample, have an EA/MMA ratio of 1.36. Pyridine compounds identified in the pyrogram (Figure 31) are pyridine, 3-methyl pyridine, 3, 5-dimethyl pyridine, 2, 3, 5-trimethyl pyridine, 3-ethyl-5-methyl pyridine and 5-ethenyl-2-methyl pyridine. Other key components identified are 2, 3, 4, 5-tetramethyl-1H-pyrrole, pentanedioic acid diethyl ester, triphenyl phosphate, octicizer and tris (methylphenyl) phosphate.

The extracted ion chromatograms shown in Figure 34 for sample 0495-6K, a trowel grade sample, have an EA/MMA ratio of 1.30. Pyridine compounds identified in the pyrogram (Figure 33) are pyridine, 3-methyl pyridine, 3, 5-dimethyl pyridine, 2, 3, 5-trimethyl pyridine, 3-ethyl-5-methyl pyridine and 5-ethenyl-2-methyl pyridine. Other key components identified are 2, 3, 4, 5-tetramethyl-1H-pyrrole, pentanedioic acid diethyl ester, triphenyl phosphate, octicizer and tris (methylphenyl) phosphate.

The extracted ion chromatograms shown in Figure 36 for sample 0495-6L, a 3 hour rated conduit sample, have an EA/MMA ratio of 1.28. Pyridine compounds identified in the pyrogram (Figure 35) are 3-methyl pyridine. Other key components identified are 2, 3, 4, 5-tetramethyl-1H-pyrrole, pentanedioic acid diethyl ester and tris (methylphenyl) phosphate (visual inspection).

The extracted ion chromatograms shown in Figure 38 for sample 0495-6M, a 1 hour rated panel sample, have an EA/MMA ratio of 1.19. Pyridine compounds identified in the pyrogram (Figure 37) are 3-methyl pyridine. Other key components identified are 2, 3, 4, 5-tetramethyl-1H-pyrrole (visual inspection), pentanedioic acid dimethyl ester, (visual inspection), triphenyl phosphate, octicizer and tris (methylphenyl) phosphate.

The extracted ion chromatograms shown in Figure 40 for sample 0495-6N, a 1 hour rated panel sample, have an EA/MMA ratio of 1.32. Pyridine compounds identified in the pyrogram (Figure 39) are pyridine, 3-methyl pyridine, 3, 5-dimethyl pyridine, 2, 3, 5-trimethyl pyridine, 3-ethyl-5-methyl pyridine and 5-ethenyl-2-methyl pyridine. Other key components identified are 2, 3, 4, 5-tetramethyl-1H-pyrrole, pentanedioic acid diethyl ester, octicizer and tris (methylphenyl) phosphate.

The extracted ion chromatograms shown in Figure 42 for sample 0495-6O, a 3 hour rated panel sample, have an EA/MMA ratio of 1.37. Pyridine compounds identified in the pyrogram (Figure 41) are 3-methyl pyridine and 3, 4-dimethyl pyridine. Other key components identified are 2, 3, 4, 5-tetramethyl-1H-pyrrole, pentanedioic acid diethyl ester, triphenyl phosphate, octicizer and tris (methylphenyl) phosphate.

In conclusion, the results indicate that the twenty-one Thermo-Lag samples tested are consistent in terms of chemical composition with other Thermo-Lag samples tested as part of the NEI generic testing program.

TABLE 1

Chromatographic Conditions:

30 meter 0.25 mm narrow bore fused silica HP-5 CB capillary column.

Carrier Gas: Helium, 0.9 mL/min, split ratio 35:1

Column Conditions:

Initial Temperature: 50°C for 1 minute hold

Temperature Ramp: 8°C/min to 250°C

Final Temperature: Hold at 250°C for 10 minutes

Injector Temperature: 250°C

Detector Temperature: 280°C

Detector was an HP MSD in scan mode (30-550 amu)

Pyrolysis Conditions:

Pyrolysis Temperature: 650°C

Interval: 2 seconds

Ramp: 2°C/millisecond

Probe Type: Platinum Coil

Interface Temperature: 205°C