

TEXAS UTILITIES GENERATING CO. CPSES	INSTRUCTION NUMBER	REVISION	ISSUE DATE	PAGE
	QI-QP-11.4-23	4	FEB 25 1982	1 of 5
REINSPECTION OF SEAL COATED AND FINISH COATED STEEL SUBSTRATES FOR WHICH DOCUMENTATION IS MISSING OR DISCREPANT	PREPARED BY: <i>[Signature]</i>	2/19/82 DATE		
	APPROVED BY: <i>[Signature]</i>	2-23-82 DATE		
	APPROVED BY: <i>[Signature]</i>	4/24/82 DATE		

1.0 REFERENCES

- 1-A Nonconformance Report Numbers C-81-01370 through C-81-01373 and C-81-01567
- 1-B CP-QP-18.0, "Inspection Reports"
- 1-C CCP-30, "Coating Steel Substrates Inside Reactor Buildings and Radiation Areas"
- 1-D CCP-30A, "Coating Steel Substrates Inside Reactor Buildings and Radiation Areas"
- 1-E QI-QP-11.4-1, "Inspection of Steel Substrate Surface Preparation and Primer Application"
- 1-F QI-QP-11.4-5, "Inspection of Steel Substrate Primer Repair and Seal and Finish Coat Application and Repair"

2.0 GENERAL

2.1 PURPOSE AND SCOPE

HISTORICAL FILE

This instruction shall describe methods utilized by Quality Control in the measurement of the dry film thickness (DFT) and adhesion to steel substrates of existing seal or finish coat applications described in Reference 1-A using the Mark II Tooke Gage and the Elcometer 106 Adhesion Tester respectively. The above tests are destructive in nature which will necessitate a repair of the coating system at each spot test location.

3.0 INSTRUCTION

For each seal or finish coated steel item or component for which documentation is missing or discrepant, the tests discussed in Paragraphs 3.1 and 3.2 shall be performed at the frequencies indicated therein.

8507030144 850311
PDR FOIA
HUGEB4-487 PDR

TEXAS UTILITIES GENERATING CO. CPSES	INSTRUCTION NUMBER	REVISION	ISSUE DATE	PAGE
	QI-QP-11.4-23	4	FEB 25 1997	2 of 5

3.1 TOOKE TEST (SCRATCH TEST)

The scratch test shall be performed by using a Mark II Tooke Inspection Gage using a 2X tip.

Each test made with the Tooke gage shall be compared to a reading of the total system obtained using a calibrated Elcometer Inspection DFT gage or equivalent. The reading obtained with the 2X tip of the Tooke gage shall not vary by more than ± 0.5 mils from the reading obtained with the Elcometer Inspection DFT gage. Any Tooke gage reading which is not within ± 0.5 mils of the corresponding DFT gage reading shall be discarded. (An additional Tooke gage reading shall be taken for each gage reading discarded.)

Five separate Tooke readings spaced evenly over each seal or finish coated item (See Note 1) shall be taken. Dry film thickness shall be as follows:

	<u>Any Single Reading</u>	<u>Average of Five</u>
CZ 11 Primer	1.5 - 5.5	2.0 - 5.5
D 6	1.5 - 5.5	2.0 - 5.5
Total Coating System	7.0 - 11.5	7.0 - 11.0

In the event that any reading(s) is found to be outside of the acceptable primer thickness range, additional readings shall be taken to determine the extent of the unacceptable area. Dimensions and locations of unacceptable areas and results of additional testing shall be documented in the "Remarks" section of Attachment 1.

NOTE 1: For small areas of seal or finish coated surfaces, five separate readings shall be taken. For items with less than 0.5 square feet of exposed coating, a minimum of three separate readings shall be taken. For larger seal or finish coated areas such as containment liner plate, five separate readings randomly spaced shall be taken for each 100 square feet of coating.

NOTE 2: Seal or finish coated surfaces meeting the following descriptions shall not be subject to testing with the Tooke gage:

TEXAS UTILITIES GENERATING CO. CPSES	INSTRUCTION NUMBER	REVISION	ISSUE DATE	PAGE
	QI-QP-11.4-23	4	FEB 25 1982	3 of 5

- a. Areas or items which are inaccessible due to installation of permanent items or equipment.
- b. Items that due to their size or configuration will not accomodate testing with a Tooke gage.

3.2 ADHESION (PATCH) TEST

The QC inspector shall perform an Adhesion (Patch) Test on each seal or finish coated item (See Note 1). A calibrated Elcometer 106 Adhesion Tester shall be used to verify that the minimum acceptable tensile strength of adhesion of the coating system to the steel substrate has been attained. Each test shall consist of three individual dollies tested to failure. (See Note 2 and 3 below.)

NOTE 1: For larger seal or finish coated areas such as containment building liner plate, the Inspector shall perform one test for every 500 square feet of coating.

NOTE 2: For items with total exposed surface area of 10 square feet or less, each adhesion test shall consist of only one dolly tested to failure.

NOTE 3: Seal or finish coated surfaces meeting the following descriptions shall not be subject to adhesion testing:

- a. Areas or items which are inaccessible due to installation of permanent items or equipment.
- b. Items that due to their size or configuration will not accomodate testing with an Elcometer 106 Adhesion Tester.

Acceptance Criteria:

The minimum acceptable strength per dolly shall be 200 psi.

If a dolly should fail the minimum strength criteria, the following additional adhesion testing shall be performed:

- 1) On large surface areas such as liner plate, four additional dollies shall be adhesion tested at approximately one foot from the failing dolly and spaced radially at approximately 90 degree intervals.

TEXAS UTILITIES GENERATING CO. CPSES	INSTRUCTION NUMBER	REVISION	ISSUE DATE	PAGE
	QI-QP-11.4-23	4	FEB 25 1982	4 of 5

- 2) On components with smaller surface area such as miscellaneous steel or supports (conduit, cable tray, or pipe), two additional dollies shall be adhesion tested at one foot or less from the failing dolly with one located on each side of it.

If any of the additional dollies should fail the minimum strength criteria, the test results shall be promptly reported to Civil Engineering for evaluation and resolution. Test results on the additional dollies shall be documented in the "Remarks" section of the IR.

NOTE 4: In the case in which all of the additional dollies pass the minimum strength criteria, test failures on any of the original three dollies shall still be documented as "unsatisfactory" on the IR.

3.3 DOCUMENTATION

Results of inspections per Paragraphs 3.1 through 3.2 shall be documented on Inspection Report, Attachment 1, in accordance with Reference 1-B. The completed IR shall be forwarded to the PPRV for retention. For inspections of coated containment liner surfaces, the Inspector may document one IR for each 500 square feet of surface area.

3.4 REPAIRS

Repairs of each coating area either scratch-tested or adhesion tested shall be performed in accordance with Reference 1-C or 1-D and reinspection of repaired coatings shall be in accordance with Reference 1-F.

3.5 MAPPING OF LARGE AREAS

For large areas (such as reactor containment liner plate) each IR No. and the inspection area to which the IR corresponds shall be indicated on the map drawing.

The map drawing shall be maintained by the QC Supervisor, or his designee, until the entire surface has been inspected as required. Completed map drawings shall be transmitted to the Permanent Plant Records Vault.

TEXAS UTILITIES GENERATING CO.
CPSES

INSTRUCTION
NUMBER

REVISION

ISSUE
DATE

PAGE

QI-QP-11.4-23

4

FEB 25 1982

5 of 5

Attachment 1

COMANCHE PEAK STEAM ELECTRIC STATION
INSPECTION REPORT

SHEET NO. 1 OF 1

ITEM DESCRIPTION PROTECTIVE COATINGS		IDENTIFICATION NO.		SYSTEM / STRUCTURE DESIGNATION	
SPEC. NO. AS-31	REV.	REF. Q.C. DOC. & REV. & CHANGE NO. QI-QP-11.4-23, Rev.		MEASURE OR TEST EQUIP. IDENT. NO.	
<input type="checkbox"/> IN PROCESS INSPECTION	<input type="checkbox"/> PRE INSTALLATION VERIFICATION	<input type="checkbox"/> INSTALLATION INSPECTION	<input type="checkbox"/> FINAL INSPECTION	<input type="checkbox"/> PRETEST INSPECTION	
UNSP. RESULTS					
<input type="checkbox"/> INSPECTION COMPLETED, ALL APPLICABLE ITEMS SATISFACTORY					
<input type="checkbox"/> INSPECTION COMPLETED, UNSATISFACTORY ITEMS LISTED BELOW					
ITEM NO.		INSPECTION ATTRIBUTES		QC INSPECTOR	DATE
		SEAL OR FINISH COAT			
1. Perform Tooke test per para. 3.1 to determine thickness in mils of primer and total system (document one set of readings for each 100 sq. ft. when testing Containment liner)					
RECORD:					
		1	2	3	4 5
Min. Soot Primer:					
Max. Soot Primer:					
Avg. Soot Primer:					
Min. Soot Tot. System:					
Max. Soot Tot. System:					
Avg. Soot Tot. System:					
2. Perform Adhesion test per para. 3.2.					
RECORD: Adhesion Test Strength in psi:					
Dolly #1:		Dolly #2:		Dolly #3	
REMARKS (DWGS, SPECS, ETC.)					
RELATED NCR NO.					
I.R. CLOSED <input type="checkbox"/>		DATE		SIGNATURE	
				QC INSPECTOR	