

TEXAS UTILITIES GENERATING CO. CPSES	INSTRUCTION NUMBER	REVISION	ISSUE DATE	PAGE
	QI-QP-11.4-24	1	FEB 10 1982	1 of 6

  

REINSPECTION OF PROTECTIVE COATINGS ON CONCRETE SUBSTRATES FOR WHICH DOCUMENTATION IS MISSING OR DISCREPANT	PREPARED BY: <u><i>[Signature]</i></u>	<u>2-10-82</u> DATE
	APPROVED BY: <u><i>[Signature]</i></u>	<u>2-10-82</u> DATE
	APPROVED BY: <u><i>[Signature]</i></u>	<u>2/10/82</u> DATE

# HISTORICAL FILE

## 1.0 REFERENCES

- 1-A Nonconformance Report Numbers C-81-01613 and C-81-01823
- 1-B CP-QP-18.0, "Inspection Reports"
- 1-C CCP-40, "Protective Coating of Concrete Surfaces"
- 1-D QI-QP-11.4-10, "Inspection of Concrete Substrate Surface Preparation and Coatings Application and Repair"

## 2.0 GENERAL

### 2.1 PURPOSE AND SCOPE

This instruction shall describe methods to be utilized by Quality Control in the measurement of dry film thickness (DFT) and adhesion to concrete substrates of existing concrete coating applications described in Reference 1-A using the Mark II Tooke Gage and the Elcometer 106 Adhesion Tester respectively. The above tests are destructive in nature which will necessitate a repair of the coating system at each test location. In addition, criteria for visual inspection, documentation, and mapping for each coated area to be reinspected are described.

## 3.0 INSTRUCTION

For all coated concrete surfaces for which documentation is missing or discrepant, the inspection activities discussed in Paragraphs 3.1 through 3.2 shall be performed as indicated therein.

8507080196 850311  
PDR FOIA  
HUGE84-487 PDR

TEXAS UTILITIES GENERATING CO. CPSES	INSTRUCTION NUMBER	REVISION	ISSUE DATE	PAGE
	QI-QP-11.4-24	1	FEB 10 1982	2 of 6

### 3.1 TOOKE TEST (SCRATCH TEST)

The scratch test of the REACTIC 1201 finish coat shall be performed using a Mark II Tooke Inspection Gage equipped with a 2x tip. Five separate readings spaced randomly over each finish coated area of 100 square feet or less shall be taken.

NOTE: Tooke tests are not required to be performed on areas of concrete which have not been finish coated with REACTIC 1201.

#### Acceptance Criteria

The acceptable range for dry film thickness of the REACTIC 1201 finish coat is 3 mils minimum and 12 mils maximum.

In the event that any reading(s) is found to be outside of the acceptable finish coat thickness range, additional readings shall be taken to determine the extent of the unacceptable area. Results of additional testing shall be documented in the "Remarks" section of Attachment 1.

### 3.2 ADHESION (PATCH TEST)

The QC Inspector shall perform an Adhesion (Patch) Test on each 500 square feet or less of concrete surfaces which have been previously coated with surfacer only (NUTEC 11 or 11S) or with surfacer and finish coat (REACTIC 1201). A calibrated Elcometer 106 Adhesion Tester shall be used to measure the tensile strength of adhesion of the coating to the concrete substrate. For test areas of 300 square feet or less, each test shall consist of three (3) dollies randomly spaced and tested to failure. For test areas greater than 300 square feet but less than or equal to 500 square feet, each test shall consist of one (1) dolly tested to failure for each 100 square feet or fraction thereof.

#### EXAMPLES:

1. For test area of 450 square feet, test 5 dollies to failure.
2. For test area of 350 square feet, test 4 dollies to failure.
3. For test area of 100 square feet, test 3 dollies to failure.

TEXAS UTILITIES GENERATING CO. CPSES	INSTRUCTION NUMBER	REVISION	ISSUE DATE	PAGE
	QI-QP-11.4-24	1	FEB 10 1982	3 of 6

Acceptance Criteria:

The minimum acceptable strength per dolly shall be 200 psi.

If a dolly should fail the minimum strength criteria, the following additional adhesion testing shall be performed:

Four (4) additional dollies shall be adhesion tested at approximately one foot from the failing dolly and spaced radially at approximately 90 degree intervals. If any of the additional dollies should fail the minimum strength criteria, the test results shall be promptly reported to Civil Engineering for evaluation and resolution. Test results on the additional dollies shall be documented in the "Remarks" section of the IR.

NOTE 1: In the case in which all of the additional dollies pass the minimum strength criteria, test failures on any of the original three (3) dollies shall nevertheless be documented as "unsatisfactory" on the IR.

3.3 REPAIRS

Repairs of each coated area which has been destructively tested per Sections 3.1 and 3.2 shall be performed in accordance with Reference 1-C and inspected in accordance with Reference 1-D.

3.4 DOCUMENTATION

Results of all inspections described in Sections 3.1 through 3.2 shall be documented on an Inspection Report, Attachment 1, in accordance with Reference 1-8.

3.5 MAPPING

For each IR generated in accordance with Section 3.4, a sketch shall be attached to indicate the location and size of the applicable coated concrete area (See Note 1). The individual sketches from each IR shall be used to prepare composite maps which shall cover in scope a specific room, compartment, quadrant, or cavity within the Reactor Containment Buildings. The IR number shall be transferred to the applicable area on the composite map in order to provide traceability to the IR.



TEXAS UTILITIES GENERATING CO. CPSES	INSTRUCTION NUMBER	REVISION	ISSUE DATE	PAGE
	QI-QP-11.4-24	1	FEB 10 1981	4 of 6

The composite maps shall be maintained by the QC Supervisor, or his designee, until all surfaces applicable to this instruction within a given area have been reinspected and mapped. Each completed composite map shall be transmitted to the Permanent Plant Records Vault.

NOTE 1: The following parameters (as necessary) should be considered for descriptions of test areas on the sketch.

- a. Bottom and Top Elevations (vertical and diagonal surfaces) or Elevation of Surface (horizontal surfaces).
- b. Dimensions in relation to Azimuths, column lines, reactor centerline or other components of known location.
- c. Whether concrete substrate is wall, ceiling, floor, beam or column.
- d. Quadrant, compartment, cavity or room in which inspection area is located.
- e. Unit number.
- f. Relation of surface to Cardinal Directions (i.e. North, South, etc.).



TEXAS UTILITIES GENERATING CO. CPSES	INSTRUCTION NUMBER	REVISION	ISSUE DATE	PAGE
	QI-QP-11.4-24	1	FEB 11 1987	6 of 6

ATTACHMENT 2

TOTAL NUMBER OF ALLOWABLE POINTS OF DISCONTINUITY

SURFACE AREA BEING COATED (SQ. FT.)	COND. "C" COMMERCIALY CONTINUOUS
10	5
10-50	10
50-100	20
100-500	30
500-1000	50
1000-5000	75

Gross Discontinuities - None Allowed.